Published in final edited form as:

Macromolecules. 2019 February 26; 52(4): 1536–1545. doi:10.1021/acs.macromol.8b02138.

Mobility of Polymer-Tethered Nanoparticles in Unentangled Polymer Melts

Ting Ge and Michael Rubinstein

Department of Mechanical Engineering and Materials Science, Duke University, Durham, NC 27708, USA

Abstract

A scaling theory is developed for the motion of a polymer-tethered nanoparticle (NP) in an unentangled polymer melt. We identify two types of scaling regimes depending on the NP diameter d and the size of a grafted polymer chain (tail) R_{tail} . In one type of regimes, the tethered NP motion is dominated by the bare NP, as the friction coefficient of the tails is lower than that of the less mobile particle. The time dependence of the mean square displacement (MSD) of the tethered NP $\langle r^2(t) \rangle$ in the particle-dominated regime can be approximated by $\langle r^2(t) \rangle_{bare}$ for the bare NP. In the other type of regimes, the tethered NP motion is dominated by the tails when the friction coefficient of the tails surpasses that of the particle at times longer than the crossover time τ^* . In a tail-dominated regime, the MSD $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{bare}$ only for $t < \tau^*$. $\langle r^2(t) \rangle$ of a single-tail NP for $t > \tau^*$ is approximated as the MSD $\langle r^2(t) \rangle_{tail}$ of monomers in a free tail, whereas $\langle r^2(t) \rangle$ of a multi-tail NP for $t > \tau^*$ is approximated as the MSD $\langle r^2(t) \rangle_{star}$ of the branch point of a star polymer. The time dependence of $\langle r^2(t) \rangle$ in a tail-dominated regime exhibits two qualitatively different sub-diffusive regimes. The first sub-diffusive regime for $t < \tau^*$ arises from the dynamical coupling between the particle and the melt chains. The second sub-diffusive regime for $t > \tau^*$ occurs as the particle participates in the dynamics of the tails. For NPs with loosely grafted chains, there is a Gaussian brush region surrounding the NP, where the chain strands in Gaussian conformations undergo Rouse dynamics with no hydrodynamic coupling. The crossover time τ^* for loosely grafted multi-tail NPs in a tail-dominated regime decreases as the number of tails increases. For NPs with densely grafted chains, the tails are hydrodynamically coupled to each other. The hydrodynamic radii for the diffusion of densely grafted multi-tail NPs are approximated by the sum of the particle and tail sizes.

Graphical Abstract:

1. Introduction

The mobility of particles in a polymeric viscoelastic medium is important to a broad range of applications, including the particle-based micro-rheology studies of polymer solutions^{1,2} and melts,^{3–6} the fabrication and processing of nanoparticle polymer composites,^{7,8} and the design of drug carriers moving through cells and extracellular matrices.⁹ In many cases, the particles are sticky to the surrounding chains due to the attractive interactions between the particles and polymers. For instance, nanoparticles often stick to the polymers in nanocomposites,^{10,11} and viruses and pathogens adhere to mucin molecules in the mucus defending human airways and gastrointestinal tract.¹² The attraction between particles and polymers leads to either reversible or permanent adsorption of polymers to the particles.^{13,14} The adsorbed chains tend to retard the motion of a sticky particle with respect to that of a non-sticky particle. This has ramifications for the applications relying on the mobility of particles.

In this paper we present a theoretical description of the motion of polymer-tethered nanoparticles (NPs) in an unentangled polymer melt. We consider a NP either with a single polymer chain (tail) or with multiple chains (tails) permanently end-grafted onto it. The grafted chains and the matrix chains in the melt are assumed to be chemically identical. We also assume that there is no adsorption of either grafted chains or matrix chains onto the nanoparticles. Although a single-tail NP rarely occurs in experiments, it serves as a prototype model for the study of how tethered polymers affect NP motion. The research of polymer-tethered NPs provides the first step towards understanding how NP motion is affected by the adsorption layer resulting from the attraction between NPs and surrounding polymers, as the adsorption layer can be mapped to a combination of tails and loops.^{15–17}

We demonstrate that the motion of a tethered NP in a polymer melt is determined by the competition between the dynamics of the bare NP in the polymer melt and the dynamics of the tethered polymer chains. The theory in this paper is based on the previous scaling theories of the mobility of a non-sticky NP in a polymer melt^{18,19} and of polymer dynamics.²⁰ Through the comparison of the motion of the bare NP and the dynamics of tethered polymer chains, we distinguish particle-dominated and tail-dominated scaling regimes. In a particle-dominated regime, a tethered NP moves as a bare NP, while the effects of the tethered tails on NP motion can be neglected. In a tail-dominated regime, the motion of a tethered NP is not significantly affected by the tails below a crossover time, but is dominated by the tails above the crossover time. Section 2 presents the theory for a single-tail NP in an unentangled polymer melt. Section 3 deals with a multi-tail NP in an unentangled polymer melt. Summary of the results and concluding remarks are in Section 4.

2. NP with a Single Tail

We first consider a nanoparticle (NP) with a grafted polymer chain (a tail) diffusing in an unentangled polymer melt, as illustrated in Figure 1(a). The diameter of the NP is d , and its mass is m . Kuhn lengths of the grafted chain and of the melt chains are both b . The number of Kuhn segments in the tail is N_{tail} , while the number of Kuhn segments per melt chain is N . The root mean square end-to-end size of a melt chain is $R \approx bN^{1/2}$. The root mean square

end-to-end size of the tail $R_{tail} \approx bN_{tail}^{1/2}$ for $N_{tail} < N^2$, obeying the ideal random-walk statistics. A longer tail with $N_{tail} > N^2$ is expected to swell in the melt, and $R_{tail} \approx bN$ (N_{tail}/N^2)^{3,5}, corresponding to a self-avoiding random-walk conformation of chain sections each containing N^2 Kuhn segments.²⁰ Throughout the paper, we ignore any order-unity prefactors while focusing on the scaling relations and use the sign $\approx$ to indicate equality on the scaling level.

The diffusion coefficient D quantifies the mobility of a single-tail NP. According to the Stokes-Einstein relation, D is related to the friction coefficient ζ

$$D \approx \frac{k_B T}{\zeta} \quad (1)$$

in which k_B is the Boltzmann constant and T is the absolute temperature. We determine the friction coefficient ζ on the basis of the previous scaling theories for the friction coefficients ζ_{bare} of a bare NP without the tail^{18,19} and ζ_{tail} of a free tail without the particle.²⁰ For the diffusion of a bare NP in an unentangled polymer melt,

$$\zeta_{bare} \approx \begin{cases} \eta_0 \left(\frac{d}{b}\right)^2 d \approx \zeta_0 \left(\frac{d}{b}\right)^3, & \text{for } b < d < R \\ \eta_0 \left(\frac{R}{b}\right)^2 d \approx \zeta_0 \left(\frac{R}{b}\right)^2 \left(\frac{d}{b}\right), & \text{for } d > R \end{cases} \quad (2)$$

where η_0 is the monomeric viscosity and $\zeta_0 \approx \eta_0 b$ is the monomeric friction coefficient. A small bare NP with $b < d < R$ does not experience the viscosity $\approx \eta_0 N \approx \eta_0 (R/b)^2$ of the polymer melt, but only an effective viscosity $\approx \eta_0 (d/b)^2$ corresponding to polymer chain sections whose sizes $\approx d$. In contrast, a large bare NP with $d > R$ experiences the full polymer melt viscosity $\approx \eta_0 N$ independent of d . For the diffusion of a free tail in an unentangled polymer melt,

$$\zeta_{tail} \approx \begin{cases} \zeta_0 N_{tail} \approx \zeta_0 \left(\frac{R_{tail}}{b}\right)^2, & \text{for } b < R_{tail} < Nb \\ \zeta_0 N^2 \left(\frac{R_{tail}}{Nb}\right), & \text{for } R_{tail} > Nb \end{cases} \quad (3)$$

ζ_{tail} is proportional to the number of monomers N_{tail} in the tail if the melt chains screen the hydrodynamic coupling between sections of the tail with $b < R_{tail} < Nb$. ζ_{tail} for a longer tail with $R_{tail} > Nb$ scales with the size of the tail R_{tail} due to the unscreened hydrodynamic coupling between sections of the tail.²⁰ For $R_{tail} > Nb$, the friction of the tail $\zeta_{tail} \approx \zeta_0 N^2 (R_{tail}/Nb) \approx \zeta_0 N_{tail}^{3/5} N^{4/5}$ resulting from the hydrodynamic coupling is smaller than $\zeta_{tail} \approx \zeta_0 N_{tail}$ without hydrodynamic coupling, and thus is a more favorable way of energy dissipation.

Since the bare NP is dynamically coupled to a wake of size $\approx d$ in the melt surrounding the particle, adding a small tail with $R_{tail} < d$ to the wake does not significantly change the motion of the particle with respect to that of the bare NP. As a result, the friction coefficient ζ of the single-tail NP with $R_{tail} < d$ is approximated as ζ_{bare} of a bare NP, and the mobility of the single-tail NP is dominated by the particle with $D \approx k_B T / \zeta_{bare}$. If $R_{tail} > d$, a significant portion of the tail is beyond the wake surrounding the particle. The friction coefficient of the single-tail NP is approximated as

$$\zeta \approx \zeta_{bare} + \zeta_{tail} \quad (4)$$

where ζ_{bare} and ζ_{tail} are given in Eq. 2 and Eq. 3, respectively. The diffusion coefficient for a single-tail NP is

$$D \approx \frac{k_B T}{\zeta_{bare} + \zeta_{tail}} \quad (5)$$

If $\zeta_{tail} \ll \zeta_{bare}$, the diffusion of the particle is not significantly affected by the tail, as the tail with a smaller friction coefficient is more mobile than the particle. Therefore, D is approximated as the diffusion coefficient for the bare NP

$$D \approx \frac{k_B T}{\zeta_{bare}} \approx D_{bare}, \quad \text{for } \zeta_{tail} \ll \zeta_{bare} \quad (6)$$

If ζ_{tail} is comparable to ζ_{bare} , the effects of the tail on the diffusion of the particle cannot be ignored. The expression in Eq. 5 can be used to approximate D . If $\zeta_{tail} \gg \zeta_{bare}$, the diffusion of the single-tail NP is controlled by the tail that has a higher friction coefficient. As a result, D is approximated as the diffusion coefficient for the free tail

$$D \approx \frac{k_B T}{\zeta_{tail}} \approx D_{tail}, \quad \text{for } \zeta_{tail} \gg \zeta_{bare} \quad (7)$$

For $R_{tail} > d$, the two friction coefficients ζ_{tail} and ζ_{bare} are compared to determine if the diffusion of a single-tail NP is controlled by the particle with $D_{tail} > D_{bare}$ or by the tail with $D_{tail} < D_{bare}$. Whether the combined friction coefficient ζ (Eq. 4) for a single-tail NP is dominated by ζ_{bare} or ζ_{tail} depends on d and R_{tail} . In the parameter space (d, R_{tail}) , the boundary line with $\zeta_{tail} \approx \zeta_{bare}$ separates the regions where the diffusion of the single-tail NP is controlled by the particle and the tail, respectively. The boundary line is

$$R_{tail} \approx \begin{cases} b\left(\frac{d}{b}\right)^{3/2} \approx d\left(\frac{d}{b}\right)^{1/2}, & \text{for } b < d < R \approx bN^{1/2} \\ bN^{1/2}\left(\frac{d}{b}\right)^{1/2}, & \text{for } R < d < bN \\ d, & \text{for } d > bN \end{cases} \quad (8)$$

Note that the particle and the sections of the tail are hydrodynamically coupled for $R_{tail} > d > bN$. The friction coefficient of the single-tail NP ζ is approximated as ζ_{tail} as the size or the hydrodynamic radius of the tail is larger than that of the particle. The mobility of the single-tail NP is dominated by the tail with $D \approx k_B T / \zeta_{tail}$.

On time scales shorter than the onset of terminal diffusion, the motion of a single-tail NP is quantified by the time dependence of its mean square displacement (MSD) $\langle r^2(t) \rangle$. For $R_{tail} < d$, the motion of the particle is not significantly affected by the attached tail, and therefore $\langle r^2(t) \rangle$ is approximated as the MSD of a bare NP $\langle r^2(t) \rangle_{bare}$. For $R_{tail} > d$, the MSD

$$\langle \Delta r^2(t) \rangle \approx \frac{k_B T}{\zeta(t)} t \approx \frac{k_B T}{\zeta_{bare}(t) + \zeta_{tail}(t)} t \quad (9)$$

where the time-dependent effective friction coefficient $\zeta(t)$ includes $\zeta_{bare}(t)$ for the bare NP and $\zeta_{tail}(t)$ for a chain section of $g(t)$ monomers that move coherently with each other on time scale t . Similar to Eq. 6 and Eq. 7 for terminal diffusion,

$$\langle \Delta r^2(t) \rangle \approx \frac{k_B T}{\max\{\zeta_{bare}(t) + \zeta_{tail}(t)\}} \approx \begin{cases} \frac{k_B T}{\zeta_{bare}(t)} t \approx \langle \Delta r^2(t) \rangle_{bare}, & \text{for } \zeta_{tail}(t) \ll \zeta_{bare}(t) \\ \frac{k_B T}{\zeta_{tail}(t)} t \approx \langle \Delta r^2(t) \rangle_{tail}, & \text{for } \zeta_{tail}(t) \gg \zeta_{bare}(t) \end{cases} \quad (10)$$

In Appendix A, we present the scaling results for $\langle r^2(t) \rangle_{bare}$ (Eqs. A.1, A.2, and A.6) and $\langle r^2(t) \rangle_{tail}$ (Eqs. A.7-A.10). $\langle r^2(t) \rangle_{bare}$ and $\langle r^2(t) \rangle_{tail}$ are compared in order to identify different scaling regimes for the motion of a single-tail NP with $R_{tail} > d$ in an unentangled polymer melt.

As shown in Figure 1(b), there is a particle-dominated regime below the blue solid line, where both the terminal diffusion of the single-tail NP and the motion prior to the diffusion are controlled by the particle with $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{bare}$. In the particle-dominated regime, the tail does not significantly affect the particle dynamics at all time scales. There are five different tail-dominated regimes depending on the NP size d and the tail size R_{tail} . In each regime, there is a crossover from the particle-dominated motion at shorter time scales to the tail-dominated motion as t increases. At the crossover time τ^* , $\langle r^2(\tau^*) \rangle_{bare} \approx \langle r^2(\tau^*) \rangle_{tail}$. For Regimes I-IV, the friction coefficients $\zeta_{bare}(\tau^*)$ for the bare NP and $\zeta_{tail}(\tau^*)$ for the chain section of $g(\tau^*)$ coherently moving monomers are comparable to each other. The

results of τ^* for the five tail-dominated regimes are listed in Table 1 and plotted as a function of d in Figure 2. At time scales shorter than τ^* , the single-tail NP motion is controlled by the particle. The single-tail NP behaves as a bare NP with $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{bare} < \langle r^2(t) \rangle_{tail}$. The time dependence of $\langle r^2(t) \rangle_{bare}$ is $\langle r^2(t) \rangle_{bare} \sim t^2$ for the ballistic particle motion at time scales shorter than the ballistic time τ_{bal} , $\langle r^2(t) \rangle_{bare} \sim t^{1/2}$ for the sub-diffusive motion resulting from the coupling to the Rouse dynamics of the melt chains at time scales between τ_{bal} and the diffusion time τ_d , and $\langle r^2(t) \rangle_{bare} \sim t$ for the diffusive particle motion at time scales between τ_d and τ^* . The three distinctive time dependences of $\langle r^2(t) \rangle$ for $t < \tau^*$ are sketched in Figure 3 for the five regimes. At time scales longer than τ^* , the dynamics of the tail dominates the single-tail NP motion. The particle follows the tail dynamics, and $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{tail} < \langle r^2(t) \rangle_{bare}$. For Regimes I and III with $b < R_{tail} < bN$, the particle participates in the Rouse dynamics of the tail with $\langle r^2(t) \rangle_{tail} \sim t^{1/2}$ at time scales between τ^* and the Rouse time $\tau_{R,tail}$, and then diffuses with $\langle r^2(t) \rangle_{tail} \sim t$ for $t > \tau_{R,tail}$. The sub-diffusive motion with $\langle r^2(t) \rangle \sim t^{1/2}$ occurs in two time ranges, as shown in Figure 3(a). The first one for $\tau_{bal}^I(\tau_{bal}^{III}) < t < \tau_d^I(\tau_d^{III})$ results from the coupling between the NP motion and the Rouse dynamics of surrounding polymers in the melt. The second one in $\tau_I^*(\tau_{III}^*) < t < \tau_{R,tail}$ arises from the Rouse relaxation modes of the tail. For Regimes II, IV, and V with $R_{tail} > bN$, the motion of the tail changes from Rouse dynamics with $\langle r^2(t) \rangle_{tail} \sim t^{1/2}$ to Zimm dynamics with $\langle r^2(t) \rangle_{tail} \sim t^{2/3}$ at the crossover time τ_T . Whether a particle participates in the Rouse dynamics of such a long tail depends on whether τ^* is smaller than τ_T . As shown in Figure 3(b), a particle in Regime II or IV participates in the Rouse dynamics for $\tau_{II}^*(\tau_{IV}^*) < t < \tau_T$ and then the Zimm dynamics for $\tau_T < t < \tau_{Z,tail}$, whereas a particle in Regime V only participates in the Zimm dynamics for $\tau_V^* < t < \tau_{Z,tail}$. The single-tail NP finally diffuses with $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{tail} \sim t$ for $t > \tau_{Z,tail}$. The details of the calculation of $\langle r^2(t) \rangle$ and the features of $\langle r^2(t) \rangle$ for different regimes are presented in Appendix A.

3. NP with Multiple Tails

A NP with multiple grafted chains is illustrated in Figure 4(a). The conformations of the tails grafted to the NP are similar to the conformations of the arms in the outer part (the part excluding the inner region of size $\approx d$) of a star polymer in the same melt, as shown in Fig. 4 (b). Previously, scaling theories^{21–24} have been developed to describe the static properties of an isolated star polymer with z arms and N_a monomers per arm dissolved in a melt of chemically identical linear chains with N monomers per chain. Below we first briefly review the existing theories for the conformations of star polymers and then develop a new scaling theory for the mobility of a multi-tail NP on the basis of mapping a multi-tail NP to a star polymer.

According to the scaling theories,^{21–24} the radius and the structure of a star polymer in a melt depend on the number of arms z and the number of monomers N_a per arm, as shown in Figure 5. For a loosely branched star with $1 < z < N^{1/2}$ arms, the radius of the star

$$R_{star} \approx \begin{cases} b(zN_a)^{1/3}, & \text{for } N_a < z^2 \\ bN_a^{1/2}, & \text{for } z^2 < N_a < (N/z)^2 \\ bN_a^{3/5}(z/N)^{1/5} & \text{for } N_a > (N/z)^2 \end{cases} \quad (11)$$

If the arms are short with $N_a < z^2$, the star is dry with almost no mixing with the melt chains, i.e., the volume fraction of monomers belonging to the star ≈ 1 . The arms of the dry star and the arm strands in the dry core of a larger star are stretched with respect to their ideal Gaussian sizes. The stretching is due to the steric hindrance between all the arms originating from the same branch point, as illustrated in Fig. 5(c). The radius of the dry star $R_{star} \sim (zN_a)^{1/3}$. If $z^2 < N_a < (N/z)^2$, the star consists of a brush corona surrounding a dry core of size $\approx bz$, which contains z^2 monomers per arm. Chain segments in the brush corona adopt ideal random-walk conformations, as the excluded volume interactions between the arms are almost screened by the melt chains. Such a Gaussian brush with $R_{star} \sim N_a^{1/2}$ is illustrated in Fig. 5(d). If the arms are long with $N_a > (N/z)^2$, the brush corona covering the dry core contains an inner Gaussian brush and an outer brush where chain segments adopt swollen conformations. The size of the Gaussian brush region $\approx bN/z$, which corresponds to $(N/z)^2$ monomers per arm. The overall star radius $R_{star} \sim N_a^{3/5}(z/N)^{1/5}$. For $(N/z)^2 < N_a < N^2 z^{1/2}$, there are multiple chain sections of Gaussian conformations in a correlation blob of a swollen brush, as shown in Fig. 5(e). Multiple chain sections are required to make the overall excluded volume interaction of a chain strand in a correlation blob $\approx k_B T$, because the excluded volume interactions are partially screened by the melt chains. For $N_a > N^2 z^{1/2}$, there is also a swollen brush with multiple chain sections per correlation blob at intermediate distances $bN/z < r < bNz^{1/2}$ from the branch point. However, each correlation blob at $r > bNz^{1/2}$ contains only one chain section, as shown in Fig. 5(f). The chain section in a blob adopts a swollen conformation as the blob size $\xi(r) \approx r/z^{1/2}$ is larger than the thermal blob size $\approx bN$ for $r > bNz^{1/2}$. The brush structure for $r > bNz^{1/2}$ can be described using the model proposed by Daoud and Cotton.²¹ The Daoud-Cotton brush corona only exists in a star polymer with $N_a > N^2 z^{1/2}$. The locations of different regions along the radial axis of a loosely branched star with sufficiently long arms are shown in Fig. 5(a).

For a densely branched star with $z > N^{1/2}$, the radius of the star

$$R_{star} \approx \begin{cases} b(zN_a)^{1/3}, & \text{for } N_a < z^{1/2}N^{3/4} \\ bN_a^{3/5}(z/N)^{1/5}, & \text{for } N_a > z^{1/2}N^{3/4} \end{cases} \quad (12)$$

If the arms are short with $N_a < z^{1/2}N^{3/4}$, the star is dry with $R_{star} \sim (zN_a)^{1/3}$. If the arms are long with $N_a > z^{1/2}N^{3/4}$, the star consists of a dry core surrounded by a brush corona. The size of the core $\approx bz^{1/2}N^{1/4}$, corresponding to $z^{1/2}N^{3/4}$ monomers per arm, while the overall star radius $R_{star} \sim N_a^{3/5}(z/N)^{1/5}$. As in a loosely branched star, the Daoud-Cotton brush exists in a densely branched star only for $N_a > N^2 z^{1/2}$. The locations of different regions along the

radial axis of a densely branched star with $N_a > N^2 z^{1/2}$ are shown in Fig. 5(b). Unlike the brush corona of a loosely branched star, the brush corona of a densely branched star does not contain a Gaussian brush region. There is no intermediate range of N_a for which the star contains a dry core and a Gaussian brush corona, because the screening by the melt chains is not strong enough to reduce the overall excluded volume interaction between all densely branched arms below $k_B T$ per arm.

We develop a scaling theory for the motion of a multi-tail NP in an unentangled polymer melt by considering a star polymer with z arms and arm length $N_a \approx N_{tail}$ in the same melt (see Fig. 4). Similar to the motion of a single-tail NP, the motion of a multi-tail NP is significantly affected by the tails only if $R_{tail} > d$. Therefore, below we only describe the motion of a multi-tail NP with $R_{tail} > d$. The motion of a multi-tail NP with $R_{tail} < d$ can be approximated as that of a bare NP.

3.1 Loosely Grafted Tails with $1 < z < N^{1/2}$

If the grafted tails are short with $d < R_{tail} < bz$, a multi-tail NP corresponds to a dry star polymer. The size of this multi-tail NP $\approx R_{tail} \approx bN_{tail}^{1/3} z^{1/3}$ (see Eq. 11 for a dry star with $N_a < z^2$). As demonstrated in Appendix B, although the position of the particle fluctuates under the confinement of the grafted dry tails, the motion of the multi-tail NP can be approximated as that of a larger particle with diameter $\approx R_{tail}$ in the matrix of melt chains. This tail-dominated regime with $d < R_{tail} < bz$ is indicated as Regime VI of the (d, R_{tail}) parameter space in Fig. 6.

A multi-tail NP with intermediate tail size in the range $\max\{d, bz\} < R_{tail} < bN/z$ corresponds to a star polymer consisting of a dry core and a Gaussian brush corona. The size of the multi-tail NP is $\approx R_{tail} \approx bN_{tail}^{1/2}$ (see Eq. 11 for a star with $z^2 < N_a < (N/z)^2$). If $d < bz$, the multi-tail NP motion is controlled by the tails, as the particle and the dry portions of the tails move together as a larger particle with diameter $\approx bz$. This corresponds to Regime VII in Fig. 6. The MSD of the multi-tail NP in this regime is $\langle r^2(t) \rangle \approx (b^2/z)(t/\tau_0)^{1/2}$ for $t < \tau_0 z^4$ (substitute R_{tail} by bz in Eq. B.1). Note that $\tau_0 z^4$ is the Rouse time of a segment containing z^2 monomers in the dry core of a star polymer. At times longer than $\tau_0 z^4$, $\langle r^2(t) \rangle$ is approximately the same as $\langle r^2(t) \rangle_{star}$ of the branch point of a Gaussian star. If $d > bz$, the tails do not contain any dry portions. Whether the multi-tail NP motion is controlled by the particle or the tails in the Gaussian brush depends on the competition of the friction coefficients of the bare particle and the tails. The friction coefficient of the bare particle ζ_{bare} is given in Eq. 2. The friction coefficient of the tails $\approx z\zeta_{tail}$, where $\zeta_{tail} \approx \zeta_0 N_{tail} \approx \zeta_0 (R_{tail}/b)^2$ is the friction coefficient of a single tail undergoing Rouse dynamics. The friction coefficients for individual tails are additive due to the absence of hydrodynamic coupling between the tails. The overall friction coefficient of the multi-tail NP is approximated as

$$\zeta \approx \zeta_{bare} + z\zeta_{tail}, \quad \text{for } 1 < z < N^{1/2} \quad \text{and} \quad bz < d < R_{tail} < bN/z \quad (13)$$

ζ is dominated by the larger of the two contributions ζ_{bare} and $z\zeta_{tail}$. In the parameter space (d, R_{tail}) , the boundary line separating the regions where the diffusion of a multi-tail NP is dominated respectively by the particle and the Gaussian brush is

$$R_{tail} \approx \begin{cases} \frac{b}{z^{1/2}} \left(\frac{d}{b} \right)^{3/2}, & \text{for } zb < d < R \approx bN^{1/2} \\ \frac{bN^{1/2}}{z^{1/2}} \left(\frac{d}{b} \right)^{1/2}, & \text{for } R < d < bN/z \end{cases} \quad (14)$$

as indicated by the blue solid line in Fig. 6. Two regimes, which are indicated as Regimes I and III in Fig. 6, exist in the tail-dominated region with $bz < d < R_{tail} < bN/z$. Regimes I and III for multi-tail NP motion are similar to their counterparts for single-tail NP motion (see Fig. 1(b)). The time dependence of $\langle r^2(t) \rangle$ is similar to that in the corresponding regime for single-tail NP motion (Fig. 3(a)). However, the crossover time τ^* for multi-tail NP motion is reduced with respect to the corresponding τ^* for single-tail NP motion, as shown in Table 2 and Figure 2. The earlier crossover to the tail-dominated motion reflects the enhanced friction coefficient of multiple tails compared to that of a single tail. For $t > \tau^*$, the multi-tail NP MSD $\langle r^2(t) \rangle$ is approximately equal to the MSD $\langle r^2(t) \rangle_{star}$ of the branch point of a Gaussian star polymer.

For sufficiently long tails with $R_{tail} > \max\{d, bN/z\}$, a multi-tail NP corresponds to a star polymer consisting of a dry core, an intermediate Gaussian brush, and an outer brush corona ("hairy" NP). The size of the multi-tail NP is $\approx R_{tail} \approx bN_{tail}^{3/5}(z/N)^{1/5}$ (see Eq. 11 for a star with $N_a > (N/z)^2$). In a star polymer with arms forming either a swollen brush corona (Fig. 5(e)) or a Daoud-Cotton brush corona (Fig. 5(f)) covering a swollen brush, hydrodynamical coupling between the arms affects the the branch point motion for t above the Rouse time $\approx \tau_0(N/z)^4$ of a strand in the Gaussian brush. In particular, the arms are hydrodynamically coupled for the terminal diffusion of the star. Likewise, a multi-tail NP with $R_{tail} > \max\{d, bN/z\}$ diffuses in the melt with the NP and the tails hydrodynamically coupled. The hydrodynamic radius of the multi-tail NP can be approximated by the sum of R_{tail} and d , which is dominated by $R_{tail} > d$. The multi-tail NP experiences the melt viscosity $\eta_0 N$, as its size $\approx R_{tail} > bN/z$ is larger than the melt chain size $R \approx bN^{1/2}$. The diffusion coefficient of the multi-tail NP is $D \approx k_B T / (\eta_0 N R_{tail})$. There are four regimes in the tailed-dominated region with $R_{tail} > bN/z$, which are indicated as Regimes II, IV, V, and VIII in Fig. 6. Regimes II, IV, and V for multi-tail NP motion are similar to their counterparts for single-tail NP motion (see Fig. 1(b) for the regimes and Fig. 3(b) for the sketch of $\langle r^2(t) \rangle$). However, the crossover time τ^* is reduced as shown in Table 2 and Figure 2. The time for the crossover from Rouse dynamics to Zimm dynamics of the hydrodynamically coupled tails is also reduced from $\tau_T \approx \tau_0 N^4$ for a single tail to $\tau_T \approx \tau_0 (N/z)^4$, which is the Rouse time of a chain segment containing $(N/z)^2$ monomers in the Gaussian star brush (Fig. 5(d)). In Regime VIII, the particle with $d < bz$ and the dry portions of the tails move as a larger particle with diameter $\approx bz$, and thus the multi-tail NP motion is controlled by the tails. As in Regime VII, the multi-tail NP MSD $\langle r^2(t) \rangle \approx (b^2/z)(t/\tau_0)^{1/2}$ for $t < \tau_0 z^4$. At time scales

above $\tau_0 z^4$, $\langle r^2(t) \rangle$ is approximately the same as $\langle r^2(t) \rangle_{star}$ of the branch point of the corresponding star polymer.

3.2 Densely Grafted Tails with $z > N^{1/2}$

If the grafted tails are short with $d < R_{tail} < bz^{1/2}N^{1/4}$, a densely grafted multi-tail NP corresponds to a dry star in the same melt (see Eq. 12 for $N_a < z^{1/2}N^{3/4}$). The multi-tail NP motion is similar to that in Regime VI for loosely grafted multi-tail NPs (see Fig. 6). It is controlled by the tails, as the particle and the dry tails move together as a larger particle with diameter $\approx R_{tail}$. More detailed analysis is presented in Appendix B. The MSD of a multi-tail NP before the terminal diffusion in this regime is given in Eq. B.2.

A densely grafted multi-tail NP with long tails of size $R_{tail} > \max\{d, bz^{1/2}N^{1/4}\}$ corresponds to a star consisting of a dry core and a brush corona (either a swollen brush or Daoud-Cotton brush covering a swollen brush). The particle and the tails are hydrodynamically coupled for the diffusion of the multi-tail NP. The hydrodynamic radius can be approximated by the sum of the tail size R_{tail} and the particle size d , and is dominated by $R_{tail} > d$. The viscosity experienced by the multi-tail NP is the melt viscosity ηN , as $R_{tail} > bz^{1/2}N^{3/4}$ is larger than the melt chain size $R \approx bN^{1/2}$. The diffusion coefficient is $D \approx k_B T / (\eta N R_{tail})$.

Various aspects of the dynamics of grafted nanoparticles in polymer matrices have been studied experimentally, such as the effects of temperature,^{25,26} morphology of particles in aggregated state,²⁷ and grafted polymer chains.^{28,29} We compare the theory developed in this paper with one experimental study that focused on the effects of grafted polymers.²⁹ In this study, the center-of-mass diffusion of Fe_3O_4 NPs densely grafted with PMMA chains in an unentangled PMMA melt was measured using Rutherford backscattering spectrometry (RBS).²⁹ In one set of experiments, Fe_3O_4 NPs with diameter $d = 4.3 nm$ were grafted with PMMA chains and dispersed in a melt of PMMA chains with molecular weight $M_w = 14 kg/mol$, which corresponds to $N = 26$ Kuhn monomers of size $b = 1.53 nm$.³⁰ There were three samples with grafting density $\sigma = 0.55 chains/nm^2$, $0.33 chains/nm^2$, and $0.17 chains/nm^2$. The number of grafted tails per NP is $z = \pi d^2 \sigma = 32, 19$, and 10 , and the corresponding number of Kuhn monomers per tail is $N_{tail} = 30, 39$, and 39 . We refine the criterion for a loosely grafted NP in a melt matrix and show that the NPs in all three samples are indeed not loosely grafted. The criterion $z < N^{1/2}$ for a loosely grafted NP corresponds to the existence of a Gaussian star with $R_{star} \approx bN_a^{1/2}$ for $z^2 < N_a < (N/z)^2$, as shown in Eq. 11. A strand with less than z^2 Kuhn monomers from the branch point is located in the dry core, while a strand with more than $(N/z)^2$ Kuhn monomers from the branch point goes beyond the Gaussian region and becomes swollen. The expression for the size of a dry star $R_{star} \approx b(zN_a)^{1/3}$ for $N_a < z^2$ (Eq. 11) is refined by considering that the volume of a Kuhn monomer is not b^3 but more precisely ba^2 , where a is the thickness of a Kuhn monomer. The refined expression is $R_{star} \approx a^{2/3}b^{1/3}(zN_a)^{1/3}$ for $N_a < z^2(a/b)^4$. The refined criterion for the existence of a Gaussian star is $z^2(a/b)^4 < N_a < (N/z)^2$, which requires $z < (b/a)N^{1/2}$. Accordingly, the refined criterion for a loosely grafted NP is $z < (b/a)N^{1/2}$. For the three samples in the experiments, the volume of a monomer is $v = 0.149 nm^3$, the molecular weight of a monomer is $M_0 = 0.1 kg/mol$, the molecular weight of a Kuhn monomer is $M_k = 0.54 kg/mol$, and hence the thickness of a Kuhn monomer is $a = (M_k v / M_0 b)^{1/2} = 0.73 nm$. The refined criterion

for loose grafting in the experiments is $z < (b/a)N^{1/2} = 11$. As a result, the NPs with $z = 32$ and 19 are densely grafted, while the NPs with $z = 10$ are in the crossover from loosely to densely grafted regimes. Next we estimate the structure of the grafted NPs in the experiments. Suppose a strand in the dry layer surrounding the particle contains x Kuhn monomers, then x satisfies $(4\pi/3)(d/2)^3 + zx(ba^2) = (4\pi/3)(d/2 + x^{1/2}b)^3$. Note that the contribution of the particle volume to the dry core volume is considered. For the NPs with $(z, N_{tail}) = (32, 30)$, $(19, 39)$, and $(10, 39)$, we obtain $x = 0$, meaning that the dry core consists only of the particle. The overall size of a grafted NP is approximated by the size of a swollen star $R_{star} \approx bN_a^{3/5}(z/N)^{1/5}$ with $N_a \approx N_{tail}$. For $(z, N_{tail}) = (32, 30)$, $(19, 39)$, and $(10, 39)$, the estimated overall size $\approx 12.3nm$, $12.9nm$, and $11.4nm$. Experiments found that the hydrodynamic radii of the NPs in the three samples $R_H \approx 10nm$.²⁹ This result roughly agrees with the estimated overall size of the densely grafted NPs, supporting the scaling description that the hydrodynamic radius R_H of a densely grafted NP with $R_{tail} > d$ is dominated by R_{tail} . Note that hydrodynamic interactions in a semi-dilute polymer solution are screened on a length scale comparable to that for the screening of the intermolecular interactions. The melt chains drain through the grafted polymer brush on the length scale of the last correlation blob size ζ_{last} (see Figure 5). As a result, $R_H \approx R_{tail} - C_\zeta \zeta_{last}$ where C_ζ is a numerical coefficient of order unity.³¹

Below we discuss the extension of the experiments to single-tail NPs and loosely grafted multi-tail NPs. Consider a Fe_3O_4 NP with $d = 4.3nm$ in a melt of PMMA chains with $N = 26$ Kuhn monomers per chain and chain size $R \approx bN^{1/2} = 7.8nm$. A single grafted PMMA chain would control the motion of the Fe_3O_4 particle if the grafted chain size $R_{tail} > b(d/b)^{3/2} \approx 7.2nm$ or the number of Kuhn monomers in the chain $N_{tail} > 22$, according to Eq. 8 for a single-tail NP with $b < d < R$. At $N_{tail} = 22$, the friction coefficients ζ_{tail} and ζ_{bare} of the PMMA tail and the bare Fe_3O_4 particle are almost the same. Therefore, the diffusion coefficient of a single tail NP with $N_{tail} = 22$ is about half of that of a bare NP without the tail. For multiple grafted PMMA chains, the condition for loose grafting is $z < (b/a)N^{1/2} = 11$. If $z = 6$ PMMA chains were loosely grafted to a NP, no PMMA chains are in the dry core (as in the more densely grafted cases with $z = 10, 19$, and 32). The PMMA chains with less than $(N/z)^2 = 19$ Kuhn monomers per chain form a Gaussian brush. There is no hydrodynamic coupling between the tails in the Gaussian brush, and the overall friction coefficient of the tails is $6\zeta_{tail}$. For $d = 4.3nm < R = 7.8nm$, the $z = 6$ chains would control the motion of the Fe_3O_4 particle if $R_{tail} > b(d/b)^{3/2}/z^{1/2} \approx 2.9nm$ or $N_{tail} > 4$, according to Eq. 14 for a NP grafted with a Gaussian brush. At $N_{tail} = 4$, the friction coefficient of the Gaussian brush $6\zeta_{tail}$ is comparable to that of the bare particle ζ_{bare} , and therefore reduces the diffusion coefficient of the particle by 50% with respect to that of the bare particle.

4. Conclusions

We study the motion of a polymer-tethered NP in a polymer melt using scaling analysis. For a single-tail NP in an unentangled polymer melt, the friction coefficient $\zeta(t)$ for the single-tail NP includes the contributions $\zeta_{bare}(t)$ from the bare NP and $\zeta_{tail}(t)$ from the tail. The competition between $\zeta_{bare}(t)$ and $\zeta_{tail}(t)$ determines whether the single-tail NP motion is dominated by the bare NP or the tail. In the particle-dominated regime, $\zeta(t) \approx \zeta_{bare}(t) >$

$\zeta_{tail}(t)$, and the mean squared displacements of the tailed NP $\langle r^2(t) \rangle$ is approximated as $\langle r^2(t) \rangle_{bare}$ for the bare NP. In a tail-dominated regime, $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{bare}$ for t smaller than a crossover time τ^* , but $\langle r^2(t) \rangle$ is approximated as the MSD of monomers in the tail $\langle r^2(t) \rangle_{tail}$ for $t > \tau^*$, as $\zeta(t) \approx \zeta_{tail}(t) > \zeta_{bare}(t)$ for $t > \tau^*$. We construct a diagram of regimes (Figure 1(b)) to show the particle-dominated regime and various tail-dominated regimes in the parameter space (d, R_{tail}) . The tail-dominated regimes differ in the tail dynamics that controls the single-tail NP motion (see Figure 3) and the crossover time τ^* at which the tail-dominated motion begins (see Table 1).

The model of a multi-tail NP in an unentangled polymer melt can be mapped onto a corresponding star polymer in the same melt. A Gaussian brush region where chain segments adopt ideal random-walk conformations exists for loosely grafted tails with $1 < z < N^{1/2}$, but is absent for densely grafted tails with $z > N^{1/2}$. For loosely grafted short tails with $d < R_{tail} < bz$, a multi-tail NP corresponds to a dry star diffusing in the melt with hydrodynamic radius $\approx R_{tail}$. With intermediate grafted chain size $bz < R_{tail} < bN/z$, a loosely grafted multi-tail NP corresponds to a star with a dry core (Fig. 5(c)) and a Gaussian brush corona (Fig. 5(d)). Similar to the motion of a single-tail NP, the motion of such a multi-tail NP can be in the particle-dominated regime or one of many tail-dominated regimes in the parameter space (d, R_{tail}) (see Figure 6). If the tails are sufficiently long with $R_{tail} > bN/z$, a loosely grafted multi-tail NP corresponds to a star with either a swollen brush corona (Fig. 5(e)) or a swollen brush surrounded by Daoud-Cotton brush corona (Fig. 5(f)). For the diffusion of such a multi-tail NP, the particle and the tails are hydrodynamically coupled. The tails with $R_{tail} > d$ control the diffusion of the multi-tail NP, as R_{tail} dominates the hydrodynamic radius approximated by $R_{tail} + d$. The crossover time τ^* for a tail-dominated regime of multi-tail NP motion is reduced with respect to the counterpart for single-tail NP motion (see Table 2 and Fig. 2). For densely grafted tails with $z > N^{1/2}$, depending on the grafted chain size, a multi-tail NP corresponds to either a dry star or a star consisting of a dry core and a brush corona with no Gaussian region. In both scenarios, the densely grafted multi-tail NP diffuses in the melt with the hydrodynamic radius $\approx R_{tail} + d$, which is dominated by R_{tail} for $R_{tail} > d$.

In conclusion, our scaling theory for the mobility of polymer-tethered NPs in polymer melts demonstrates the interplay between the dynamics of the bare NP and the dynamics of the tethered polymer tails. The theory can be extended to polymer-tethered NPs in entangled polymer melts. As in unentangled polymer melts, the mobility of tethered particles in entangled polymer melts is dominated by the lower of the two mobilities: of the bare particle or of the tails. Bare particles with sizes smaller than the entanglement mesh size a behave essentially the same as those in unentangled polymer melts. However, the mobility of particles is significantly reduced as the particle size exceeds the tube diameter a of the melt. While sufficiently large particles are confined by the entanglement network with the mobility determined by the melt viscosity, particles only moderately larger than a can diffuse through the hopping mechanism and exhibit mobility higher than the prediction of the Stokes-Einstein relation.¹⁹ For a single-tail NP, the particle participates in the reptation dynamics of the long tail if the tail has a lower mobility. For a multi-tail NP, the mobility of the tails can be approximated as that of a star polymer undergoing arm retraction in the same melt. The lower of the mobility of the bare particle and the corresponding star polymer

determines the mobility of the multi-tail NP. Detailed theoretical description of the mobility of tethered-NPs in entangled polymer melts will be presented in a future publication. One can also extend the present theory to study the the mobility of a NP with an adsorption layer in a polymer melt by describing the adsorption layer as loops and tails.^{15–17} Furthermore, the theory can be generalized to investigate the motion of a NP with reversibly grafted or adsorbed polymer chains.

Acknowledgement

We acknowledge financial support from National Science Foundation under Grants DMR-1121107 and EFMA-1830957, the National Institutes of Health under Grants P01-HL108808, R01-HL136961, and 5UH3HL123645, and the Cystic Fibrosis Foundation.

Appendix

A. MSD of a Single-Tail NP in an Unentangled Polymer Melt

The MSD $\langle r^2(t) \rangle_{bare}$ of a bare non-sticky NP in an unentangled polymer melt has been calculated using scaling theory.¹⁸ The results of $\langle r^2(t) \rangle_{bare}$ are shown in Figure A.1(a). The first scaling regime

$$\langle \Delta r^2(t) \rangle_{bare} \approx \frac{k_B T}{m} t^2, \text{ for } t < \tau_{bal} \quad (\text{A.1})$$

corresponds to the ballistic motion of the bare NP at time scales shorter than the ballistic time τ_{bal} . Subsequent scaling regimes describe the thermal motion of the NP. The subdiffusive regime with

$$\langle \Delta r^2(t) \rangle_{bare} \approx \left(\frac{b^3}{d} \right) \left(\frac{t}{\tau_0} \right)^{1/2}, \text{ for } \tau_{bal} < t < \tau_d \quad (\text{A.2})$$

results from the coupling between the NP motion and the Rouse dynamics of the unentangled polymers up to the diffusion time τ_d . Matching Eq. A.1 and Eq. A.2, one obtains the ballistic time as the crossover time between the ballistic and sub-diffusive regime

$$\tau_{bal} \approx \tau_0 \left(\frac{mb}{\zeta_0 \tau_0 d} \right)^{2/3} \quad (\text{A.3})$$

where ζ_0 is the monomeric friction coefficient and

$$\tau_0 \approx \frac{\zeta_0 b^2}{k_B T} \quad (\text{A.4})$$

is the monomer relaxation time. The sub-diffusion of a NP with $b < d < R$ is coupled to the relaxation of chain segments with sizes up to d , while the sub-diffusion of a NP with $d > R$ is coupled to the relaxation of the entire polymer chain. As a result, the diffusion time for the onset of Brownian motion of a NP is

$$\tau_d \approx \begin{cases} \tau_0 \left(\frac{d}{b}\right)^4 \approx \tau_R \left(\frac{d}{R}\right)^4, & \text{for } b < d < R \\ \tau_R, & \text{for } d > R \end{cases} \quad (\text{A.5})$$

where $\tau_R \approx \tau_0 N^2 \approx \tau_0 (R/b)^4$ is the Rouse relaxation time of the polymer melt. The final scaling regime with $t > \tau_d$ corresponds to NP diffusion with MSD increasing linearly with time

$$\langle \Delta r^2(t) \rangle_{bare} \approx \begin{cases} \frac{b^3}{Nd} \left(\frac{R}{d}\right)^2 \left(\frac{t}{\tau_0}\right), & \text{for } b < d < R \\ \frac{b^3}{Nd} \left(\frac{t}{\tau_0}\right), & \text{for } d > R \end{cases} \quad (\text{A.6})$$

The MSD $\langle \Delta r^2(t) \rangle_{tail}$ of monomers in a linear polymer containing N_{tail} monomers is obtained based on scaling models for the dynamics of unentangled polymers.²⁰ Scaling descriptions of $\langle \Delta r^2(t) \rangle_{tail}$ are presented in Figure A.1(b). A shorter polymer with $N_{tail} < N^2$ relaxes by Rouse dynamics, and

$$\langle \Delta r^2(t) \rangle_{tail} \approx b^2 \left(\frac{t}{\tau_0}\right)^{1/2}, \quad \text{for } N_{tail} < N^2 \text{ and } \tau_0 < t < \tau_{R,tail} \quad (\text{A.7})$$

where $\tau_{R,tail} \approx \tau_0 N_{tail}^2$ is the Rouse time. The shorter polymer finally diffuses with

$$\langle \Delta r^2(t) \rangle_{tail} \approx R_{tail}^2 \left(\frac{t}{\tau_{R,tail}}\right) \approx b^2 N_{tail} \left(\frac{t}{\tau_{R,tail}}\right), \quad \text{for } N_{tail} < N^2 \text{ and } t > \tau_{R,tail} \quad (\text{A.8})$$

Figure A.1:

(a) MSD $\langle \Delta r^2(t) \rangle_{bare}$ of a bare NP with $d < R$ (blue solid line) and $d > R$ (magenta dotted line) in a melt of unentangled polymers with chain size R . (b) MSD $\langle \Delta r^2(t) \rangle_{tail}$ for monomers in an unattached (free) tail polymer with $N_{tail} < N^2$ (green dotted line) and $N_{tail} > N^2$ (red solid line) in a melt of unentangled polymers with N monomers per chain.

A longer polymer with $N_{tail} > N^2$ first relaxes by Rouse dynamics until $\tau_T \approx \tau_0 N^4$, which is the relaxation time of a chain segment containing N^2 monomers, and then relaxes by Zimm dynamics until the Zimm time $\tau_{Z, tail} \approx \tau_T (N_{tail}/N^2)^{9/5}$. Zimm dynamics occurs at time scales $t > \tau_T$, as the hydrodynamics coupling between sections of the long polymer can no longer be screened by the shorter melt chains. For the Rouse dynamics and the subsequent Zimm dynamics, the MSD of monomers is

$$\langle \Delta r^2(t) \rangle_{tail} \approx \begin{cases} b^2 \left(\frac{t}{\tau_0} \right)^{1/2}, & \text{for } N_{tail} > N^2 \text{ and } \tau_0 < t < \tau_T \\ b^2 N^2 \left(\frac{t}{\tau_T} \right)^{2/3}, & \text{for } N_{tail} > N^2 \text{ and } \tau_T < t < \tau_{Z, tail} \end{cases} \quad (\text{A.9})$$

Finally, the long polymer diffuses with

$$\langle \Delta r^2(t) \rangle_{tail} \approx R_{tail}^2 \left(\frac{t}{\tau_{Z, tail}} \right) \approx b^2 N^2 \left(\frac{N_{tail}}{N^2} \right)^{6/5} \left(\frac{t}{\tau_{Z, tail}} \right), \text{ for } N_{tail} > N^2 \text{ and } t > \tau_{Z, tail} \quad (\text{A.10})$$

For $d < R_{tail} < bN$, the MSD $\langle \Delta r^2(t) \rangle$ of a single-tail NP is obtained based on the approximation in Eq. 10. Below we describe the time dependence of $\langle \Delta r^2(t) \rangle$ for different tail-dominated scaling regimes in the (d, R_{tail}) parameter space (see Figure 1(b)).

Regime I:

Small NP with $b < d < R$ and Long tail with $b(d/b)^{3/2} < R_{tail} < bN$ (SL). The time dependence of $\langle \Delta r^2(t) \rangle$ in Regime I is shown by the blue dashed line in Figure 3(a). $\langle \Delta r^2(t) \rangle \approx \langle \Delta r^2(t) \rangle_{bare} \sim t^2$ (Eq. A.1) for $t < \tau_{bal}$, $\sim t^{1/2}$ (Eq. A.2) for $\tau_{bal} < t < \tau_d^I$, and $\sim t$ (Eq. A.6)

for $\tau_d^I < t < \tau_f^*$. Subsequently, $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{tail} \sim t^{1/2}$ (Eq. A.7) for $\tau_f^* < t < \tau_{R,tail}$ and $\sim t$ (Eq. A.8) for $t > \tau_{R,tail}$.

Regime II:

Small NP with $b < d < R$ and Very long tail with $R_{tail} > bN$ (SV). The time dependence of $\langle r^2(t) \rangle$ in Regime II is shown by the magenta dashed line in Figure 3(b). The crossover time $\tau_{II}^* \approx \tau_f^*$ (see Table 1), and the time dependence of $\langle r^2(t) \rangle$ for $t < \tau_{II}^*$ in Regime II is identical to that for $t < \tau_f^*$ in Regime I. Above the crossover time, $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{tail} \sim t^{1/2}$ and $\sim t^{2/3}$ (Eq. A.9) for $\tau_{II}^* < t < \tau_T$ and $\tau_T < t < \tau_{Z,tail}$, respectively. Finally, $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{tail} \sim t$ (Eq. A.10) for $t > \tau_{Z,tail}$. Compared with Regime I, Regime II has an additional time dependence $\langle r^2(t) \rangle \sim t^{2/3}$, which is due to the Zimm dynamics of a very long tail with $R_{tail} > bN$.

Regime III:

Large NP with $R < d < bN$ and Long tail with $R(d/b)^{1/2} < R_{tail} < bN$ (LL). The time dependence of $\langle r^2(t) \rangle$ in Regime III (red solid line in Figure 3(a)) is similar to that in Regime I (blue dashed line in Figure 3(a)). One difference between Regime III and Regime I is that $\tau_d^{III} \approx \tau_R$ while $\tau_d^I \approx \tau_R(d/R)^4 < \tau_R$ (see Eq. A.5). Another difference is in the d -dependence of the crossover time, $\tau_{III}^* \approx \tau_0(d/b)^2(R/b)^4$ whereas $\tau_f^* \approx \tau_0(d/b)^6$ (see Table 1).

Regime IV:

Large NP with $R < d < bN$ and Very long tail with $R_{tail} > bN$ (LV). Regime IV and Regime II have a similar time dependence of $\langle r^2(t) \rangle$ (see green dotted line and magenta dashed line in Figure 3(b)). The differences between Regime IV and Regime II are identical to those between Regime III and Regime II: (1). $\tau_d^{IV} \approx \tau_d^{III} \approx \tau_R$ vs. $\tau_d^{II} \approx \tau_d^I \approx \tau_R(d/R)^4$ and (2).

$$\tau_{IV}^* \approx \tau_{III}^* \approx \tau_0(d/b)^2(R/b)^4 \text{ vs. } \tau_{II}^* \approx \tau_f^* \approx \tau_0(d/b)^6.$$

Regime V:

Very large NP with $d > bN$ and Very long tail with $R_{tail} > d$ (VV). As shown by the cyan solid line in Figure 3(b), $\langle r^2(t) \rangle \approx \langle r^2(t) \rangle_{bare} \sim t^2$ (Eq. A.1) for $t < \tau_{bal}$, $\sim t^{1/2}$ (Eq. A.2) for $\tau_{bal} < t < \tau_d^V$, and $\sim t$ (Eq. A.6) for $\tau_d^V < t < \tau_V^*$. Above the crossover time τ_V^* , $\langle \Delta r^2(t) \rangle \approx \langle \Delta r^2(t) \rangle_{tail} \sim t^{2/3}$ (Eq. A.9) for $\tau_V^* < t < \tau_{Z,tail}$ and finally $\sim t$ (Eq. A.10) for $t > \tau_{Z,tail}$. Since the crossover time $\tau_V^* > \tau_T$, the tailed NP does not participate in the Rouse dynamics of the tail. As a result, there is no time range with $\langle r^2(t) \rangle \sim t^{1/2}$ for $t > \tau_V^*$ in Regime V.

B. Motion of a NP Tethered with a Dry Layer in an Unentangled Polymer Melt

Consider a NP with $1 < z < N^{1/2}$ loosely grafted tails and $d < R_{tail} < bz$. The grafted layer is dry, as R_{tail} is smaller than the dry core size bz of the corresponding star polymer (see Fig. 5(a)). Below we show that the mean square fluctuation of the NP under the confinement of the grafted layer is smaller than the MSD of a dry sphere with size $\approx R_{tail}$ in the matrix of melt chains. As a result, the motion of the tethered NP is approximated as that of the dry sphere with size $\approx R_{tail}$.

Suppose a coherently moving segment of a tail in the dry layer contains $g(t)$ monomers at time t . The fluctuation of the size of a segment containing g monomers is $r_g \approx bg^{1/2}$. The relaxation time of the segment is approximately the time it takes for the segment with diffusion coefficient $\approx k_B T / \zeta_0 g$ to diffuse a distance comparable to the fluctuation of its size, i.e., $\tau_g \approx r_g^2 / (k_B T / \zeta_0 g) \approx \tau_0 g^2$. As a result, $g(t) \approx (t/\tau_0)^{1/2}$. The mean square fluctuation of the particle confined by the tethered chains is $\langle r^2(t) \rangle_f \approx b^2 g(t)/z \approx b^2 (t/\tau_0)^{1/2}/z$. Note that $\langle r^2(t) \rangle_f$ is smaller than the MSD $\langle r^2(t) \rangle_{bare}$ of a bare NP in the same dry layer. The viscosity of a melt consisting of chains with g monomers per chain is $\eta_g \approx (k_B T / b^3 g) \tau_g \approx \eta_0 g$. The effective viscosity experienced by the bare particle at time scale t is $\eta_g(t) \approx \eta_0 g(t) \approx \eta_0 (t/\tau_0)^{1/2}$, and the effective friction coefficient $\zeta(t) \approx \eta_g(t) d \approx \zeta_0 (d/b) (t/\tau_0)^{1/2}$. As a result, $\langle r^2(t) \rangle_{bare} \approx [k_B T / \zeta(t)] t \approx (b^3/d) (t/\tau_0)^{1/2}$. For $d < bz$, $\langle r^2(t) \rangle_{bare} > b^2 (t/\tau_0)^{1/2}/z \approx \langle r^2(t) \rangle_f$, which means the confinement of tethered chains reduces the mobility of the particle with respect to the bare particle in the same dry layer.

The MSD of a dry sphere with diameter $\approx R_{tail} < bz$ in the matrix of melt chains with chain size $R \approx bN^{1/2} > bz$ is $\langle r^2(t) \rangle_{dry} \approx (b^3/R_{tail})(t/\tau_0)^{1/2}$ (see Eq.A.2) for $t < \tau_0 (R_{tail}/b)^4$ (see Eq.A.5). The ratio $\langle r^2(t) \rangle_{dry} / \langle r^2(t) \rangle_f \approx bz/R_{tail} > 1$ for $R_{tail} < bz$. Therefore, the MSD of the dry sphere dominates over the mean square fluctuation of the particle confined by the tethered chains. Accordingly, we approximate the MSD of the NP with a loosely grafted dry layer as

$$\langle \Delta r^2(t) \rangle \approx \langle \Delta r^2(t) \rangle_{dry} \approx \frac{b^3}{R_{tail}} \left(\frac{t}{\tau_0} \right)^{1/2}, \quad \text{for } 1 < z < N^{1/2} \text{ and } t < \tau_0 \left(\frac{R_{tail}}{b} \right)^4 \quad (\text{B.1})$$

while $\langle r^2(t) \rangle_f < \langle r^2(t) \rangle$ is the internal fluctuation of the particle position.

Next, consider a NP with $z > N^{1/2}$ densely grafted tails and $d < R_{tail} < bz^{1/2} N^{1/4}$, where $bz^{1/2} N^{1/4}$ is the dry core size of the corresponding star polymer (see Fig. 5(b)). Similar to the result for a loosely tethered NP, the mean square fluctuation $\langle r^2(t) \rangle_f \approx b^2 (t/\tau_0)^{1/2}/z$, and it is smaller than $\langle r^2(t) \rangle_{bare}$ of the bare particle in the same dry chains. The MSD of a dry sphere with diameter $\approx R_{tail}$ in the melt chains with chain size R is $\langle r^2(t) \rangle_{dry} \approx (b^3/R_{tail})(t/\tau_0)^{1/2}$ (see Eq.A.2) at times smaller than the diffusion time τ_d . According to Eq. A.5, $\tau_d \approx \tau_0 (R_{tail}/b)^4$ if $R_{tail} < R$, whereas $\tau_d \approx \tau_0 R \approx \tau_0 (R/b)^4$ if $R < R_{tail} < bz^{1/2} N^{1/4}$. The ratio

$\langle r^2(t) \rangle_{dry} \langle r^2(t) \rangle_f \approx (bz/R_{tail}) > z^{1/2}/N^{1/4} > 1$ for $R_{tail} < bz/2N^{1/4}$ and $z > N^{1/2}$. As a result, the MSD of the NP with a densely grafted dry layer is

$$\langle \Delta r^2(t) \rangle \approx \langle \Delta r^2(t) \rangle_{dry} \approx \frac{b^3}{R_{tail}} \left(\frac{t}{\tau_0} \right)^{1/2}, \text{ for } z > N^{1/2} \text{ and } t < \tau_d \approx \tau_0 \left(\frac{\min\{R_{tail}, R\}}{b} \right)^4 \quad (\text{B.2})$$

with the internal fluctuation of the particle position $\langle r^2(t) \rangle_f < \langle r^2(t) \rangle$.

References

- (1). Ye X; Tong P; Fetters LJ Transport of Probe Particles in Semidilute Polymer Solutions. *Macromolecules* 1998, 31, 5785–5793.
- (2). Omari RA; Aneese AM; Grabowski CA; Mukhopadhyay A Diffusion of Nanoparticles in Semidilute and Entangled Polymer Solutions. *J. Phys. Chem. B* 2008, 113, 8449–8452.
- (3). Tuteja A; Mackay ME; Hawker CJ; Horn BV Effect of Ideal, Organic Nanoparticles on the Flow Properties of Linear Polymers: Non-Einstein-like Behavior. *Macromolecules* 2005, 38, 8000–8011.
- (4). Guo H; Bourret G; Corbierre MK; Rucareanu S; Lennox RB; Laaziri K; Piche L; Sutton M; Harden JL; Leheny RL Nanoparticle Motion within Glassy Polymer Melts. *Phys. Rev. Lett* 2009, 102, 075702. [PubMed: 19257691]
- (5). Guo H; Bourret G; Lennox RB; Sutton M; Harden JL; Leheny RL Entanglement-Controlled Subdiffusion of Nanoparticles within Concentrated Polymer Solutions. *Phys. Rev. Lett* 2012, 109, 055901. [PubMed: 23006188]
- (6). Grabowski CA; Mukhopadhyay A Size Effect of Nanoparticle Diffusion in a Polymer Melt. *Macromolecules* 2014, 47, 7238–7242.
- (7). Balazs AC; Emrick T; Russell TP Nanoparticle polymer composites: Where two small worlds meet. *Science* 2006, 314, 1107–1110. [PubMed: 17110567]
- (8). Karatrantos A; Composto RJ; Winey KI; Clarke N Polymer and spherical nanoparticle diffusion in nanocomposites. *J. Chem. Phys* 2017, 146, 203331. [PubMed: 28571344]
- (9). Schuster BS; Ensign LM; Allan DB; Suk JS; Hanes J Particle tracking in drug and gene delivery research: state-of-the-art applications and methods. *Adv. Drug Deliv. Rev* 2015, 91, 70–91. [PubMed: 25858664]
- (10). Voylov DN; Holt AP; Doughty B; Bocharova V; Meyer HM; Cheng S; Martin H; Dadmun M; Kisliuk A; Sokolov AP Unraveling the Molecular Weight Dependence of Interfacial Interactions in Poly(2-vinylpyridine)/Silica Nanocomposites. *Macromolecules* 2017, 6, 68–72.
- (11). Cheng S; Carroll B; Bocharova V; Carrillo J-MY; Sumpter BG; Sokolov AP Focus: Structure and dynamics of the interfacial layer in polymer nanocomposites with attractive interactions. *J. Chem. Phys* 2017, 146, 203201. [PubMed: 28571333]
- (12). Lai SK; Wang Y-Y; Wirtz D; Hanes J Micro- and macrorheology of mucus. *Adv. Drug Deliv. Rev* 2009, 61, 86–100. [PubMed: 19166889]
- (13). Eisenriegler E Polymer Near Surfaces: Conformation Properties and Relation to Critical Phenomena; World Scientific Publishing Co. Pte. Ltd., 1993.
- (14). Guiselin O Irreversible Adsorption of a Concentrated Polymer Solution. *Europhysics Letters* 1992, 17, 225–230.
- (15). Scheutjens JMHM; Fleer GJ Statistical theory of the adsorption of interacting chain molecules. 2. Train, loop, and tail size distribution. *J. Phys. Chem* 1980, 84, 178–190.
- (16). Semenov AN; Joanny J-F Structure and Adsorbed Polymer Layers: Loops and Tails. *Europhysics Letters* 1995, 29, 279.
- (17). Ge T; Rubinstein M Strong Selective Adsorption of Polymers. *Macromolecules* 2015, 48, 3788–3801. [PubMed: 27065491]

- (18). Cai LH; Panyukov S; Rubinstein M Mobility of Nonsticky Nanoparticles in Polymer Liquids. *Macromolecules* 2011, 44, 7853–7863. [PubMed: 22058573]
- (19). Cai LH; Panyukov S; Rubinstein M Hopping Diffusion of Nanoparticles in Polymer Matrices. *Macromolecules* 2014, 48, 847–862.
- (20). Rubinstein M; Colby RH *Polymer Physics*; Oxford, 2003.
- (21). Daoud M; Cotton JP Star shaped polymers: a model for the conformation and its concentration dependence. *J. Phys. France* 1982, 43, 531–538.
- (22). Raphaël E; Pincus P; Fredrickson GH Conformation of Star Polymers in High Molecular Weight Solvents. *Macromolecules* 1993, 26, 1996–2006.
- (23). Aubouy M; Fredrickson GH; Pincus P; Raphaël E End-Tethered Chains in Polymeric Matrices. *Macromolecules* 1995, 28, 2979–2981.
- (24). Gay C; Raphaël E Static Properties of a Star Polymer in a High Molecular Weight Solvent. 1996, 6, 587–591.
- (25). Kandar AK; Srivastava S; Basu JK; Mukhopadhyay MK; Seifert S; Narayanan S Unusual dynamical arrest in polymer grafted nanoparticles. *J. Chem. Phys* 2009, 130, 121102. [PubMed: 19334800]
- (26). Hoshino T; Murakami D; Tanaka Y; Takata M; Jinnai H; Takahara A Dynamical crossover between hyperdiffusion and subdiffusion of polymer-grafted nanoparticles in a polymer matrix. *Phys. Rev. E* 2013, 88, 032602.
- (27). Liu S; Senses E; Jiao Y; Narayanan S; Akcora P Structure and Entanglement Factors on Dynamics of Polymer-Grafted Nanoparticles. *Macromolecules* 2016, 5, 569–573.
- (28). Choi J; Hore MJA; Clarke N; Winey KI; Composto RJ Nanoparticle Brush Architecture Controls Polymer Diffusion in Nanocomposites. *Macromolecules* 2014, 47, 2404–2410.
- (29). Lin C-C; Griffin PJ; Chao H; Hore MJA; Ohno K; Clarke N; Riggleman RA; Winey KI; Composto RJ Grafted polymer chains suppress nanoparticle diffusion in athermal polymer melts. *J. Chem. Phys* 2017, 146, 203332. [PubMed: 28571331]
- (30). Lin et al.²⁹ used $b = 1.96\text{nm}$ for the Kuhn monomer size of PMMA The value $b = 1.53\text{nm}$ we use in this paper is from Table 25.3 in Chapter 25 of *Physical Properties of Polymers Handbook*, 2nd ed. edited by Mark JE, Springer Science + Business Media, LLC: New York, 2007.
- (31). Zhulina EB; Adam M; LaRue I; Sheiko SS; Rubinstein M Diblock Copolymer Micelles in a Dilute Solution. *Macromolecules* 2005, 12, 5330–5351.

Figure 1:

(a) Schematic illustration of a NP (blue sphere) with a tethered polymer tail (red line) in a melt of unentangled polymers (green lines). The NP diameter is d . The size of a melt chain is R , while the size of the tail is R_{tail} . (b) Scaling regimes in the (d, R_{tail}) parameter space for the mobility of a single-tail NP in an unentangled polymer melt.

Figure 2:

Dependence of the crossover time τ^* (see Table 1 and Table 2) on the particle diameter d for a single-tail NP (green upper line) and a NP loosely grafted with $1 < z < N^{1/2}$ tails (blue lower line) in an unentangled polymer melt.

Figure 3:

Time dependence of the mean square displacement (MSD) $\langle \Delta r^2(t) \rangle$ of a single-tail NP in an unentangled polymer melt for (a) Regimes I and III and (b) Regimes II, IV, and V in Figure 1(b).

Figure 4:

(a) Schematic illustration of a NP (blue sphere) with $z > 1$ grafted tails (red lines) in a melt of unentangled polymers (green lines) with N monomers per chain. The NP diameter is d . The size of a melt chain is $R \approx bN^{1/2}$, while the size of the tail is R_{tail} . The multi-tail NP in (a) is mapped to a star polymer in the same melt, as illustrated in (b). The number of arms in the star is z . The size of the star is $R_{star} \approx R_{tail}$. The red sphere in (b) indicates the inner region of the star with diameter $\approx d$.

Figure 5:

Locations of different regions in (a) a loosely branched star polymer with $1 < z < N^{1/2}$ arms and (b) a densely branched star polymer with $z > N^{1/2}$ arms in a linear polymer melt with N monomers per chain. In both scenarios, only a star consisting of sufficiently long arms with the number of monomers per arm $N_a > N^2 z^{1/2}$ contains all the sketched regions. The structure of a dry core is illustrated in (c), where filled circles and black thick lines indicate the monomers and backbones, respectively. The conformations of chain sections in the Gaussian brush, swollen brush, and Daoud-Cotton brush are illustrated in (d), (e), and (f), respectively. The filled circle in (d) indicates the dry core surrounded by the Gaussian brush. For each type of brush, the strand belonging to one arm is highlighted by the black thick line. Dashed circles in (e) and (f) indicate the correlation blobs with sizes growing along the radial axis. Magenta dashed circles in (e) and (f) indicate the correlation blobs of the arm highlighted by the black solid line. Multiple chain strands exist in a correlation blob of a swollen brush, and the correlation blobs of different strands overlap, as illustrated in (e). By contrast, only one chain strand occupies a correlation blob of a Daoud-Cotton brush, as illustrated in (f). In a correlation blob, the excluded volume interaction of a chain strand with other strands at the same length scale is on the order of thermal energy $k_B T$.

Figure 6: Scaling regimes in the (d, R_{tail}) parameter space for the mobility of a NP with $1 < z < N^{1/2}$ tails in an unentangled polymer melt. Blue solid and dashed lines indicate the boundaries between tail-dominated regimes and the particle-dominated regimes for a multi-tail NP and a single-tail NP, respectively. Red solid lines indicate the boundaries between different tail-dominated regimes for a multi-tail NP.

Table 1:

Crossover time τ^* for a single-tail NP in an unentangled polymer melt.

Regimes I and II	Regimes III and IV	Regime V
$\tau_{I,II}^* \approx \tau_0(d/b)^6$	$\tau_{III,IV}^* \approx \tau_0(d/b)^2(R/b)^4$	$\tau_V^* \approx \tau_0 N(d/b)^3$

Table 2:

Crossover time τ^* for a NP loosely grafted with $1 < z < N^{1/2}$ tails in an unentangled polymer melt.

Regimes I and II	Regimes III and IV	Regime V
$\tau_{I,II}^* \approx \tau_0 (d/b)^6 / z^2$	$\tau_{III,IV}^* \approx \tau_0 (d/b)^2 (R/b)^4 / z^2$	$\tau_V^* \approx \tau_0 N (d/b)^3 / z$