Photocrosslinked ultrathin anionic polysaccharide supports for accelerated growth of human mesenchymal stem cells

A. Mikulska*, J. Filipowska†, A. M. Osyczka†, M. Szuwarzyński*, M. Nowakowska* and K. Szczubiałka*

*Faculty of Chemistry, Jagiellonian University, 30-387, Kraków, Poland and †Faculty of Biology and Earth Sciences, Jagiellonian University, 30-387, Kraków, Poland

Received 20 January 2014; revision accepted 30 April 2014

Abstract

Objectives: Properties of cell culture supports obtained from ultrathin multilayer films containing anionic natural polysaccharides (PSacs) and a synthetic polycation were studied.

Materials and methods: Supports were prepared via a layer-by-layer (LbL) self-assembly deposition method. Polymers used were: heparin (Hep), chondroitin sulphate (CS), hyaluronic acid (HA), and ι -carrageenan (Car) as polyanions, and diazoresin (DR) as a polycation. PSac layers were crosslinked with DR layers by irradiation with UV light absorbed by DR resin.

Results: DR/PSac films are very efficient cell culture growth supports as found from experiments with human mesenchymal stem cells (hMSCs). Irradiation of the films resulted in changing zeta potential of outermost layers of both DR and PSac to more negative values, and in increased film hydrophobicity, as found from the contact angle measurements. Photocrosslinking of the supports led to their increased stability.

Conclusions: The supports allow for obtaining intact cell monolayers faster than when typical polystyrene tissue culture plates are used. Moreover, these monolayers spontaneously detach permitting formation of new cell layers on these surfaces relatively early during culture, compared to cells cultured on commonly used tissue culture plastic.

Introduction

Tissue engineering (TE) is an ever-emerging branch of biotechnology aiming at repairing malfunctioning organs and tissues. It allows patients to achieve recovery when conventional therapeutic methods such as transplantation, surgery, prostheses and pharmacological treatment fail (1). Thus, over the last decade, enormous progress has been made in TE, accompanied by rapid development of experimental clinical cell therapies (2). TE methods have been successfully applied in the treatment of different organs and tissues including skin (3), heart (4), liver (5), gastrointestinal tract (6), bone (7), muscle (8), nervous tissue (9), blood vessels (10), lymphatic system (11), and cornea (12,13).

Tissue engineering methods usually require the use of a 3-D scaffold or 2-D surface, which serves as a support for the attachment and proliferation of cells. Cell culture scaffolds and surfaces are usually prepared from biopolymers by a variety of methods (14). One of these is a layer-by-layer (LbL) method, that we have applied in this study. Sequential LbL films in supports may be bound to each other by electrostatic (15), hydrogen bonding (16), coordination (17), and charge-transfer (18) interactions between the molecules (macromolecules) forming each layer. This technique has found many biomedical applications (19) such as preparation of supports for culturing corneal endothelial cells (20), cartilage tissue (21), pre-osteoblast cells (22), and hepatocytes (23). Among biopolymers used, polysaccharides are of particular interest due to their biodegradability, low toxicity, ease of functionalization and low cost (24).

In the present work, we report studies on the cell culture surfaces obtained with natural anionic polysaccharides, heparin (Hep), chondroitin sulphate (CS), hyaluronic acid (HA), and ι -carrageenan (Car) (Fig. 1). The first three polysaccharides are glycosaminoglycans (GAGs), while Car is a sulphated marine polysaccharide.

Correspondence: K. Szczubiałka, Faculty of Chemistry, Jagiellonian University, 30-060 Kraków, Ingardena 3, Poland. Tel.: +48 12 663 2062; Fax: +48 12 634 0515; E-mail: szczubialka@chemia.uj.edu.pl

Figure 1. Chemical structures of polymers used for synthesis of the multilayer films.

GAGs perform many structural and physiological functions such as maintaining haemostasis, morphogenesis and the immune response, and they take part in a variety of pathological processes. GAGs are being extensively studied as materials for preparation of cell culture scaffolds (25–27). There are two approaches for surface immobilization of GAGs to produce cell culture supports, that is, methods involving electrostatic interactions and those involving covalent attachment of the polymers. Coating a surface with GAGs using non-covalent (electrostatic) binding is usually achieved by making the surface positively charged by chemical modification, so that it is able to attract negatively charged GAGs. One of the methods of surface modification for coating with GAGs is plasma polymerization. It can be used to enrich the surface with functionalities such as amine groups (28–30). This way, heparin can be supported on the plasma-polymerized allylamine (31). Another way of attaching GAGs is to functionalize the surface with compounds, including polymers, bearing positively charged groups, for example, chains of poly(amido-amine), a tertiary amine polymer capable of forming stable complexes with heparin. Chains of this polymer are

either surface-grafted on polyurethane or interconnected with polyurethane, which allows ionic binding of heparin (32).

Covalent binding of GAGs may be achieved, for example, by tethering them to polydopamine thin layers. Dopamine spontaneously polymerizes forming an ultrathin layer on a surface by simple immersion in dilute dopamine solution, at slightly basic pH (33). Polydopamine has been used to covalently immobilize HA (33) and biomolecules with amine or thiol groups, for example trypsin (34). HA can be also tethered to aminosilane (APTMS)-treated glass surfaces using the carbodiimide reaction (35), while heparin has been covalently immobilized to the surface of anatase film using 3-aminopropyltriethoxysilane, the bifunctional linking reagent (36), to polyurethane surfaces *via* PEO (36) or alkyl spacers (37).

We have studied application of photocrosslinked polysaccharide supports to culturing human mesenchymal stem cells (hMSCs), which are of particular interest due to their broad potential in regenerative medicine (38). hMSCs undergo mesodermal lineage-specific differentiation to osteocytes, adipocytes and chondrocytes. Compared to embryonic stem cells, they show restricted proliferation and differentiation, but their use and application is free from ethical concerns and poses no risk of teratoma formation (39). hMSCs are present in many adult tissues, including brain, heart, intestine, skin, cornea, bone marrow, and muscle where they help in maintaining tissue homeostasis and repair tissue in response to injury.

Here, we present an innovative hMSC culture support fabrication based on the LbL method, enabling formation of a multilayer ultrathin polymeric film. This method has previously been reported for preparation of cell culture supports from HA and poly-L-lysine (40). However, in our case, formation of the LbL film was followed by its photocrosslinking, enabled by application of diazo-resin, a photoreactive polycation. In the previous study by our group (41), we showed that this approach can be used to obtain cell culture supports based on pectin, an anionic polysaccharide. Here, we have applied this methodology to obtain the culture supports using selected GAGs, Hep, CS and HA, as well as ι -carrageenan (Car), a sulphated polysaccharide of marine origin. An important property of the obtained supports is that they sustain more rapid growth of hMSC than currently commercially available cell culture supports. An unexpected, but very important feature of the supports obtained with sulphated polysaccharides (Hep, CS, and Car) is that they allow culturing of self-detachable cell monolayers.

Materials and methods

Materials

Heparin sodium salt (Hep) (Sigma-Aldrich, St. Louis, MO, USA), chondroitin sulphate (CS) (Sigma, St. Louis, MO, USA), ι -carrageenan (Car) (Sigma), hyaluronic acid sodium salt from *Streptococcus equi* (Sigma), sodium chloride (POCH, Gliwice, Poland), 4-diazodiphenylamine sulphate (Sigma-Aldrich), paraformaldehyde (POCH), zinc chloride (POCH), and tetraethyl orthosilicate (TEOS; Fluka, St. Louis, MO, USA) were all reagent grade and used as received. Water was distilled twice and deionized using the Simplicity Millipore Water Purification System (Billerica, MA, USA).

Apparatus

UV-Vis film spectra were measured using a HP 8452A diode-array spectrophotometer; IR spectra of non-irradiated and irradiated films were obtained on a Bruker IFS 48 spectrometer. Atomic force microscope (AFM) (Pico-force; Veeco, Plainview, NY, USA) working in tapping mode was used to characterize topography and roughness of the surfaces in air. Standard silicon cantilevers (Veeco) with nominal spring constant of 40 N/m and tip radius <10 nm were used for all measurements. Contact angle was measured using a Surftens Universal instrument (OEG GmbH, Frankfurt, Germany). Irradiation of samples was carried out using a Rayonet photoreactor equipped with six 21W lamps with emission intensity maximum at 350 nm. Zeta potential of Stöber particles coated with DR/Pec films was evaluated using Zetasizer Nano ZS (Malvern Instruments Ltd., Malvern, UK). SEM images were obtained using a Hitachi S-4700 scanning electron microscope (Hitachi Company, Tokyo, Japan) with a Noran Vantage microanalytical system. Measurements of film thickness were performed with an XLS-100 spectral ellipsometer (J.A. Woollam Co., Inc., Lincoln, NE, USA) and AFM scratch method. Zeiss Axiovert 40 inverted optical microscope (Jena, Germany) was used to visualize cell number expansion on the supports. The number of viable hMSCs was measured using ELISA infinite F200PRO, TECAN microplate reader.

Synthesis of diazoresin

Diazoresin (DR) was synthesized according to the literature procedure (42). Briefly, 4.707 g 4-diazodiphenylamine sulphate was added to a 50-ml flask containing 16 ml concentrated H_2SO_4 , which was cooled in an ice-water bath. Then, 0.430 g paraformaldehyde was added

in four batches at 0–5 °C; and the reaction was continued for 4 h at this temperature. Reaction mixture was poured carefully into 30 ml of the iced water. Subsequently, 8.018 g zinc chloride was added to precipitate the diazonium resin as a $\frac{1}{2}$ ZnCl_2 complex. After filtration and drying under vacuum, a yellow-green powder was obtained, which was stored in the dark.

Synthesis of silica gel particles

Silica gel microparticles were obtained using the Stöber method (43), modified as described elsewhere (44). Briefly, 3 ml of 16.7% ammonium hydroxide was added rapidly to a solution of 0.65 ml of TEOS in 11.35 ml ethanol. The mixture was stirred vigorously with a magnetic stirrer for 24 h and a suspension of silica gel particles was obtained. Ethanol and ammonium hydroxide were removed under vacuum. Silica particles were stored in the aqueous suspension.

Preparation of multilayer films

The surface of quartz plates, used to fabricate self-assembled films, was pre-treated in piranha solution [boiling $\text{H}_2\text{O}_2/\text{H}_2\text{SO}_4$ (3:7 v/v) mixture], for 30 min then carefully rinsed in distilled water and dried under argon before being used (CAUTION: piranha solution is highly corrosive and reacts violently with organics; proper caution must be taken when handling). Polysaccharides were dissolved at 1.0 mg/ml in 0.1 M NaCl while concentration of DR aqueous solution was 2.0 mg/ml. Multilayer films were assembled according to the procedure described in the literature (45). The negatively charged quartz plate was first immersed in DR cationic solution under sonication for 5 min, then rinsed in distilled water and dried in a stream of argon. Subsequently, a quartz plate coated with a DR layer was dipped into the solution of a respective polysaccharide, under sonication for 5 min, rinsed in distilled water and dried again with argon, to complete a bilayer fabrication cycle. In each cycle, bilayers of DR/Hep, DR/CS, DR/HA and DR/Car films were deposited on both surfaces of the substrate. The coating process was repeated until plates were covered with six DR/PSac bilayers. The outermost layer was always made of a PSac. The film deposition process was conducted in the dark to avoid photodecomposition of DR. Fabricated films were irradiated with nUV light (using lamps with maximum intensity of emission at 350 nm) for sufficient time to obtain a photocrosslinked multilayer film.

Films were also deposited on Stöber silica gel particles using the same polymer solutions as those used during preparation of films on quartz slides, as described

previously (41). The suspension of particles in water was centrifuged at $1.3 \times 10^4 g$ for 3 min to separate the particles. Water was removed by decantation and DR solution was added to the particles. The sample was then sonicated for 5 min at 0 °C followed by centrifugation and decantation of the supernatant solution. DR-coated silica gel particles were washed in water by filling the centrifuge tube containing coated particles with water, sonication for 2 min, centrifugation ($1.3 \times 10^4 g$, 3 min) and decantation of water. Procedures described above were repeated 5 times. The solution of a respective PSac was then added to DR-coated particles and the sample was sonicated for 5 min at 0 °C. Thereafter, the particle suspension was washed in water 5 times, as described above.

Cell cultures

Adult hMSCs were harvested from iliac crest of adult patients (aged 19–71 of both genders) under the Institutional Review Board-approved protocol (KBET/17/L/2007). Mononuclear cell fraction was isolated using a Ficoll-Paque reagent (GE Healthcare, Fairfield, CT, USA), as described previously (46). Primary cells were cultured in standard tissue culture flasks using alpha-MEM supplemented with 10% pre-selected MSC-qualified foetal bovine serum (MSC-FBS) and 1% penicillin/streptomycin solution (Life Technologies, Carlsbad, CA, USA). Cells were maintained at 37 °C in a humidified 5% CO₂ atmosphere. Medium was changed twice weekly until a confluent cell monolayer formed. Secondary cultures were used for evaluation of experimental films. Briefly, glass plates were coated with experimental films composed of 6 bilayers (prepared as described above), placed in wells of 24-well tissue culture plates, and pre-sterilized by irradiating with UV light for 5 min. Primary cells were detached from culture flasks using 0.25% trypsin–EDTA (Life Technologies) and seeded on films at 2×10^4 cells/ml/well. Cells were then cultured for 7 days in alpha-MEM supplemented with 10% MSC-FBS and antibiotics. Medium was changed on the second, fourth and sixth day of culture. Cell population growth was monitored over 7-day culture, by phase-contrast light microscopy. Cell viability assays were performed on days 1, 3, 5, and 7.

Alamar blue (AB) cell viability assay

Number of viable hMSCs was estimated using Alamar blue (AB) assay. Cells were washed once in the PBS buffer, pH 7.4, and each well of a 24-well plate was covered with 200 µl of solution prepared as 1:10 vol/vol dilution of the reagent, containing AB in the pH 7.4 PBS. Cells were then incubated for 6 h at 37 °C in a

humidified 5% CO₂ atmosphere. Next, media from each well were transferred separately to 96-well plates and absorbance was measured at 570 and 600 nm.

Results

Preparation of DR/PSac films

Polymeric films were supported on quartz plates or on the silica gel microparticles obtained using the Stöber method. As the surface of these supports is negatively charged, DR was always used to prepare the first layer, while the last (outermost) layer was always made of PSac. Growth of layers formed by adsorption were examined using UV-Vis spectroscopy, as DR absorbs strongly at 380 nm. Figure 2 shows UV-Vis absorption spectra of DR/Hep films composed of up to six bilayers (corresponding spectra for other polysaccharides used are shown in Fig. S1). When analysing the spectra, it should be kept in mind that both sides of quartz plates are coated with the polymers.

UV-Vis absorption spectroscopy was also used to follow photocrosslinking reaction in the films as it is accompanied by the disappearance of the 380 nm absorption band (data not shown). Time dependence of

Figure 2. UV-Vis absorption spectra of the first six bilayers of DR/Hep multilayer film supported on a quartz slide.

Figure 3. Changes due to irradiation, in the relative absorbance at 380 nm of the DR/PSac films composed of 6 bilayers ($\lambda_{irr} = 400$ nm).

relative absorbance at 380 nm per irradiation time, is shown in Fig. 3 for all DR/PSac films studied. Under these experimental conditions, the photocrosslinking reaction was completed within around 35 s for CS, Car, and HA, while for Hep, it was noticeably faster and ended within 20 s, as shown by almost complete disappearance of the DR absorption band.

To confirm formation of covalent bonds between adjacent layers, IR spectra of self-assembled films were recorded. Figure 4 shows IR spectra of DR/CS films before and after UV irradiation (IR spectra of other DR/PSac films are shown in Fig. S2).

Physicochemical and structural properties of the DR/PSac films

Stability of the multilayer films. To determine whether photocrosslinking of films resulted in their expected stability and resistance to degradation in aqueous media, the quartz plates were coated with irradiated six-bilayer films, immersed in PBS (pH = 7.4), shaken for up to 20 days and their absorption spectra were measured after different shaking times (Fig. 5).

Figure 4. IR spectra of DR/Hep films measured before (solid line) and after irradiation (dashed line).

Figure 5. Dependence on time of relative absorbance at 380 nm of DR/PSac photocrosslinked six-bilayer films immersed and shaken in pH 7.4 PBS buffer (pH = 7.4, λ_{irr} = 400 nm, irradiation time 7 min for DR/Hep, DR/CS and DR/HA, and 15 min for DR/Car film).

Table 1. Properties of the DR/PSac films composed of six bilayers before and after photocrosslinking

	DR/Hep	DR/CS	DR/Car	DR/HA
Thickness (nm)				
Before	6.9 ± 0.4	10.2 ± 0.6	12.6 ± 0.4	8.7 ± 0.6
After	5.7 ± 0.1	8.9 ± 0.1	10.7 ± 0.3	8.5 ± 0.4
RMS roughness				
Before	0.51	0.55	1.32	1.02
After	0.56	0.83	1.36	1.38
Contact angle (degrees)				
Before	26	27	24	22
After	61	46	50	43

Morphology of films – thickness. Thickness of polymeric films was assessed using ellipsometry. Values obtained are shown in Table 1.

Morphology of films – roughness. Morphology of DR/PSac films before and after photocrosslinking, was imaged using AFM (Fig. 6) and SEM (Fig. S3) microscopy. Values of RMS roughness of the six-bilayer films are given in Table 1. Films were quite smooth with RMS roughness ranging from 0.51 (DR/Hep) to 1.32 (DR/Car).

Contact angle measurements. To estimate hydrophobicity/hydrophilicity for the studied films, water contact angle values were measured both before and after irradiation (Table 1). Before irradiation, films were quite hydrophilic with contact angle values ranging from 22 to 27°. Irradiation resulted in significant reduction in their hydrophilicity (increase in water contact angle), which was greatest for DR/Hep (61°) and lowest for DR/HA (43°).

Zeta potential of films. To evaluate changes in surface charge on deposition of subsequent polymeric layers, up to five DR/PSac bilayers were deposited on the Stöber silica gel particles, and their zeta potential was measured, for both non-irradiated and irradiated films (Fig. 7). It was found that deposition of subsequent layers was accompanied by reversal in the sign of the zeta potential, from highly negative (for bare particles and for particles coated with a PSac as the outermost layer) to highly positive (when DR was the outermost layer). It was found, however, that for the DR/HA system, only three bilayers could be supported on Stöber particles. Further repeating of the coating procedure did not result in reversal in the sign of the zeta potential for this polymer pair, probably due to too low charge density of HA.

Figure 6. Atomic force microscope images of DR/PSac films before (left) and after (right) UV irradiation.

Properties of cell culture supports obtained from DR/PSac films

Microscopy images of hMSC cells cultured on supports prepared from six bilayer films of all studied DR/PSac systems are shown in Fig. 8. hMSCs were also cultured on a commercial tissue culture plastic (TCP) as reference.

To quantitatively compare the ability of the studied materials to support hMSC cultures, the numbers of live cells were monitored using the AB assay, at different culture times. AB is designed to provide a rapid and sensitive measure of cell population growth and cytotoxicity of various human and animal cell lines. Resazurin,

Figure 7. Zeta potential of nonirradiated (■) and irradiated (●) films composed of DR/Hep, DR/CS, DR/Car and DR/HA (from top to bottom) supported on Stöber microparticles. Arrows show changes in zeta potential due to irradiation.

Figure 8. human mesenchymal stem cells cultured on DR/PSac films composed of six bilayers, and on tissue culture plastic, used as a reference. Seeding cell density, 2500 cells/cm². White bars at lower left corners = 250 μ m.

the active ingredient of the AB reagent, is a non-toxic, cell-permeable blue compound, virtually non-fluorescent. Upon entering cells, resazurin is reduced to resorufin, a red compound that is highly fluorescent. Intensity of fluorescence/absorbance produced is proportional to number of living cells and thus it is an ideal indicator to generate quantitative measurement of the cell viability, and thus of the potential cytotoxicity of a material matrix. Results obtained are given in Table 2. Figure 9 is composed of images of cells grown at high cell seeding density, 1×10^4 cells/cm².

Discussion

Polymers used in this study included diazonium resin (DR), a synthetic polymer, and natural anionic polysaccharides, heparin (Hep), chondroitin sulphate (CS), hyal-

uronic acid (HA), and ι -carrageenan (Car) (Fig. 1). Except for Car, these polysaccharides are GAGs, biopolymers which play many structural and physiological roles in tissues. DR carries a net positive charge due to content of diazonium groups ($-N_2^+$), while the polysaccharides are negatively charged due to presence of sulphate groups (Car), carboxylic groups (HA), or both (Hep and CS). Because the degree of dissociation of the carboxylic group is much lower than that of the sulphate group under our experimental conditions (pH $\sim$ 7) and because the various content of ionized groups present in the macromolecules, these polysaccharides differ significantly in charge density along their chains, with Hep being the most strongly charged [in fact heparin has the highest negative charge density of any known biological molecule (47) with an average of 2.7 negative charges *per* disaccharide repeating unit (48)], a while HA,

Table 2. The number of hMSC cells grown on different supports and on TCP as a reference determined using Alamar Blue assay. Cells were seeded at the density of 2500 cells/cm². Biological evaluations were performed at least in triplicates

Day of culture	Number of hMSC cells ($\times 10^{-3}$)				
	DR/Hep	DR/CS	DR/Car	DR/HA	TCP
1	8.8 $\pm$ 0.6	8.9 $\pm$ 0.5	8.2 $\pm$ 0.5	7.9 $\pm$ 0.2	9.3 $\pm$ 0.3
3	19.8 $\pm$ 0.4	20.2 $\pm$ 0.3	19.3 $\pm$ 0.4	16.7 $\pm$ 0.2	17.0 $\pm$ 0.2
5	35.4 $\pm$ 2.7	31.3 $\pm$ 1.1	37.6 $\pm$ 1.2	28.4 $\pm$ 1.1	27.4 $\pm$ 0.6
7	57.4 $\pm$ 2.4	55.8 $\pm$ 2.0	64.2 $\pm$ 1.9	47.9 $\pm$ 2.4	48.7 $\pm$ 1.5
<i>P</i> value (<i>t</i> -Student test)	9.17E-05	2.61E-04	6.23E-08	6.24E-01	

Data are expressed as mean $\pm$ SD. The results for each type of cell culture support were separately compared with TCPS by Student's *t*-test and *P* < 0.05 was considered significant.

hMSC, human mesenchymal stem cells; TCP, tissue culture plastic.

Figure 9. (a) human mesenchymal stem cells, day 3 of culture, grown on DR/PSac films and on tissue culture plastic as a reference; (b) cells grown on films after detachment of cell monolayer. Cells were seeded at 10 000 cells/cm². White bars in upper left corners = 250 μ m.

containing only one carboxylic group *per* disaccharide unit, is the least charged among the polyanions used.

Due to strong electrostatic interactions between positively charged diazonium groups of DR and negatively charged groups of polysaccharides, ultrathin films can be constructed very easily using the LbL method (49). We have found that the intensity of the absorption band at 380 nm, associated with the π - π^* transition of the diazonium group in DR, increases linearly with the number of bilayers, for up to six bilayers (Fig. 2). This indicates a linear increase in the multilayer thickness. No substrate effect on thickness of the first bilayer was observed for any of the films.

DR is a photosensitive polymer and decomposes easily under irradiation with light at $\sim$ 380 nm, or when heated. Decomposition is accompanied by liberation of nitrogen, and with transformation of ionic bonds between $-N_2^+$ of DR and COO^- or SO_4^- groups of PSacs, into covalent bonds. Thus, irradiation of a multilayer DR/PSac film with light of the wavelength absorbed by DR, results in the photocrosslinking of adjacent layers within the film, which could be seen as the reduction in the film absorbance at 380 nm (Fig. 3).

It could be expected that photocrosslinking rate and/or density of crosslinks would be higher for strongly charged Hep than for weakly charged HA. In fact, photocrosslinking was faster for films containing Hep than for those containing other polysaccharides. This could be ascribed to, as mentioned above, Hep having the highest density of reactive ionized groups among the polyanions studied. This was confirmed experimentally in the stability tests of the photocrosslinked films.

Formation of crosslinks between layers was confirmed using IR spectroscopy. As shown in Fig. 4, the peak at 2165 cm^{-1} (stretching vibration of the diazonium group) disappeared after irradiation of the films with UV light, indicating decomposition of diazonium groups in the DR/CS film. The peak at 1740 cm^{-1} increased noticeably, indicating formation of the ester bonds in the film (50). Changes in IR spectra of other DR/PSac films were qualitatively the same (see Supporting Information).

As can be concluded from Fig. 5, absorbance of the films did not change for at least 20 days, which indicated that they were stable over this period. This is an important finding as it makes application of the films

possible, to virtually any surface, which in addition to ease of the fabrication procedure and favourable biological properties of the films, opens a variety of their practical applications related to cell culturing. Interestingly, it was found that irradiation for 7 min was sufficient to photocrosslink films DR/Hep, DR/CS and DR/HA strongly enough to obtain water-resistant surfaces, while for DR/Car, a longer period (15 min) was required to produce a stable film.

Thickness of six-bilayer films, measured using ellipsometry, varies significantly from almost 6.9 nm for DR/Hep, to 12.6 nm for DR/Car (Table 1). Greatest thickness of DR/Car correlates with longest time of irradiation required for efficient photocrosslinking in this system, and may suggest that it is due to the lowest photocrosslinking degree and the greatest distance between reacting groups of adjacent layers. It was also found that the irradiation of films did not significantly change the thickness of DR/HA films, while for DR/Hep, DR/CS and DR/Car, moderate reduction in thickness was observed.

Roughness of films was studied using AFM microscopy. Photocrosslinking of the films resulted in an increase in surface roughness, quite modest for DR/Hep and DR/CS, but more pronounced for DR/HA and DR/Car (Table 1).

Hydrophobicity/hydrophilicity of the surface of a cell culture support is an important parameter, which may strongly influence ability of cultured cells to adhere and proliferate. Due to photocrosslinking, the surface of DR/PSac supports changed from hydrophilic (contact angle 22–27°) to moderately hydrophilic (contact angle 43–61°), being highest for DR/Hep and DR/Car. This reduction may be due to disappearance of ionized diazonium groups and reaction of carboxylic and sulphate groups of PSac, resulting in reduction of charge density of the respective polymers. Cell proliferation on these supports was particularly intense. One possible explanation for increased cell viability/proliferation may be that due to increased hydrophobicity, the culture supports adsorbed serum proteins. Recently, Bauer *et al.* proposed that, initially, hydrophobic biomaterials may become more hydrophilic on exposure to serum proteins (51). Thus, even strongly hydrophobic surfaces may promote cell adhesion due to favourable serum protein adsorption. Similarly, these polysaccharides (especially Car) may have promoted cell adhesion due to supporting serum protein adsorption. Alternatively, Liu *et al.* recently showed that growth surfaces made of graphene oxide modified with Car increased cell adhesion and proliferation compared to plain graphene oxide (52). This suggests that properties of Car positively influence cell attachment and proliferation, regardless of the mechanism. Our studies indicate similar effects with Car-containing films.

As expected, irradiation of the films resulted in change of their zeta potentials (Fig. 7). Reversal in sign of zeta potential was a further confirmation of an efficient formation of a multilayer film. When a DR layer was the outermost one, zeta potential was changed from highly positive to highly negative, which can be ascribed to decomposition of positive diazonium groups. However, when the outermost layer was composed of PSac, change in zeta potential was opposite for DR/Hep and DR/CS systems, that is, zeta potential changed slightly from more negative to less negative values, while for DR/Car and DR/HA, irradiation did not affect the zeta potential. Thus, irrespective of the polymer forming the outermost layer, zeta potential of photocrosslinked films was highly negative, around –60 mV, except for DR/HA films, for which it was in the order of –40 mV.

The main purpose of the studies described here was to construct materials which can be useful as cell culture supports. Thus, we tested whether adult hMSCs could be cultured on the photocrosslinked DR/PSac films. Their population growth expansion was monitored for 7 days, using phase-contrast light microscopy. Steady increase in cell numbers could be observed on all DR/PSac films (Fig. 8). Results obtained using AB cell viability testing are provided in Table 2. They clearly show that the numbers of cells grown on DR/PSac were greater than of cells grown on a commercial TCP support. DR/Car was found to be the best support with numbers of cells after 7-day culture being statistically higher, by one-third, than for TCP. DR/Hep and DR/CS are better supports than TCP, although not as good as DR/Car, while DR/HA is comparable to TCP.

When higher cell seeding density was applied (10^4 cells/cm²), it was seen that hMSCs grown on supports containing Hep, CS, and Car formed monolayers that spontaneously detached from the support, as soon as the 3rd day of culture, and the growth of a new cell monolayer was initiated (Fig. 9). This phenomenon was not observed for DR/HA and TCP supports, even over longer culture times. We have not previously observed such phenomena for pectin supports from our previous studies (41). Spontaneous cell detachment is an important observation for the supports studied here, as this property may be useful for obtaining intact monolayers, while standard trypsinization used to detach adherent cells from culture support yields a suspension of isolated cells. Notably, spontaneous detachment of monolayers was observed only on those obtained from polysaccharides containing sulphate groups (Hep, CS and Car) and not on supports prepared from polysaccharides containing only carboxylic groups (pectin, HA).

Also, these culture supports can be used for re-expansion by new proliferating cells that remain after

detachment of the first cell monolayer. This suggests that these culture supports are not modified by the growing cells in any way that deteriorates their favourable properties, as is often the case for biopolymeric culture supports.

Acknowledgements

The project operated within the Foundation for Polish Science Team Programme co-financed by the EU European Regional Development Fund, PolyMed, TEAM/2008-2/6. The research was carried out with the equipment purchased with the support of the European Regional Development Fund (POIG.02.01.00-12-023/08). AM is grateful to Polish National Science Centre for a financial support in the form of the grant UMO-2012/05/N/ST5/01495. The work was supported in part by the Polish National Science Center grant B/NZ4/0066 (AMO). The authors thank Prof. T. Niedzwiedzki, Head of the Department of Orthopaedics and Musculoskeletal Traumatology of L. Rydygier Hospital in Krakow, for procuring adult hMSC cells.

References

- Persidis A (1991) Tissue engineering. *Nat. Biotechnol.* **17**, 508–510.
- Culme-Seymour EJ, Davie NL, Brindley DA, Edwards-Parton S, Mason C (2012) A decade of cell therapy clinical trials (2000–2010). *Regen. Med.* **7**, 455–462.
- Biedermann T, Boettcher-Haberzeth S, Reichmann E (2013) Tissue engineering of skin for wound coverage. *Eur. J. Pediatr. Surg.* **23**, 375–382.
- Boffito M, Sartori S, Ciardelli G (2014) Polymeric scaffolds for cardiac tissue engineering: requirements and fabrication technologies. *Polym. Int.* **63**, 2–11.
- Palakkan AA, Hay DC, Pr AK, Tv K, Ross JA (2013) Liver tissue engineering and cell sources: issues and challenges. *Liver Int.* **33**, 666–676.
- Shen Q, Shi P, Gao M, Yu X, Liu Y, Luo L *et al.* (2013) Progress on materials and scaffold fabrications applied to esophageal tissue engineering. *Mat. Sci. Eng. C* **33**, 1860–1866.
- Lu CH, Chang YH, Lin SY, Li KC, Hu YC (2013) Recent progresses in gene delivery-based bone tissue engineering. *Biotechnol. Adv.* **31**, 1695–1706.
- Fishman JM, Tyraskis A, Maghsoudlou P, Urbani L, Totonelli G, Birchall MA *et al.* (2013) Skeletal muscle tissue engineering: which cell to use? *Tissue Eng. B* **19**, 503–515.
- Yu X, Bellamkonda RV (2003) Tissue-engineered scaffolds are effective alternatives to autografts for bridging peripheral nerve gaps. *Tissue Eng.* **9**, 421–430.
- Li S, Sengupta D, Chien S (2014) Vascular tissue engineering: from in vitro to in situ. *Wiley Interdiscip. Rev. Syst. Biol. Med.* **6**, 61–76.
- Weitman E, Cuzzone D, Mehrara BJ (2013) Tissue engineering and regeneration of lymphatic structures. *Future Oncol.* **9**, 1365–1374.
- Mimura T, Yamagami S, Amano S (2013) Corneal endothelial regeneration and tissue engineering. *Prog. Retin. Eye Res.* **35**, 1–17.
- Grolnik M, Kopeć M, Szczubiałka K, Wowra B, Dobrowolski D, Wylegała E *et al.* (2012) Regeneration of corneal epithelium using keratin modified chitosan membranes. *Przegl. Lek.* **69**, 992–997.
- Weigel T, Schinkel G, Lendlein A (2006) Design and preparation of polymeric scaffolds for tissue engineering. *Expert Rev. Med. Devices* **3**, 835–851.
- Decher G (1997) Fuzzy nanoassemblies: toward layered polymeric multicomposites. *Science* **277**, 1232–1237.
- Zhang H, Wang D, Wang Z, Zhang X (2007) Hydrogen bonded layer-by-layer assembly of poly(2-vinylpyridine) and poly(acrylic acid): influence of molecular weight on the formation of microporous film by post-base treatment. *Eur. Polym. J.* **43**, 2784–2791.
- Zhao W, Tong B, Shi J, Pan Y, Shen J, Zhi J *et al.* (2010) Fabrication and optoelectronic properties of novel films based on functionalized multiwalled carbon nanotubes and (phthalocyaninato) ruthenium(II) via coordination bonded layer-by-layer self-assembly. *Langmuir* **26**, 16084–16089.
- Alencar WS, Crespiho FN, Santos MRMC, Zucolotto V, Oliveira ON Jr, Silva WC (2007) Influence of film architecture on the charge-transfer reactions of metallophthalocyanine layer-by-layer films. *J. Phys. Chem. C* **111**, 12817–12821.
- Boudou T, Crouzier T, Ren K, Blin G, Picart C (2010) Multiple functionalities of polyelectrolyte multilayer films: new biomedical applications. *Adv. Mater.* **22**, 441–467.
- Ozcelik B, Brown KD, Blencowe A, Daniell M, Stevens GW, Qiao GG (2013) Ultrathin chitosan-poly(ethylene glycol) hydrogel films for corneal tissue engineering. *Acta Biomater.* **9**, 6594–6605.
- Silva JM, Georgi N, Costa R, Sher P, Reis RL, van Blitterswijk CA *et al.* (2013) Nanostructured 3D constructs based on chitosan and chondroitin sulphate multilayers for cartilage tissue engineering. *PLoS One* **8**, e55451.
- Samuel RE, Shukla A, Paik DH, Wang MX, Fang JC, Schmidt DJ *et al.* (2011) Osteoconductive protamine-based polyelectrolyte multilayer functionalized surfaces. *Biomaterials* **32**, 7491–7502.
- Wittmer CR, Phelps JA, Lepus CM, Saltzman WM, Harding MJ, Van Tassel PR (2008) Multilayer nanofilms as substrates for hepatocellular applications. *Biomaterials* **29**, 4082–4090.
- Khan F, Ahmad SR (2013) Polysaccharides and their derivatives for versatile tissue engineering application. *Macromol. Biosci.* **13**, 395–421.
- Lee CR, Grodzinsky AJ, Spector M (2001) The effects of cross-linking of collagen-glycosaminoglycan scaffolds on compressive stiffness, chondrocyte-mediated contraction, proliferation and biosynthesis. *Biomaterials* **22**, 3145–3154.
- Singh S, Wu BM, Dunn JCY (2011) The enhancement of VEGF-mediated angiogenesis by polycaprolactone scaffolds with surface cross-linked heparin. *Biomaterials* **32**, 2059–2069.
- Fiumana E, Pasquinelli G, Foroni L, Carboni M, Bonafé F, Orrico C *et al.* (2013) Localization of mesenchymal stem cells grafted with a hyaluronan-based scaffold in the infarcted heart. *J. Surg. Res.* **179**, E21–E29.
- Robinson DE, Marson A, Short RD, Buttle DJ, Day AJ, Parry KL *et al.* (2008) Surface gradient of functional heparin. *Adv. Mater.* **20**, 1166–1169.
- Marson A, Robinson DE, Brookes PN, Mulloy B, Wiles M, Clark SJ *et al.* (2009) Development of a microtiter plate-based glycos-

- aminoglycan array for the investigation of glycosaminoglycan-protein interactions. *Glycobiol.* **19**, 1537–1546.
- 30 Beck AJ, Candan S, Short RD, Goodyear A, Braithwaite NSJ (2001) The role of ions in the plasma polymerization of allylamine. *J. Phys. Chem. B* **105**, 5730–5736.
 - 31 Mahoney DJ, Whittle JD, Milner CM, Clark SJ, Mulloy B, Buttle DJ *et al.* (2004) A method for the non-covalent immobilization of heparin to surfaces. *Anal. Biochem.* **330**, 123–129.
 - 32 Barbucci R, Magnani A, Albanese A, Tempesti F (1991) Heparinized polyurethane surface through ionic bonding of heparin. *Int. J. Artif. Organs* **14**, 499–507.
 - 33 Lee H, Dellatore SM, Miller WM, Messersmith PB (2007) Mussel-inspired surface chemistry for multifunctional coatings. *Science* **318**, 426–430.
 - 34 Lee H, Rho J, Messersmith PB (2009) Facile conjugation of biomolecules onto surfaces via mussel adhesive protein inspired coatings. *Adv. Mater.* **21**, 431–434.
 - 35 Ibrahim S, Joddar B, Craps M, Ramamurthi A (2007) A surface-tethered model to assess size-specific effects of hyaluronan (HA) on endothelial cells. *Biomaterials* **28**, 825–835.
 - 36 Weng Y, Hou R, Xie D, Wang J, Huang N (2007) Covalent immobilization of heparin on anatase TiO₂ films via chemical adsorbent phosphoric acid interface. *Key Eng. Mater.* **330–332**, 865–868.
 - 37 Heyman PW, Cho CS, McRea JC, Olsen DB, Kim SW (1985) Heparinized polyurethanes: in vitro and in vivo studies. *J. Biomed. Mater. Res.* **19**, 419–436.
 - 38 Russell AJ (2013) Regenerative medicinal chemistry: the in situ control of stem cells. *ACS Med. Chem. Lett.* **4**, 365–368.
 - 39 Nussbaum J, Minami E, Laflamme MA, Virag JAI, Ware CB, Masino A *et al.* (2007) Transplantation of undifferentiated murine embryonic stem cells in the heart: teratoma formation and immune response. *FASEB J.* **21**, 1345–1357.
 - 40 Khademhosseini A, Suh KY, Yang JM, Eng G, Yeh J, Levenberg S *et al.* (2004) Layer-by-layer deposition of hyaluronic acid and poly-L-lysine for patterned cell co-cultures. *Biomaterials* **25**, 3583–3592.
 - 41 Plewa A, Niemiec W, Filipowska J, Osyczka AM, Lach R, Szczubiałka K *et al.* (2011) Photocrosslinkable diazo-resin/pectin films – synthesis and application as cell culture supports. *Eur. Polym. J.* **47**, 1503–1513.
 - 42 Anderson LI (2000) Molecular imprinting for drug bioanalysis: a review on the application of imprinted polymers to solid-phase extraction and binding assay. *J. Chromatogr. B Biomed. Sci. Appl.* **739**, 163.
 - 43 Stöber W, Fink A, Bohn E (1968) Controlled growth of monodisperse silica spheres in the micron size range. *J. Colloid Interf. Sci.* **26**, 62–69.
 - 44 Wybrańska K, Niemiec W, Szczubiałka K, Nowakowska M, Morishima Y (2010) Adenine molecularly imprinted polymer-coated submicrometer silica gel particles. *Chem. Mater.* **22**, 5392–5399.
 - 45 Cao T, Yang S, Cao J, Zhang M, Huang C, Cao W (2001) Nano-assembly film of carboxylic polyaniline with photosensitive diazo-resin and its photoelectric conversion properties. *J. Phys. Chem. B* **105**, 11941–11944.
 - 46 Osyczka AM, Leboy PS (2005) Bone morphogenetic protein regulation of early osteoblast genes in human marrow stromal cells is mediated by extracellular signal-regulated kinase and phosphatidylinositol 3-kinase signaling. *Endocrinol.* **146**, 3428–3437.
 - 47 Cox MM, Nelson DL (2004). *Lehninger Principles of Biochemistry*. New York: WH Freeman, 1100pp.
 - 48 Capila I, Linhardt RJ (2002) Heparin-protein interactions. *Angew. Chem. Int. Ed. Engl.* **41**, 391–412.
 - 49 Lvov Y, Decher G, Möhwald H (1993) Assembly, structural characterization and thermal behavior of layer-by-layer deposited ultrathin films of poly(vinylsulfate) and poly(allylamine). *Langmuir* **9**, 481–486.
 - 50 Zhi J, Tian X, Zhao W, Shen J, Tong B, Dong Y (2008) Self-assembled film based on carboxymethyl- β -cyclodextrin and diazo-resin and its binding properties for methylene blue. *J. Colloid Interface Sci.* **319**, 270–276.
 - 51 Bauer S, Park J, von der Mark K, Schmuki P (2008) Improved attachment of mesenchymal stem cells on super-hydrophobic TiO₂ nanotubes. *Acta Biomater.* **4**, 1576–1582.
 - 52 Liu H, Cheng J, Chen F, Hou F, Bai D, Xi P *et al.* (2014) Biomimetic and cell-mediated mineralization of hydroxyapatite by carrageenan functionalized graphene oxide. *ACS Appl. Mater. Interfaces* **6**, 3132–3240.

Supporting Information

Additional Supporting Information may be found in the online version of this article:

Fig. S1. UV-Vis absorption spectra of DR/CS, DR/Car, and DR/HA (from top to bottom) six-bilayer films.

Fig. S2. IR spectra of a) DR/Hep, b) DR/Car, and c) DR/HA films before (solid line) and after irradiation (dashed line).

Fig. S3. SEM images of DR/Car six-bilayer films coated onto (a) Stöber particles and (b) quartz plates.