Published in final edited form as:

Nat Protoc. 2019 May ; 14(5): 1339–1376. doi:10.1038/s41596-019-0135-9.

Non-genetic optical neuromodulation with silicon-based materials

Yuanwen Jiang^{1,2,*,#}, Ramya Parameswaran^{3,*}, Xiaojian Li^{4,*}, João L. Carvalho-de-Souza^{5,*}, Xiang Gao², Lingyuan Meng⁶, Francisco Bezanilla^{5,7,8}, Gordon M. G. Shepherd⁴, and Bozhi Tian^{1,2,7,#}

¹Department of Chemistry, the University of Chicago, Chicago, IL 60637

²The James Franck Institute, the University of Chicago, Chicago, IL 60637

³The Graduate Program in Biophysical Sciences, the University of Chicago, Chicago, IL 60637

⁴Department of Physiology, Feinberg School of Medicine, Northwestern University, Chicago, IL 60611

⁵Department of Biochemistry and Molecular Biology, the University of Chicago, Chicago, IL 60637

⁶Institute for Molecular Engineering, the University of Chicago, Chicago, IL 60637

⁷Institute for Biophysical Dynamics, the University of Chicago, Chicago, IL 60637

⁸Centro Interdisciplinario de Neurociencia de Valparaíso, Facultad de Ciencias, Universidad de Valparaíso, Valparaíso, Chile

Abstract

Optically-controlled non-genetic neuromodulation represents a promising approach for the fundamental study of neural circuits and the clinical treatment of neurological disorders. Among existing material candidates that can transduce light energy into biologically-relevant cues, silicon (Si) is particularly advantageous due to its highly tunable electrical and optical properties, ease of fabrication into multiple forms, ability to absorb a broad range of light spectrum, and biocompatibility. This protocol describes a rational design principle for Si-based structures, general procedures for material synthesis and device fabrication, a universal method to evaluate material photo-responses, detailed illustrations of all instrumentation used, and demonstrations of optically-controlled non-genetic modulation of cellular calcium dynamics, neuronal excitability, neurotransmitter release from mouse brain slices, and brain activity in the mouse brain *in vivo* using the aforementioned Si materials. The entire procedure takes ~ 4–8 days in the hands of an experienced graduate student, depending on the specific biological targets. We anticipate that our

Corresponding authors: btian@uchicago.edu, yuanwen@uchicago.edu.

*These authors contributed equally to this work.

Author contributions Y.J., R.P., X.L., J.L.C.-d.-S., F.B., G.M.G.S., and B.T. developed the protocol. Y.J., R.P., X.L., and J.L.C.-d.-S. performed the experiments. Y.J., R.P., X.L., and B.T. wrote the manuscript with inputs from all authors.

Competing financial interest The authors declare no competing financial interests.

Data availability statement The authors declare that all data supporting the findings of this study are available within the original papers. Other supporting data are available upon reasonable request to the corresponding author.

approach can be adapted in the future to study other systems such as cardiovascular tissues and microbial communities.

EDITORIAL SUMMARY

This Protocol describes how to fabricate and apply silicon-based structures for optically controlled neuromodulation. The structures can be used for non-genetic neuronal excitation in cultured neurons, brain slices and *in vivo* applications.

Abstract

New Protocol for fabricating and applications of silicon-based structures for optically controlled neuromodulation.

Keywords

Bioelectronic interfaces; Neuromodulation; Photostimulation; Silicon; Bioelectronics; Biointerfaces; Neuroengineering

Introduction

Electrical neuromodulation constitutes the basis of many implantable medical devices that are valuable in treating debilitating medical conditions such as Parkinson's disease, clinical depression, and epilepsy^{1–8}. While traditional stimulation electrodes have significantly improved patients' quality of life, they are often limited by their need to be tethered to electrical wiring and their inability to target single cells. Moreover, the bulky and rigid nature of these electrodes can induce severe inflammation in target tissue^{9–13}. Alternative neuromodulation methods using optical stimuli can significantly alleviate tissue inflammatory responses and offer greater flexibility with even single cell resolution. Over the past decade, optogenetics, or genetic engineering that allows for optical control of cellular activity, has been able to address many of the aforementioned issues with physical electrodes^{14–17}. However, neuromodulation methods that rely on genetic modifications are technically challenging on larger-brained mammals as they may produce unpredictable or even permanent side effects, and are controversial if applied to human subjects. On the other hand, non-genetic photostimulation approaches could revolutionize the field of neuromodulation, especially when minimally invasive, tightly integrated with the target biological system, and able to achieve a high spatiotemporal resolution. Unlike optogenetics that expresses light-gated ion channels or pumps on the cell membrane, non-genetic photostimulation does not alter the biological targets, but instead uses the transient physicochemical outputs from synthetic materials that are attached to the cells or tissues. When the material is illuminated, its light-induced electrical or thermal output yields temporary biophysical responses (*e.g.*, membrane electrical capacitance increase) in neurons, producing a neuromodulation effect in the close proximity to the material.

So far, several light-responsive materials have been utilized for optical neuromodulation, including quantum dots, gold nanoparticles, and semiconducting polymers, and these studies have already suggested the enormous potential of using non-genetic neuromodulation

towards fundamental neuroscience and prosthetic applications. For example, cadmium selenide (CdSe) quantum dots in a nanorod geometry were able to efficiently elicit excitation of retinal ganglion cells in light-insensitive chick retinas with photostimulation¹⁸. In another study, gold nanoparticles deposited on top of primary dorsal root ganglion (DRG) neurons from neonatal rats and mouse hippocampal brain slices were used to elicit action potentials in the target neurons via laser stimulation. Furthermore, it was shown that the nanoparticles could be bound to specific cell types of interest via chemical surface modification with neurotoxins and antibodies¹⁹. Finally, the production of photocurrents from poly(3-hexylthiophene) (P3HT) semiconducting polymer films were used to restore light sensitivity in retinal explants from blind rats and even rescue visual functions *in vivo*^{20,21}.

Besides these existing platforms, Si-based nanostructured materials possess some unique properties that are particularly suited for optical neuromodulation. For instance, Si can be easily fabricated into multiple forms with highly tunable chemical and physical properties and good biocompatibility^{22–26}. Si can also absorb a broad band of light up to near infrared (NIR)^{27,28}, which is particularly suitable for *in vivo* applications given living mammal tissues absorb and scatter less light in this regime^{29,30}. Indeed, the photovoltaic, photoelectrochemical, and thermal properties of Si have been explored thoroughly in the context of energy sciences^{31–34}. However, a precise understanding of Si-based biomaterials and biointerfaces, especially at the nanoscale level, has remained elusive. Recently, we have borrowed concepts from energy sciences and developed a set of Si-based biomaterials, including mesoporous particles³⁵ and coaxial nanowires³⁶, that can achieve optical induction of action potentials in single cells. Furthermore, we have systematically screened a wide variety of Si structures with unique compositions, surface chemistries, and geometries in order to formulate a biological application-guided rational design principle for establishing intra-, inter-, and extracellular neural interfaces (Figure 1a)³⁷. This work has enabled us to non-genetically and optically modulate cellular calcium dynamics, neuronal excitability, neurotransmitter release from brain slices, and brain activity *in vivo* (Figure 1b)³⁷. In this protocol, we present detailed procedures for 1) the synthesis and fabrication of several unique Si materials, 2) the evaluation of material photo-responses, 3) DRG neuron cell culture and brain tissue harvesting, and 4) optical modulation of single cell and brain tissue excitability, as well as animal behaviors. The entire procedure takes ~ 4–8 days in the hands of an experienced graduate student who has been trained in electrophysiological and optic techniques, depending on the specific biological targets (*i.e.*, single cells, tissue slices or animals). We anticipate that our approach can be adapted to other cellular systems, such as cardiovascular tissues or microbial communities, in the future.

Overview of the procedure

This protocol comprises of four major blocks that are connected in series (Figure 2). First of all, the material preparation part includes the synthetic methods for a spectrum of Si materials and devices. These include mesoporous Si particles (Steps 1–12), coaxial Si nanowires (Steps 13–18), Si diode junction membranes (Steps 19–24), and distributed Si meshes (Steps 25–43). Specifically, Si particles and nanowires are used for single cells, along with membranes for cell cultures or brain slices, and meshes for brain tissues *in vivo* (Figure 1b and Figure 2). The photo-response evaluation section introduces a universal

measurement and analysis technique that can quantify individual photo-responses of each Si materials (*i.e.*, photocapacitive, photofaradaic, and photothermal), that will form the basis for their corresponding applications (Steps 44–50). We then described the preparation of different neural systems including cultured DRG neurons from rats (Steps 51–60), mouse brain slices (Steps 91–95), and live mouse brains (Steps 106–112). The last part encompasses the detailed procedures of using the aforementioned Si materials for optical neuromodulation (Steps 61–122). These include photostimulation of cultured DRG neurons (Steps 61–90), acute brain slices (Steps 96–105), and brain cortex *in vivo* (Steps 113–122).

Alternative methods

Current neuromodulation techniques are mostly based on electrical stimulation, such as patch-clamp or multi-electrode arrays (MEA) for cultured neurons and deep brain stimulation for *in vivo* studies. Patch clamp is highly efficacious, especially in the context of biophysical studies and single ion channel studies, and can be used to both depolarize and hyperpolarize cells^{38,39}. However, patch clamp is a highly invasive technique and is only suitable for short-term experiments. Another significant drawback of patch clamp is that the throughput of this technique is extremely low. It normally takes minutes to patch one single cell and it would be extremely difficult to patch multiple cells at the same time, not to mention large-scale modulation of a cell population or even a small tissue. To address the invasiveness and scalability issues, MEA can be used since extracellular electrode arrays can non-invasively depolarize cell membranes at different locations where cells and electrodes form junctions^{40–42}. However, as MEA has limited electrode number and area coverage in cell cultures, a high-density stimulation with random-access capability is hard to achieve. Deep brain stimulation has already been shown effective in treating a number of neurological disorders^{1,3} but the approach is limited by the fact that stimulation electrodes need to be tethered to electrical wiring. Furthermore, the bulky and rigid nature of these electrodes can induce severe inflammation in target tissue, which is deleterious for the long-term studies and treatment of diseases.

Given the intrinsic limitations of electrical stimulation approaches, in particular the need for external wiring, wireless neuromodulation techniques have been emerging as promising alternatives towards both cell-level fundamental studies and organ-level therapeutic benefits. Typically, wireless platforms include the use of light^{18–21,35–37,43}, magnetic fields^{44–46} or acoustic waves^{47–51}. For example, the Anikeeva group at the Massachusetts Institute of Technology has used the magnetothermal property of ferrite (Fe_3O_4) nanoparticles to control intracellular calcium fluxes in neurons. By exposing the nanoparticles to alternating magnetic fields, heat-sensitive ion channels open to induce neural activity⁴⁴. This method allows for the remote control of excitability in specific neurons and could be particularly advantageous for deep brain stimulation, because the alternating magnetic fields in the low radiofrequency range penetrate deep into tissue without significant attenuation⁴⁴. Another methodology that has shown significant promise is ultrasonic neuromodulation. Recent studies from the Tyler group at Arizona State University have demonstrated that focused ultrasound can stimulate neurons in brain slices and even in human brains^{47,52}. Although transcranial ultrasound stimulation can modulate activities as deep as 3 cm in the human

somatosensory cortex, it suffers from a limited lateral spatial resolution of several millimeters, which may be insufficient to obtain precise neuromodulation.

Within the area of light-based technologies, the development of optogenetics in the early 2000s represented a huge leap forward^{14–16}. Optogenetics-based neuromodulation is performed by introducing light-activatable ion channels or pumps into target cells that may be either excitatory or inhibitory for neuronal activity^{15,16}. This technique has been used both for single cell studies and tissue-level studies *in vivo* and has the advantage of being able to target specific cell types with a high spatiotemporal resolution^{17,53–55}. To overcome the need for genetic engineering, which is difficult to implement in humans for the purpose of clinical therapeutics, material-based platforms have emerged in the field of light-based neuromodulation^{19–21,43,56–62}. Two pertinent examples of these methodologies include the use of gold nanoparticles, for photothermal neuromodulation mediated by a change in membrane capacitance (optocapacitance) in both DRG neurons and brain slices¹⁹, as well as semiconducting polymers, such as poly(3-hexylthiophene) (P3HT), for photovoltaic restoration of light-sensitivity in retinal slices of blind rats²⁰. These methods are highly versatile in that they can be applied in free-standing or substrate-based configurations, bypassing the need for gene transfection to photo-sensitize the target cells.

We appreciate that the current protocol only describes one system of remotely controlled non-genetic neuromodulations. Future development of other material systems that can effectively convert external physical inputs into output signals that are recognizable by the biological systems—in combination with advanced imaging and recording techniques—may ultimately lead to an integrated system for multimodal neuromodulations.

Applications

Our studies have demonstrated a class of new technologies for use in neural engineering, especially for the control of neuronal membrane potential and excitability, which are broadly applicable to both fundamental electrophysiological studies and light-controlled therapeutics in the clinic. These Si-based materials can be used for the modulation of cellular excitability—not just in the brain or central nervous system—but potentially also in any other electrically active parts of the body such as the peripheral nervous system, the musculoskeletal system, the cardiovascular system, the visual system, the gastrointestinal (GI) tract, or even the immune system. For potential clinical therapeutics, we have shown that these materials can be implanted surgically. Surface modification of the Si in the future may even realize cell type-specific targeting upon Si administration. Si-based optical modulation of cellular activity could be particularly advantageous in the context of peripheral nerve diseases. These may include diabetic peripheral neuropathy, wound healing processes on the skin, or the restoration of vision as near infrared light can penetrate well into these areas and can be absorbed well by Si. Concerning applications in the deep brain (seizure disorders or Parkinson's disease), in the GI tract (motility disorders) or in the heart (cardiac arrhythmias), Si materials could provide a less immunogenic way to modulate cellular activity as they are highly biocompatible; however, the implantation of a light source at the site of injury may be required.

Si materials can also revolutionize the ways in which fundamental bioelectric studies are conducted as they can remain inert inside of cells or tissues until being triggered to alter the local electrical environment. This minimal invasiveness allows for minor or no alteration in cellular viability upon interfacing with cellular systems and while modulating cellular activity, thus permitting studies that can connect cellular electrical signatures with other biochemical signal processes. This advantage is particularly relevant in the context of non-excitable cells that do not produce action potentials upon membrane depolarization.

Advantages and limitations

Compared to electrical stimulation for *in vitro* studies, optical stimulation cannot only function in a minimally invasive manner but also achieve targeted modulation of specific cells with programmed spatiotemporal profiles. In particular, for cells cultured on Si substrates, a focused laser spot can easily move around the substrate using a laser scanning system and, therefore, stimulate any cell of interest at any time. Owing to the high flexibility of optical stimulation, our approach can also be used for the sequential excitation of calcium dynamics from user-defined locations (see Steps 76–82 for this procedure).

Compared to magnetic and ultrasonic stimulation, optical stimulation has several unique advantages. Specifically, the ability to finely focus the size and precisely tune the power and duration of the light stimulus allows for a high spatial resolution and a fast temporal response from target cells. For example, mesoporous Si particle or Si nanowire based optical neuromodulation of cultured neurons can achieve a one light pulse/one neural spike temporal precision and a subcellular resolution^{35,36}. In contrast, existing magnetothermal stimulation methods depend on a high expression level of transient receptor potential cation channel subfamily V member 1 (TRPV1) channels and thus may still require genetic transfection of the target cells⁴⁴. In addition, unlike the rapid photothermal process, magnetothermal stimulation is typically slower and therefore elicits cellular responses with a higher latency. On the other hand, the exact mechanism of ultrasound-based stimulation is still under debate^{63,64}. For the brain, cortical stimulation using distributed *p-i-n* Si mesh with 500- μ m islands, the size of the light-spot is the limiting factor for spatial stimulation resolution, which is typically around 200- μ m. This level of spatial precision is substantially better than the alternative ultrasonic or magnetic stimulation, whose resolution is on the order of millimeters⁴⁷.

The Si-based approach has certain advantages over other optical stimulation approaches, such as optogenetics. The principal advantage being that there is no need for gene transfection, a process that can be difficult to implement in certain cellular systems, animal models, and in human patients. Furthermore, genetic modification may also have unpredictable consequences for the biophysical properties of the target cell membrane and spatial organization of other transmembrane proteins. Given the rich physicochemical properties of Si-based materials, instead of altering the membrane properties of the biological system, the materials themselves can be tailored to exhibit multiple functions that can achieve neuromodulation of native membranes via various mechanisms, such as photocapacitive, photoelectrochemical, and photothermal processes.

Finally, Si is particularly well suited for optically-controlled neuromodulation compared to other materials. As an inorganic semiconductor, Si can produce thermal, capacitive and Faradaic effects in saline, as opposed to metals, such as Au, that typically only yield heat upon illumination^{19,65}. The Si surface chemistry can also be tuned in a wide range to achieve different photo-response profiles^{20,21,43,61,62}. Second, Si materials and devices with various feature sizes and geometries can be fabricated easily following well-established industrial- or lab-scale processes. For other inorganic semiconductors (such as InP) and semiconducting polymers, despite the fact that they can exist in similar forms with Si, their fabrication procedures are usually more costly and sophisticated. This is particularly the case when nanoscale devices are needed for precise subcellular biophysical studies. Lastly, Si is both biocompatible and biodegradable, an important factor that promises for future transient neuromodulation.

Certain limitations of our current method include the shallow penetration depth of the visible light source in brain tissue and the lack of cell-type specific targeting. Given the small bandgap of Si (~ 1.1 eV), it can absorb light up to the NIR region, providing the potential for minimally invasive deep brain neuromodulation using transcranial photostimulation. In the future, we expect that the surface of Si substrates can be modified with antibodies or other membrane affinity moieties to realize targeted non-genetic neuromodulation.

Experimental design

Subjects.

We have previously used our optically-controlled neuromodulation protocols in cultured DRG neurons from rats^{35,36} (Sprague–Dawley, neonatal pups up to 3 days old), harvested brain slices from euthanized mice³⁷ (C57BL/6J, 6–9 weeks old), and deeply anesthetized mice³⁷ (C57BL/6J, 6–9 weeks old). These subjects were chosen due to the ease of tissue harvesting and surgical procedures. Although we focus on rodents in this protocol, we anticipate that the techniques described here can also be adapted to various other species ranging from *Caenorhabditis elegans* or zebrafish to non-human primates—or even humans, since there is no need to develop species-specific genetic engineering toolkits. All animal studies described in this Protocol followed the guidelines of the National Institutes of Health and Society for Neuroscience. All rat procedures described here were approved by the Institutional Animal Care and Use Committee at the University of Chicago, and all mouse procedures were approved by the Northwestern University Animal Care and Use Committee.

Material designs.

As one of the most thoroughly studied semiconductors, Si possesses many unique physical and chemical properties that are suitable for optically-controlled neuromodulation. Si is biocompatible and biodegradable, shows prominent responses upon light illumination, and can be easily fabricated into various forms. Biological systems are hierarchical in nature and span multiple length scales from submicron-scale organelles to centimeter-scale organs. Therefore, efficacious neuromodulation can only be achieved when the structures and properties of Si are compatible with the biological targets.

When designing a Si material, matching the mechanical properties of the material with those of the biological target is the first consideration. For example, the bending stiffness of a 2D sample scales with the cube of its thickness as defined by $D = Eh^3/12(1 - \nu^2)$, where D is the bending stiffness, E is the Young's modulus, h is the thickness, and ν is the Poisson ratio⁶⁶. Therefore, only a thin membrane of Si can form a conformal interface with a soft and curvilinear tissue, such as a brain cortex. In another scenario, to enable intracellular biointerfaces, Si nanowires can be considered since they may be readily trapped within the cytoskeletal filaments due to their nanoscale anisotropic geometries.

After the material/device geometries are determined, another crucial criterion for neuromodulation is the fundamental photo-response produced by the Si material, a process that is the driving force in the modulation of activity of the target biological system. Our recent studies demonstrated that Si can induce different processes near its surface upon light illumination, such as capacitive coupling, redox reaction, and local heating³⁷. We later uncovered that it is possible to skew the output of a Si material towards one of these processes by altering fundamental components of the Si materials, including size, doping profiles, and surface chemistry. Finally, we formulated a generalized biology-guided rational design principle for Si structures to form tight junctions with biological systems in order to promote efficient signal transduction across the resultant bio-interfaces.

Preparation of Si materials.

In prior works, we used chemical vapor deposition (CVD) to directly grow Si from a gaseous precursor, silane (SiH_4)^{35–37,67}. It is a highly versatile approach that may be extended to a wide variety of substrates to prepare different Si structures such as nanowires, mesoporous particles, and diode junctions (Figure 3). During the synthesis process, a number of parameters such as the chamber temperature and pressure, gas flow rates, and dopant concentrations can be controlled to precisely tune the structures and properties of the resultant Si material. Besides home-built CVD systems, commercial ones with proper gas inlet and temperature control can also work for the Si growth (see Equipment). Other synthetic methods such as chemical reduction and electrochemical etching may also be adopted to expand the Si material library for neuromodulation.

For mesoporous Si particles (Steps 1–12), a hard-template nanocasting process is adopted by decomposing SiH_4 inside the channels of pre-formed mesoporous silica (SiO_2) templates, including but not limited to SBA-15⁶⁸ or KIT-6⁶⁹. Removal of the SiO_2 template then yields an amorphous and mesoporous Si with the inverse structure (Figure 4a). The as-prepared Si particles have both structural and chemical heterogeneity within the porous framework and display a significant reduction in surface stiffness when compared to solid single crystalline Si.

For Si nanowires (Steps 13–18) to promote light absorption, we grow nanocrystalline coaxial nanowires instead of single crystalline ones³¹. Briefly, after the gold-nanocluster catalyzed vapor-liquid-solid (VLS) growth of the single-crystalline core, nanocrystalline shell layers are deposited through a vapor-solid (VS) mechanism at a higher temperature (Figure 4b). Besides uniformly doped Si structures, *p-i-n* coaxial nanowires can also be

synthesized by sequentially flowing in dopant gases such as diborane (B_2H_6) and phosphine (PH_3).

For Si diode junctions (Steps 19–22), a silicon-on-insulator (SOI) wafer is used as a substrate where polycrystalline Si is directly deposited onto the device layers of SOI wafers (Figure 4c). After the CVD growth, post-treatment of the Si surfaces can provide another dimension of control for the material photo-responses. For example, electroless deposition of noble metals such as gold (Au), platinum (Pt), and silver (Ag) can be performed through galvanic displacements to tune the surface chemistry (Steps 23–24). The as-synthesized Si diode junctions can be microfabricated into various geometries, such as meshes, through standard photolithography, metallization, and etching procedures to create a flexible form of Si devices (Steps 25–43) (Figure 5).

Assessment of Si photo-responses.

In this protocol, we also describe our measurement and analysis procedures that can quantify individual photo-responses of Si materials (Steps 44–50). Experimentally, we evaluated the light-triggered physicochemical processes from the Si surfaces using the patch clamp technique, since it is capable of detecting subtle changes of electrical currents in a highly localized area. Typically, Si materials with different compositions or structures were first immersed into a phosphate-buffered saline (PBS) solution before glass micropipette electrodes were positioned at the close proximity to the material surfaces ($\sim 2 \mu m$). Ionic flows through the pipette tips were then continuously monitored in the voltage-clamp mode. In the middle of a trial, light pulses from either a laser or a LED were delivered through a microscope objective onto the Si material while the ionic current dynamics was recorded under different pipette holding levels (Figure 6).

For Si materials, our measurements suggest that a *p-i-n* diode junction is critical to producing pronounced capacitive currents³⁷. Compared to a uniformly doped *p*-type Si, the built-in electric field of the diode junction can effectively separate light-generated charge carriers, and result in more charges being accumulated at the Si/saline interface. With the deposition of metallic species over the Si surfaces, both the capacitive and Faradaic effects can be further enhanced, likely due to a more efficient charge carrier collection and solution injection³⁷. Next, with the fixed composition, the reduction of Si sizes will promote the photothermal effect and thwart the photovoltaic effect since Si with a smaller dimension will naturally have a deficiency of available carriers and an impeded heat dissipation within the confined volume of Si³⁷. Therefore, a Si nanowire will exhibit a substantially higher thermal output upon light illumination when compared to a bulk Si. In addition to size reduction, the introduction of porosity can also significantly improve the Si photothermal effect by promoting light absorption and reducing thermal conductivity and heat capacity^{35,70} (BOX 1).

Besides the intrinsic properties of Si itself, another important factor that can significantly affect the Si photo-response is the light source, especially for Si structures with smaller dimensions. For a coaxial nanowire or a mesoporous particle, only tightly focused lasers can generate pronounced photo-responses; LED illumination, on the other hand, does not induce any detectable signals. Correspondingly, laser illumination on these small objects will evoke

a higher thermal response due to the substantial number of photons being absorbed and the lack of efficient heat dissipation. For a bulk Si diode junction membrane, however, even diffused LED illumination can generate a high amplitude of photocurrent with almost no thermal response (BOX 1).

In vitro experiments on neuron cultures.

In vitro experimentations on cultured neurons is the easiest way to test the feasibility of Si-based photostimulation (Steps 51–90). Using DRG neurons harvested from neonatal rats, we previously demonstrated the successful modulation of cultured neural activities by eliciting action potentials and calcium dynamics. Compared to hippocampal or cortical neurons in the brain, DRG neurons can easily be extracted from the spine without the need for complicated dissections of other parts of the central nervous system (Steps 51–60). For nanostructured materials (*e.g.*, mesoporous Si articles, coaxial Si nanowires), an aqueous suspension of Si is applied to the DRG culture in a drug-like fashion and the Si materials are let to settle onto the cells. Normally, extracellular interfaces with neurons can be formed within ~ 30 min and target cells are then photostimulated by delivering a laser pulse to a cell membrane-supported Si material interacting with a single cell (Steps 61–75) (Figures 7a–c). Due to the unique anisotropic geometry of Si nanowires, they can also be internalized by glial cells, naturally occurring in culture, after ~ 24 h of coculture to form intracellular biointerfaces (Steps 83–90).

In a typical extracellular photostimulation experiment, the electrophysiological responses of the cell can be investigated using the patch clamp technique. When the neuron under illumination is patched in whole cell current clamp mode, by sweeping the laser duration or power, the cell membrane can be passively depolarized to its excitability threshold for action potential firing (Steps 64–75). For the intracellular biointerfaces with glial cells, calcium imaging is typically used to study the stimulation effect since a network level calcium wave propagation can better demonstrate the remote neuromodulation through natural junctions between glia and neurons (Steps 83–84) (Figure 7d). Wafer-scale Si diode junctions can directly serve as the substrate for neuron culture. One advantage of this two-dimensional biointerface is that the laser spot can be arbitrarily aimed at different positions where the cell and the Si form a junction. In this way, we were able to show that calcium waves can be sequentially initiated with a high spatiotemporal resolution (Steps 76–82).

Ex vivo experiment on brain slices.

Utilizing the information from cultured neurons, photostimulation of a small tissue, such as a brain slice, is also possible. In this case, we used a Si mesh fabricated from a *p-i-n* diode junction (from Steps 25–33) for the photostimulation. In principle, the diode junction does not need to be lifted off the handling wafer. In our particular setup, however, the infrared (IR) light for the brain slice imaging comes from the bottom of the microscope such that the Si material should be at least partially transparent to form a decent cell image (Figure 8). The Si membrane is placed underneath a 300- μm slice and the membrane current of a neuron in the middle of the slice is recorded under the voltage clamp mode (Steps 91–105). In this configuration, the recorded neuron is not in direct contact with the Si membrane. Immediately after illuminating the Si mesh, both the photocapacitive artifacts and the

excitatory postsynaptic currents (EPSCs) can be recorded with short temporal delays, meaning that the photostimulation only excites the presynaptic neurons to induce EPSCs, rather than directly evoking spikes, in the recorded postsynaptic neuron. This suggests the possibility of using the Si diode junction as a localized neurostimulator for high spatiotemporal resolution mapping of functional neural circuits.

In vivo experiment on brain cortex.

An important potential application of Si-based neuromodulation is in intact brain circuits, which entails translating the methodology to a live animal model. Compared to the deep brain regions, the brain cortex is easier to access with the Si diode junction thin membranes and the photostimulation platform. Since the traditional stimulation electrode for excitable tissue typically require high capacitive and Faradaic currents for efficacious neuromodulation, we use the Au-decorated *p-i-n* diode junction (from Steps 19–22) as it outputs the maximal currents under light illumination. In addition, we adopt a bilayer device layout consisting of an Au-decorated Si mesh and a holey polydimethylsiloxane (PDMS) membrane (Steps 25–43), a configuration that allows both high flexibility and good handling capability. Notably, the *p*-type side of the diode junction is in contact with the PDMS membrane while the *n*-type side faces the brain cortex to photocathodically modulate neural activities³⁷, similar to the cathodic electrical stimulation⁷¹. The holey structure of the PDMS not only reduces the bending stiffness of the membrane, but also provides paths for the artificial cerebrospinal fluid (ACSF) to contact the *p*-side of the Si mesh and consume the excess holes under illumination.

In our *in vivo* photostimulation experiments, we use a laser scanning system that can easily move the light spot to stimulate different brain regions, such as the somatosensory and the motor cortices, with a single Si mesh attached. To read out the brain activities, extracellular linear arrays are inserted to record neural activities following laser illumination of the somatosensory cortex (Figure 9). In individual trials, enhanced neural activities are evident during the illumination period—with significant photocapacitive artifacts at the light onset and offset points. Importantly, parametric stimulations show that the evoked neural response rate is highly correlated with the stimulation strength, which is essential to using the Si mesh as a precise neuromodulator³⁷. For the motor cortex, evoked movements can serve as direct evidence of the stimulation effect; in the example in our studies we focus on forelimb movements for the ease of video capture (see Anticipated Results).

Materials

Biological materials

- Rats for cultured neuron photostimulation (Sprague-Dawley, P0-P3, Charles River Laboratories)

!CAUTION: All experiments involving rats must conform to relevant institutional and national regulations. All animal procedures that we describe here were approved by the Institutional Animal Care and Use Committee at the University of Chicago.

- Mice for brain slice and in vivo photostimulation (wild-type C57BL/6J, 6–9 weeks old, Jackson Laboratory)

!CAUTION: All experiments involving mice must conform to relevant institutional and national regulations. Animal studies followed the guidelines of the National Institutes of Health and Society for Neuroscience, and were approved by the Northwestern University Animal Care and Use Committee. Mice were maintained as in-house breeding colonies.

Reagents

General Reagents for multiple parts of the procedure

- Ethanol (200 proof, Decon Labs, cat. no. 2701)
!CAUTION: Ethanol is flammable. Avoid any open flame when handling ethanol.
- Isopropanol (IPA; Thermo Fisher Scientific, cat. no. A451SK-4)
!CAUTION: IPA is flammable. Avoid any open flame when handling ethanol.
- Hydrofluoric acid (48% (wt/vol) HF in H₂O; Sigma-Aldrich, cat. no. 30107)
- **! CAUTION:** HF is extremely corrosive. Wear heavy-duty nitrile gloves, acid resistant apron and goggles when using HF. Always have Calgonate first aid and spill kits aside before handling HF. Silane (SiH₄; Airgas)
!CAUTION: SiH₄ is extremely flammable and toxic when inhaled. Must use specialized safety cabinets for storage and usage.
- Hydrogen (H₂; Airgas)
!CAUTION: B₂H₆ is extremely flammable. Must use specialized safety cabinets for storage and usage.
- Diborane (B₂H₆; 100 ppm in H₂, Airgas)
!CAUTION: B₂H₆ is extremely flammable and fatal when inhaled. Must use specialized safety cabinets for storage and usage.
- Phosphine (PH₃; 1000 ppm in H₂, Airgas)
!CAUTION: PH₃ is extremely flammable and fatal when inhaled. Must use specialized safety cabinets for storage and usage.

Synthesis of mesoporous Si particles

- Pluronic P123 (Sigma-Aldrich, cat. no. 435465)
- Hydrochloric acid (HCl; 37% (wt/wt), Sigma-Aldrich, cat. no. 320331)
!CAUTION: Concentration HCl is corrosive. Use it only inside a well-ventilated hood.
- Tetraethyl orthosilicate (TEOS; Sigma-Aldrich, cat. no. 131903)

- cetyltrimethylammonium bromide (CTAB; Sigma-Aldrich, cat. no. H9151)
- *n*-butanol (BuOH; Sigma-Aldrich, cat. no. B7906)
- Quartz test tube (Quartz Scientific Inc., cat. no. 315020)
- Stericup Filter Units (Millipore, cat. no. SCVPU02RE)

Synthesis of coaxial Si nanowires

- Poly L-Lysine (Sigma-Aldrich, cat. no. P8920)
- 50 nm gold colloidal nanoparticles (Ted Pella Inc., cat. no. 15708–5)
- Si wafer (Nova Electronic Materials, cat. no. DN03–10624)
- Tungsten carbide scribe (Ted Pella Inc., cat. no. 829)
- Carbon-tipped tweezer (Ted Pella Inc., cat. no. 5052)

Synthesis of p-i-n Si diode junctions

- Silicon-on-insulator (SOI) wafer (Ultrasil, cat. no. 6–9263)
- Chloroauric acid (HAuCl₄; cat. no. 50790)
- Potassium tetrachloroplatinate(II) (K₂PtCl₄; cat. no. 206075)
- Silver nitrate (AgNO₃; cat. no. 209139)

Fabrication of distributed Si meshes supported on holey PDMS membranes

- Polydimethylsiloxane (PDMS; World Precision Instruments, cat. no. SYLG184)
- MCC primer 80/20 (MicroChem)
- LOR-3A (MicroChem)
- SU-8 2005 (MicroChem)
- SU-8 2050 (MicroChem)
- SU-8 developer (MicroChem)
- Tetrafluoromethane (CF₄; Airgas)
- Argon (Ar; Airgas).
- Remover-PG (MicroChem)
- Hexane (Thermo Fisher Scientific, cat. no. H292–4)
- Polyvinylpyrrolidone (PVP; average Mw ~29,000, Sigma-Aldrich, cat. no. 234257)

Photo-response measurement—1× Phosphate buffered saline (PBS; Thermo Fisher Scientific, cat. no. SH3025602)

- *Dorsal Root Ganglion neuron isolation* DMEM/F12 (Thermo Fisher Scientific, cat. no. 11320033)

- Penicillin/Streptomycin (Sigma-Aldrich, cat. no. P4333)
- Fetal Bovine Serum (FBS; Thermo Fisher Scientific, cat. no. 10438–026)
- Earle's Balanced Salt Solution (EBSS; no calcium, magnesium, and phenol red, Thermo Fisher Scientific, cat. no. 14155–063)
- Trypsin (Worthington, cat. no. TRL3)

Immunofluorescence

- 4% (wt/vol) paraformaldehyde (PFA) in PBS (with magnesium and EGTA, Alfa Aesar, cat. no. J62478)
!CAUTION: PFA is flammable and toxic. Use it only inside a well-ventilated hood.
- Triton X-100 (Sigma-Aldrich, cat. no. X100)
- Bovine serum albumin (BSA; Sigma-Aldrich, cat. no. A2153)
- GFAP (GA5) Mouse mAb (Cell Signaling, cat. no. 3670T)
- NeuN (D4G40) XP Rabbit mAb (Cell Signaling, cat. no. 24307T)
- Goat anti-Mouse IgG (H + L) Superclonal Secondary Antibody, Alexa Fluor 647 (Thermo-Fisher Scientific, cat. no. A28181)
- Goat anti-Rabbit IgG (H + L) Secondary Antibody, Alexa Fluor 488 (Thermo-Fisher Scientific, cat. no. R37116)
- S100 Polyclonal Antibody (Thermo-Fisher Scientific, cat. no. PA5–16257)
- Neurofilament-H (RMdO 20) Mouse mAb (Cell Signaling, cat. no. 2836)
- Goat anti-Rabbit IgG (H+L) Cross-Adsorbed Secondary Antibody, Alexa Fluor 488 (Thermo-Fisher Scientific, cat. no. A11008)
- Goat anti-Mouse IgG (H+L) Cross-Adsorbed Secondary Antibody, Alexa Fluor 647 (Thermo-Fisher Scientific, cat. no. A21235)
- Antifade mountant (SlowFade Diamond, Thermo-Fisher Scientific, cat. no. S36967)

Nail polish (Electron Microscopy Sciences, cat. no. 72180)

In vivo experiment preparation

- Ketamine-xylazine cocktail (ketamine 80–100 mg/kg, xylazine 5–15 mg/kg)
!CAUTION: This is a controlled substance in many countries; in the United States, researchers must register with the DEA and obtain the applicable state license before ordering and using it.

Equipment

General Equipment for multiple parts of the procedure

- KimWipes (Thermo Fisher Scientific, Kimberly-Clark, cat. no. 06–666)
- 1.5 mL Eppendorf tubes (Thermo Fisher Scientific cat. no. 3448)

Si material synthesis (mesoporous particles, coaxial nanowires, diode junctions)

- CVD system (Home-built). **!CRITICAL** Besides home-built CVD systems, commercial ones with proper gas inlet and temperature control can also work for the Si growth. Examples include systems manufactured by FirstNano or Structured Materials Industries.
- Vacuum and pressure control module (MKS Instruments, cat. no. 250E-4-D)
- Flow control and readouts module (MKS Instruments, cat. no. 247D)
- Pirani pressure meter (MKS Instruments, cat. no. 945-A-120-TR)
- Pirani vacuum sensor (MKS Instruments, cat. no. 103450214)
- Automated control valve (MKS Instruments, cat. no. 148JA14CR1M)
- Vacuum and pressure transducer (Baratron® Capacitance Manometer, MKS Instruments, cat. no. 626B)
- Mass flow controllers (MFCs, MKS Instruments, cat. no. 1479A)
- Gas flow manual valves (Swagelok Company, cat. no. 6LVV-DPFR4-P)
- Pneumatic valves (Swagelok Company, cat. no. 6L VV-P1V222P-AA, 6L VV-DPC232P-C)
- Tube furnace (Lindberg/Blue, Thermo Fisher Scientific, cat. no. TF55030A-1)
- Dry vacuum pump (Kashiyama-USA, Inc., cat. no. SDE120TX)
- Quartz tubes (Quartz Plus, Inc., 25.3 mm OD, 22 mm ID)
- Muffle furnace (Barnstead International, cat. no. FB1415M)

Si mesh fabrication

- Oxygen plasma etcher (Plasma Etch, PE-100LF)
- Spin coater (Laurell, WS-650)
- Mask aligner (EV Group, EVG 620)
- Reactive ion etcher (Oxford Instruments, Plasma Pro NGP80 ICP)

Photo-response measurement

- Borosilicate patch pipettes (4-inch thin wall with 1.5-mm outer diameter (OD) and 1.12-mm inner diameter (ID), World Precision Instruments, cat. no. TW150F-4)

- Upright microscope (Olympus, BX61WI)
- 532 nm DPSS laser (Laserglow Technologies, LRS-0532-PFM-00300-05)
- Fiber port (FC/PC, $f=11.0$ mm, 350 – 700 nm, $\varnothing 1.80$ mm waist, Thorlabs, cat. no. PAF-X-11-PC-A)
- Single mode patch cables (405 – 532 nm FC/PC, 2m, Thorlabs, cat. no. P1-405B-FC-2)
- FC/PC fiber adapter plate (with external SM1 thread, Thorlabs, cat. no. SM1FC)
- Cage Plate (SM1-threaded 30 mm, 0.35" thick, 2 retaining rings, 8-32 tap, Thorlabs, cat. no. CP02)
- Cage assembly rod (3" long, $\varnothing 6$ mm, 4 pack, Thorlabs, cat. no. ER3-P4)
- Achromatic doublet lens ($f=45$ mm, $\varnothing 1$ ", SM1-threaded mount, ARC: 400-700 nm, Thorlabs, cat. no. AC254-045-A-ML)
- Neutral density filters (twelve station dual filter wheel for $\varnothing 1$ " filters with base assembly, 10 ND filters include, Thorlabs, cat. no. FW2AND)
- Right-angle kinematic mirror mount (with tapped cage rod holes, 30 mm cage system and SM1 compatible, 8-32 and $\frac{1}{4}$ "-20 mounting holes, Thorlabs, cat. no. KCB1)
- $\varnothing 1$ " Broadband dielectric mirror (400 – 750 nm Thorlabs, cat. no. BB1-E02)
- Lens tube spacer (SM1 without internal threads, 2.5" long, Thorlabs, cat. no. SM1S25)
- Kinematic fluorescence filter cube (30 mm cage compatible, left-turning, $\frac{1}{4}$ "-20 tapped holes, Thorlabs, cat. no. DFM1L)
- Dichroic filter (TRITC, reflection band = 525-556 nm, transmission band = 580-650 nm, Thorlabs, MD568)
- 530 nm LED (mounted, Thorlabs, cat. no. M530L3)
- Adjustable collimation adapter (with $\varnothing 25$ mm lens, AR coating: 350 – 700 nm, Thorlabs, cat. no. SM1P25-A)
- Water-immersion lens (Olympus, UMPLFLN20X/W NA0.5)
- Micro-manipulator (Scientifica, PatchStar)
- Headstage (Axon Instruments, CV203BU)
- Amplifier (Axon Instruments, Axopatch 200B)
- Digitizer (Axon Instruments, Digidata 1550B)
- Automatic temperature controller (Warner Instrument, TC-344B)
- Micropipette puller (Sutter Instrument, P-97)
- Data acquisition software (Molecular Devices, pClamp)

Dorsal Root Ganglion neuron isolation

- Glass bottom dishes (Cellvis, cat. no. D35–10-1-N or World Precision Instruments, cat. no. FD35–100)
- Glass Pasteur pipets (disposable 9” borosilicate glass, Thermo Fisher Scientific, cat. no. 13–678-20D)
- Forceps (Dumont #5, cat. no. RS-5035-Carbon)
- Glass flat bottom vial (20 mL disposable scintillation vial, cat. no. FS74504–30)
- 0.22 µm filter (Millex GP, cat. no. SL9P033RS)
- 10 mL syringe (LuerLock Norm-ject, cat. no. 4100-X00V0)
- 2”×2” cotton gauze sponges (Thermo Fisher Scientific, cat. no. 22–362-178)
- Cell culture incubator (Thermo Fisher Scientific, HERACell 150i)
- 37 °C shaker (Denville Scientific Inc., Incu-Shaker Mini)
- Alcohol burner (Hach, cat. no. 2087742)
- Centrifuge (Thermo Fisher Scientific, cat. no. 75004505)

Cultured neuron photostimulation

- Sonicator (Thermo Fisher Scientific, cat. no. FB11203)
- 532 nm DPSS laser (Ultralasers, CST-H-532nm-500mW)
- Neutral density filters (Thorlabs, cat. no. TRF90)
- Pipette puller (Sutter Instrument Co., P-2000)
- Borosilicate patch pipettes (4-inch thin wall with 1.5-mm outer diameter (OD) and 1.12-mm inner diameter (ID), World Precision Instruments, cat. no. TW150F-4)
- Safety glasses (Thorlabs, cat. no. 390507)
- Silver wire (0.005-inch diameter, World Precision Instruments, cat. no. AGT0510)
- Acousto-optical-modulator (AOM) (NEOS Technologies, N48062–2.5-.55-W-10W)
- Analog-to-digital/digital-to-analog (AD/DA) converter board (Innovative Integration, SBC-6711-A4D4)
- Arbitrary waveform generator (BK Precision, 4075B)
- Inverted microscope (Zeiss, IM 35)
- Dichroic mirror (Chroma Technology Corporation)
- 785 nm notch filter (Chroma Technology Corporation)
- Headstage (Axon Instruments, CV302BU)

- Motorizers (Newport Corporation, 860)
- Motorizer controllers (Newport Corporation, 860MC3)
- 2 mL glass syringe (Becton and Dickinson Cornwall, 3425)
- Micropipette puller (Sutter Instrument, P-87)
- Micro-manipulator (Newport)
- Amplifier (Axon Instruments, Axopatch 200B)
- Inverted confocal microscope (Leica, SP5 II STED-CW)
- Data acquisition software (custom-written for electrophysiology; Leica, LAS AF for calcium imaging)

Brain slice preparation

- Vibratome (Leica, VT1200S)

Brain slice photostimulation

- Borosilicate glass (inner diameter 0.86, outer diameter 1.5 mm, with filament; Warner Instrument)
- Upright microscope (Olympus, BX51WI)
- Video camera (Q-Imaging, Retiga 2000R)
- Infrared LED (850 nm, Thorlabs, M850L2)
- Low-magnification objective lens (Olympus, UPlanSApp 4×/NA 0.16)
- High-magnification water-immersion lens (Olympus, LUMPlanFLN 60×/NA 1.00)
- In-line feedback-controlled heater (Warner Instrument, TC 324B)
- Micropipette puller (Sutter Instrument, P-97)
- Micro-manipulators (Sutter Instrument, MP-225, ROE-200, MPC-200)
- Amplifier (Axon Instruments, Multiclamp 700B)
- Blue laser (473 nm, 50 mW, CNI Laser, MLL-FN473;)
- Laser scan system (Cambridge Technologies, 6210 galvanometer pairs)
- Electro-optical modulator (Conoptics, 302 RM)
- Mechanical shutter (Uniblitz, LS2ZM2, VCM-D1)
- Data acquisition software (Vidrio Technologies, Ephus)

In vivo experiment preparation

- Stainless-steel set screw (single-ended #8–32, Thorlabs, cat. no. SS8S050)
- Spade terminal (non-insulated, McMaster-Carr, cat. no. 69145K438)

- Optical post (1/2" diameter, Thorlabs, cat. no. TR3)
- Feedback-controlled heating pad (Bowdoin, FHC)

In vivo photostimulation

- Blue-laser source (473-nm wavelength, ~100-mW maximum power, ~2-mm beam diameter, Aimplaser, LY473III-100)
- Three-dimensional linear stage (Thorlabs, cat. no. PT3)
- AOM with driver (1 μ s rise time, AA Opto-Electronic, MTS110-A3-VIS)
- Iris (Thorlabs, cat. no. SM1D12D)
- Galvanometer scanner pairs (300 μ s step response, Thorlabs, cat. no. GVSM002)
- Plano-convex spherical lens (Thorlabs, cat. no. LA1484-A)
- Optical post (1.5" diameter, Thorlabs, cat. no. DP12A)
- Bracket (Thorlabs, cat. no. C1515)
- Multifunction (analogue and digital) interface board (National Instruments, NI USB 6229)
- Optical power meter kit (Thorlabs, cat. no. PM130D)
- Graphical user interface (GUI) control software (written in National Instruments LabVIEW program)
- Microelectrode array Si probes (NeuroNexus, A1 $\times$ 32–6mm-50–177)
- Motorized four-axis micromanipulator, assembled by mounting a linear translator (Thorlabs, cat. no. MTSA1) onto a three-axis manipulator (Sutter Instrument, MP285)
- Stereoscope (AmScope, SM-4TPZ)
- Amplifier board (Intan Technologies, RHD2132)
- USB Interface Board (Intan Technologies, RHD2000)
- Experimental interface software (Intan Technologies)
- CMOS camera (FLIR Systems, CM3-U3–13Y3M-CS)
- Fixed focal length lens (Navitar, 35 mm EFL, f/2.0)

Reagent Setup

- **Modified Tyrode's buffer.** 132 mM sodium chloride (NaCl), 4 mM potassium chloride (KCl), 1.8 mM calcium chloride (CaCl₂), 1.2 mM magnesium chloride (MgCl₂), 10 mM (4-(2-hydroxyethyl)-1-piperazineethanesulfonic acid) (HEPES), 5 mM glucose, pH 7.4, 300 mOsm. This buffer can be stored up to multiple weeks at 4 °C.

- **Internal patch pipette solution for DRG.** 150 mM potassium fluoride (KF), 10 mM NaCl, 4.5 mM MgCl₂, 2 mM adenosine triphosphate (ATP), 9 mM (ethylene glycol-bis(β-aminoethyl ether)-N,N,N',N'-tetraacetic acid) (EGTA), 10 mM HEPES, pH 7.4, 310 mOsm. This solution can be stored as small aliquots up to 6 months at −20 °C.
- **Chilled cutting solution.** 110 mM choline chloride, 11.6 mM sodium L-ascorbate, 3.1 mM pyruvic acid, 25 mM sodium bicarbonate (NaHCO₃), 25 mM D-glucose, 2.5 mM KCl, 7 mM MgCl₂, 0.5 mM CaCl₂, 1.25 mM monosodium phosphate (NaH₂PO₄); aerated with 95% O₂/5% CO₂. **!CRITICAL** This solution can be stored up to 1 week at 4 °C but we recommend making it fresh each time before slicing.
- **Artificial cerebrospinal fluid (ACSF).** 127 mM NaCl, 25 mM NaHCO₃, 25 mM D-glucose, 2.5 mM KCl, 1 mM MgCl₂, 2 mM CaCl₂, 1.25 mM NaH₂PO₄. This solution can be stored up to multiple weeks at 4 °C.
- **Cesium- or potassium-based internal solution for brain slice.** 128 mM cesium or potassium methanesulfonate, 10 mM HEPES, 10 mM phosphocreatine, 4 mM MgCl₂, 4 mM ATP, 0.4 mM guanosine triphosphate (GTP), 3 mM ascorbate, 1 mM EGTA, 0.05 mM Alexa Fluor hydrazide; 4 mg/ml biocytin; pH 7.25, 290–295 mOsm. This solution can be stored as small aliquots up to 6 months at −20 °C.

Procedure

Synthesis of Si materials: mesoporous Si particles. Timing: 1 day

!CRITICAL Mesoporous Si is typically prepared by chemical vapor deposition (CVD) of Si inside mesoporous SiO₂ templates, followed by HF etching to remove the template (Figure 3). We demonstrated the feasibility of CVD to grow mesoporous Si using a widely-used template, *i.e.*, wheat-like SBA-15 (Ref.⁶⁸) although templates with different geometries and porosities can also be used in the future.

1. Dissolve 4.0 g Pluronic P123 in a mixture of 108.3 g deionized (DI) water and 24.3 g concentrated HCl solution (37%, wt/wt) in a capped glass bottle at 35 °C.
2. After the P123 is completely dissolved, add 8.3 g TEOS and stir the mixture at 35 °C for 24 h.
3. Age the reaction mixtures in a sealed graduated laboratory glass bottle under static condition at 100 °C for 24 h.
4. Use a 0.22-μm vacuum filter to collect the white product and let it air dry.
5. Place the sample in an alumina crucible with a ramp rate of 100 °C min^{−1} until 500 °C and maintain at 500 °C for 6 h in air.
6. Characterize the SBA-15 template using scanning electron microscopy (SEM), transmission electron microscopy (TEM), and small angle X-ray scattering (SAXS). Expected results include wheat-like morphologies under SEM,

hexagonal (end view) or parallel (side view) channels under TEM, and first three diffraction peaks with scattering vectors q following $1:\sqrt{3}:2$ under SAXS³⁵.

? TROUBLESHOOTING

PAUSE POINT: Store the SBA-15 template in a dry box to avoid moisture trapping in the pores. The sample can be stored indefinitely as long as the humidity is controlled.

7. Load the as-synthesized mesoporous SiO₂ powder close to the bottom of a quartz test tube (diameter: ~1.5 cm), which serves as the inner reactor.
8. Place the inner tube containing SiO₂ template into the center of an outer quartz tube (diameter: ~2.5 cm), which serves as the main chamber for CVD (Figure 3c, left). During the pump down process, slowly evacuate the chamber by setting a minimal value ($\sim 5 \times 10^{-4}$ Torr) for the pressure control.

! CRITICAL STEP: Avoid directly turn on the vacuum valve, which may push the inner tube off the center due to the sudden pressure imbalance.

9. Deposit Si at 500 °C and 40 torr using SiH₄ as the Si precursor and H₂ as the carrier gas. In a typical synthesis, we use 200 mg of SiO₂ template, with flow rates of H₂ and SiH₄ set at 60 and 2 standard cubic centimeters per minute (sccm), and a total CVD duration of 120 min.
10. Use 48% (wt/vol) HF to remove the template for 5–10 min at room temperature (20–25 °C).
11. Use a vacuum filter set to collect the etched sample and rinse it with DI water, IPA and dry in air. The final product is in a brownish powdered form.
12. Characterize the mesoporous Si particles using SEM, TEM, SAXS, and atom probe tomography (APT). Expected results include wheat-like particles with aligned nanowire bundles under SEM (Figure 4a, left), hexagonal (end view in Figure 4a, middle) or parallel (side view in Ref. ³⁵) features under TEM, first three diffraction peaks with scattering vectors q following $1:\sqrt{3}:2$ under SAXS³⁵, and hexagonal organization of Si atoms under APT (Figure 4a, right).

? TROUBLESHOOTING

PAUSE POINT

Synthesis of Si materials: coaxial Si nanowires. Timing: 1 day

! CRITICAL Coaxial Si nanowires are synthesized using a gold (Au) nanocluster-catalyzed CVD growth (Figure 3). A single crystalline core is typically grown at a lower temperature (*e.g.*, 470–485 °C) through a vapor-liquid-solid (VLS) process and nanocrystalline shells can be deposited at a higher temperature (*e.g.*, 600–750 °C) with a vapor-solid (VS) process. During the synthesis, the dopant concentration and sequence can be controlled by the gas flow system to yield a broad spectrum of combinations such as *i-i* (Step 18A) and *p-i-n* (Step 18B) coaxial nanowires for cellular level neuromodulations (Steps 83–84 for *i-i* ones and Steps 61–75 for *p-i-n* ones).

13. **Substrate preparation (Steps 13–18):** Use a tungsten carbide scribe to cut smaller pieces of Si chips from a whole wafer (*e.g.*, an *n*-type <100> substrate) as the growth substrates. A typical size of the substrate is 2×6 or 2×8 cm² for coaxial Si nanowire growth.

? TROUBLESHOOTING

14. For a newly cut substrate, use a N₂ stream to remove debris or dust. This is typically enough to clean the surface. Immerse the clean substrates into 48% (wt/vol) HF to remove the native oxide layers and blow-dry the substrate using N₂.
15. Prepare an Au solution by mixing citrate-stabilized Au colloidal nanoparticles (*e.g.*, 50 nm in diameter), HF, and H₂O with a volume ratio of 1:4.5:4.5. The dilution ratio is empirically determined and should be re-evaluated when starting with Au nanoparticles of a diameter or concentration. Apply the mixture onto the Si substrates and wait for ~ 15 min to ensure that Au can settle down on to the Si surface without native oxide.
16. Gently rinse the substrate by immersing it into a DI water bath. Avoid directly squeezing water onto the substrate since this can wash away the Au catalyst. Use a N₂ gun to blow dry the substrate after rinsing.

! CRITICAL STEP: Avoid using organic solvents (*e.g.*, IPA or acetone) that may deactivate the Au catalyst.

17. Place the growth substrate near the center of the quartz tube and evacuate the chamber to its base pressure before ramping up the temperature to 470 °C (Figure 3c, right).

! CRITICAL STEP: Once the temperature reaches the set point, avoid excessive waiting before introducing gases to the growth chamber to minimize undesired migration and aggregation of the Au catalyst.

18. **Preparing the nanowires (Step 18):** For preparing *i-i* Si nanowires, follow Option A. For preparing *p-i-n* nanowires, follow Option B. The *i-i* Si nanowires have purely the photothermal effect whereas the *p-i-n* ones can have the photovoltaic effect on top of the photothermal one.

A) *i-i* Si nanowires

- i. For an intrinsic-intrinsic coaxial nanowire growth, first synthesize the core by delivering SiH₄ and H₂ at flow rates of 2 and 60 sccm, respectively, and maintain the growth chamber at 40 torr under 470 °C for 20 min.
- ii. After the core growth, switch the SiH₄ flow off and keep the chamber under a H₂ atmosphere (60 sccm, 15 torr) while increasing the temperature to 600 °C for the subsequent shell deposition.

! CRITICAL STEP: The H₂ atmosphere instead of vacuum during the temperature ramping can minimize Au diffusion along the nanowire.

- iii. At 600 °C, deposit the intrinsic shell with flow rates of H₂ and SiH₄ at 0.3 and 60 sccm, respectively, and a chamber pressure of 15 torr for 40 min.

PAUSE POINT

B) p-i-n Si nanowires

- i. To synthesize the p-type core of *p-i-n* coaxial nanowires, introduce SiH₄, B₂H₆ and H₂ at flow rates of 2, 10 and 60 sccm, respectively, to the chamber at 40 torr under 470 °C for 30 min.
- ii. After the core growth, maintain the chamber in a vacuum for 20 min while increasing the tube furnace temperature to 750 °C.

! CRITICAL STEP: This vacuum annealing is critical to the Au diffusion process⁷².

- iii. For the intrinsic Si shell deposition, use 0.3 and 60 sccm flow rates of SiH₄ and H₂, respectively, under 750 °C at a pressure of 20 torr for 15 min. The introduction of a 1.5-sccm flow rate of PH₃ for another 15 min will create the final n-type shell.

PAUSE POINT

Synthesis of Si materials: p-i-n Si diode junctions. Timing: 1 day in total

! CRITICAL Si diode junctions are prepared using the CVD method by directly depositing intrinsic and *n*-type layers of Si onto commercial *p*-type SOI wafers through a VS process. Besides doping profiles and crystallinity, the surface chemistry of the diode junction can also be tuned by post-synthesis surface treatment through electroless deposition of metallic species for *in vivo* applications (Steps 106–122) due to its prominent photocapacitive and photofaradaic responses (BOX 1).

- 19. For a newly cut substrate, use a N₂ stream to remove debris or dust. This is typically enough to clean the surface. Immerse the clean substrates into 48% (wt/vol) HF for ~ 5 min to remove the native oxide layers and blow-dry the substrate using N₂.
- 20. Place the substrate inside a quartz tube for evacuation right after the cleaning process (Figure 3c, right). This step is critical to a good photovoltaic output of the diode junction.

? TROUBLESHOOTING

- 21. Increase the temperature to 650 °C and, after the temperature has stabilized and the pressure reaches the minimal, deposit the intrinsic layer by introducing 0.3 and 60 sccm flow rates of SiH₄ and H₂, respectively, at 15 torr for 20 min.
- 22. Deposit the *n*-type layer with the same flow rates of H₂ and SiH₄ during the intrinsic layer growth plus a 1.5-sccm flow rate of PH₃.

! CRITICAL STEP The as-grown diode junction can be used as it is or be surface modified to further improve its photo-response. A simple yet effective

way to change the Si surface property is to perform galvanic displacement by reducing metallic precursors with surface silicon hydrides (Si-H). The metal-containing solutions can be aqueous dispersion of HAuCl_4 , K_2PtCl_4 , and AgNO_3 at different concentrations (0.01 mM, 0.1 mM, or 1 mM).

23. Prepare a plating solution by mixing the metal precursor with HF. The typical metal concentration is 0.01 mM, 1 mM, or 1 mM while the final HF concentration is 1% (wt/vol).

! CRITICAL STEP: The presence of HF is critical to ensure an oxide-free surface of Si for an efficient reduction of metal precursors.

24. Dip the *p-i-n* diode junction from Step 22 into the plating solution and wait for 3 min at room temperature to finish the electroless deposition.

PAUSE POINT

Synthesis of Si materials: PDMS-supported Au-decorated Si meshes. Timing: 2 days in total!

CRITICAL The fabrication process for PDMS-supported Au-decorated Si meshes is divided into two processes that can be executed in parallel; the preparation of distributed Si meshes (Steps 25–33) and porous PDMS membranes (Steps 34–39). The fabrication of distributed Si meshes is performed with a combination of photolithography and etching techniques while the PDMS membrane is prepared using a soft-lithography technique (Figure 5). The assembled flexible device can be laminated onto the mouse brain cortex for *in vivo* neuromodulation (Steps 106–122).

25. **Fabrication of Si meshes (Steps 25–33):** Prepare a *p-i-n* Si diode junction SOI wafer as described in Step 19–22. Cut the wafer into small pieces (*e.g.*, $2 \times 2 \text{ cm}^2$) using a tungsten carbide scribe.
26. Treat the surface of the substrate with mild O_2 plasma (100 W for 1 min) and spin-coat the wafer with MCC primer (500 rpm for 5 s followed by 3000 rpm for 30 s) to promote the adhesion between Si and the subsequent photoresists.

? TROUBLESHOOTING

27. Spin coat a LOR-3A layer on the as-prepared diode junction SOI wafer (500 rpm for 5 s followed by 3000 rpm for 30 s). Bake the substrate at 190 °C for 10 min on a hot plate.
28. Spin coat a SU-8 2005 photoresist layer on the LOR-3A layer (500 rpm for 5 s followed by 3000 rpm for 30 s). Bake the substrate first at 65 °C for 3 min and then at 95 °C for 3 min.
29. Pattern the distributed mesh structure of SU-8 (Supplementary Data File 1) with a standard photolithography process consisting of ultraviolet (UV) light exposure (200 mJ cm^{-2}), post-exposure baking (65 °C for 3 min and then at 95 °C for 3 min), and developing in the SU-8 developer for 1 min. Rinse the substrate in copious amount of DI water and blow dry by N_2 guns. The as-patterned SU-8

mesh will serve as an etch mask for the subsequent reactive ion etching (RIE) process of Si.

! CRITICAL STEP: To ensure a good mechanical robustness of the mesh, wider interconnecting bridges are desired. In the particular design, 80- μm wide bridges are adopted to connect all the 500 $\times$ 500 μm^2 islands. Additionally, the sharp necks between the bridges and the islands will be the most strained region of the entire device. Curved necks with quarter circle arcs with an 80- μm radius of curvature are introduced to mitigate the strain. Finally, 20- μm diameter holes are evenly distributed within the Si islands to facilitate ion flows for the photostimulation experiment (Figure 5).

30. Hard bake the SU-8 mesh pattern under 180 °C for 20 min to improve its stability under the RIE.
31. During the RIE, introduce CF_4 (45 sccm) and Ar (5 sccm) to etch the unprotected *p-i-n* Si layers. It typically takes 10 min to completely remove the $\sim 2.3 \mu\text{m}$ of Si under a radiofrequency (RF) power of 100 W and an inductive-coupled plasma (ICP) power of 400 W.
32. Lift off the SU-8 protection layer by dissolving the underlying LOR-3A layer using Remover-PG overnight. Rinse the substrate in copious amount of DI water and blow dry using an N_2 .
33. Perform a final wet etching step of the oxide layer with 48% (wt/vol) HF to release the as-patterned Si diode junction.
34. ***Fabrication of porous PDMS membranes (Steps 34–39):*** Cut a *n*-type Si wafer into small pieces (*e.g.*, $2\times 2 \text{ cm}^2$) using a tungsten carbide scribe.
35. Treat the surface of the substrate with mild O_2 plasma (100 W for 1 min) and spin-coat MCC primer (500 rpm for 5 s followed by 3000 rpm for 30 s) to promote the adhesion between Si and the subsequent photoresists.
36. Spin coat a SU-8 2050 photoresist layer on the treated substrate (500 rpm for 5 s followed by 1500 rpm for 30 s). Bake the substrate first at 65 °C for 15 min and then at 95 °C for 45 min.
37. Pattern the SU-8 pillar array (Supplementary Data File 2) by exposing the SU-8 layer with (400 mJ cm^{-2}), baking at 65 °C for 10 min and then at 95 °C for 15 min after exposure, and developing in SU-8 developer for 15 min.
38. Spin coat a layer of PDMS (precursor: curing agent ratio = 10:1 (vol:vol)) onto the SU-8 mold at 2000 rpm for 30 s and cure the substrate at 80 °C overnight.
39. Release the as-cased PDMS layer by dipping the substrate into hexane, which will swell and release the holey PDMS membrane.
40. ***Transfer of the Si mesh onto the holey PDMS membrane (Steps 40–43):*** Use a Si wafer to transfer the as-patterned Si diode junction from Step 33 to a water bath and let the mesh float.

! CRITICAL STEP: Make sure not to flip the Si diode junction so that the *p*-type side of the diode junction will be in contact with the PDMS membrane after the transfer process.

41. Treat the holey PDMS membrane from Step 39 with O₂ plasma (100 W for 1 min) or PVP (25% (wt/vol)) to make the surface hydrophilic.
42. Laminate the Si mesh onto the PDMS membrane by gently dipping and slowing lifting the PDMS layer from the water bath.

? TROUBLESHOOTING

43. Dip the PDMS-supported Si mesh into the plating solution of 1 M HAuCl₄ and 1% (wt/vol) HF and wait for 3 min at room temperature to finish the electroless deposition. Gently rinse the device in DI water and air dry.

PAUSE POINT

Measurement of Si photo-responses Timing: 3 hours

! CRITICAL For the photo-response measurements, a standard patch-clamp setup is typically employed where a glass micro-pipette is placed near a Si material in saline. In this particular demonstration, we use an upright microscope with a water immersion objective to deliver light pulses from either a LED or a laser (Figure 6). To synchronize the light illumination and the current recording, we deliver transistor-transistor logic (TTL) signals from a digitizer to control the timing of the light pulses (*i.e.*, starting time point and duration). For the current recording, we use commercial software (*i.e.*, pClamp from Molecular Devices) to monitor the ionic current dynamics in the voltage-clamp mode of an amplifier.

44. Pull the glass pipettes in a flaming/brown type micropipette puller for a final resistance of ~1 MΩ when filled with 1× PBS.

! CRITICAL STEP: The recorded photo-induced current level will be inversely proportional to the pipette resistance value. Therefore, a fair comparison can only be made when the pipette resistance remains at the similar level.

45. Immerse the Si material in the same PBS solution by directly placing a Si wafer with diode junctions or settling down aqueous suspensions of particles or nanowires.
46. Lower the pipette tip to the close proximity to the Si surface (~2 μm) using a micro-manipulator. Visually determine the distance between the pipette tip and the Si material surface by changing the objective lens focus from the pipette to the Si.

? TROUBLESHOOTING

47. Set the software protocol as follows: In a 250-ms trial, apply a step function of a constant command voltage of −0.5 mV to the pipette electrode between the 100-ms and the 200-ms time points. Apply the voltage bias only to calculate the dark state resistance of the pipette. Starting from the 150-ms time point, a 10-ms wide

TTL signal will be sent to the light source (*i.e.*, LED or laser) to generate a light pulse. By manually adjusting the pipette offset knob, record the ionic currents across the pipette tip under different voltage holding levels.

? TROUBLESHOOTING

48. Fit the plot of the light-induced current amplitude (I_{light}) over the holding level (I_0), and calculate the individual quantities of each photo-response, *i.e.*, capacitive, Faradaic, and thermal. At a given time point, the slope of the $I_{\text{light}}-I_0$ plot represents the photothermal response whereas the intercept of the plot is contributed by the photovoltaic responses. Therefore, photocurrent and temperature over time curves can be generated using the fitted intercept and slope values from each time point (BOX 1).
49. After the photo-response measurement, place the same micropipette into another dish of pre-heated PBS with an initial temperature of about 50 °C and continuously monitor the pipette resistance. Position a thermocouple close to the pipette tip to simultaneously measure the local temperature.
50. Based on the calibrated dependence of pipette resistance over temperature, estimate the value of the local temperature increase by the photothermal process.

PAUSE POINT

Preparing a DRG neuron culture. Timing: 3 hours

51. Decapitate two rat pups (P0-P3) and leave the bodies in a container on ice until they are no longer moving.
! CRITICAL STEP: The dissection does not need to be performed in a sterile tissue culture hood; however, all tools must be thoroughly cleaned prior to use by soaking in 70% ethanol. See Ref.⁷³ for a detailed description of the culture procedure.
52. For dorsal root ganglia resection from the pups, first cut the skin down the center of their backs, open the spinal canal dorsally and longitudinally with scissors, and remove the spinal cord with tweezers. The ganglia sit laterally in between each vertebra, on both sides of the animal (~30 pairs of ganglia in each rat).
! CRITICAL STEP: Center the spinal canal cut as much as possible and do not perforate the abdominal cavity as that can contaminate the culture. Wipe out the open spinal canal once in a while as blood and lymph tend to appear during DRG resection. Blood is especially unwanted during digestion and culture of neurons.
53. Remove the ganglia using ultra-fine tipped forceps and place them into a petri dish containing 2 mL of DMEM/F12 media (no serum) on ice.
54. Transfer the petri dish into a tissue culture hood and transfer the neurons into a 15 mL conical using a glass pipette. Pellet the cells by centrifuging them at room temperature until the speed reaches $100 \times g$ and immediately stop spinning.

55. Remove the supernatant and resuspend the pellet into 3.5 mL of 2.5 mg mL⁻¹ trypsin solution. Transfer the cells in trypsin into a 20 mL flat bottom glass vial, cover with a lid, and shake in a 37 °C shaker (130 rpm) for 20 minutes.

! CRITICAL STEP: The timing of this step is extremely important. A little bit under-digestion is fine while over-digestion often leads to poor cell conditions. DRG should look a bit softened after this step.

56. Coat 6 glass bottom petri dishes or 6 O₂-plasma treated *p-i-n* diode junction substrates (~2×2 mm²) from Step 22 with sterile-filtered 0.01% (wt/vol) poly L-lysine for 20 minutes inside of the tissue culture hood.

57. In the meantime, centrifuge the trypsinized DRGs in a 15 mL conical at 225 × *g* for 2 minutes at room temperature and remove the trypsin containing supernatant. During this step, wash the petri dishes with DI water 3 times.

58. Resuspend the cell pellet in 4 mL EBSS with 10% (vol/vol) FBS and mechanically triturate the DRGs using a glass Pasteur pipette for 5 minutes. Repeat this trituration twice more with two new glass pipettes with smaller tip sizes (make the tip smaller by holding the pipette over a flame).

! CRITICAL STEP: Do not triturate the DRGs for too long. Most of the large cell chunks will disappear by the end, but if the pellet dissolves too quickly, then the ganglia might have already been over-digested by trypsin. The total trituration process should take no longer than 20 minutes and avoid bubble formation.

? TROUBLESHOOTING

59. Centrifuge the digested and triturated DRGs at 225 × *g* for 2 minutes at room temperature and remove the supernatant. Resuspend the pelleted cells into 600 µL of neuron culture media (DMEM/F12 + penicillin/streptomycin + 10% (vol/vol) FBS) and apply 100 µL of cells to the center of each glass bottom dish or *p-i-n* diode junction substrate from Step 22.
60. Incubate the cells in a tissue culture incubator for 20–25 min and flood each of the dishes with 2.5 mL neuron culture media. Check the cells under a microscope and use the cells for experiments within 3 days to avoid overgrowth of fibroblasts and glial cells. The cultured DRG neurons can be used for extracellular stimulation using mesoporous particles or nanowires (Step 61–75), extracellular stimulation using diode junction substrates (Step 76–82), or intracellular stimulation using nanowires (Step 83–90).

PAUSE POINT Cells cultured on the *p-i-n* diode junction substrates can remain viable for at least 7 days. Nevertheless, glial cells will dominate the culture after 3 days such that the identification of neurons for patch clamp electrophysiology will be more challenging.

Extracellular photostimulation of neurons with Si particles and nanowires. Timing: 1 day

! CRITICAL: Either mesoporous Si particles or coaxial Si nanowires can be used for neuromodulation with a subcellular resolution. In both cases, a direct contact between the Si materials and the cells is needed.

61. Mount a dish of neurons from Step 60 onto the electrophysiology setup and remove the media from the dish with a vacuum line.
62. Wash the cells 3 times with modified Tyrode's solution to remove any extracellular proteins from the culture media and leave 1 mL in the dish after the last wash.
63. Both porous Si particles and coaxial Si nanowires can be applied to extracellularly stimulate cultured neurons (Figure 7a–c). When using porous Si particles, follow Option A. When using Si nanowires, follow Option B.

A) Porous Si particles

- i. Grind the porous Si particles from Step 12 for 10 min and suspend 1 mg of particles in 5 mL Tyrode's solution. Sonicate the suspension for 5 min and check the size of particles in a microscope to make sure roughly spherical shapes of ~ 1–2 μm in diameter are abundant.
- ii. Add approximately 50 μL of the suspension containing 0.01 mg of porous Si particles into the cell culture from Step 60 and allow them to settle down for about 5 min.

B) Coaxial Si nanowires

- i. Cut a $0.5 \times 0.5 \text{ cm}^2$ nanowire chip from the wafer piece created in Step 18 using a tungsten carbide scribe.
- ii. Etch the oxide layer off the nanowire chip with a 10% (wt/vol) HF solution for 30 seconds, using carbon-tipped tweezers to handle the nanowire chip.
! CRITICAL STEP: Use freshly made 10% (wt/vol) HF for this step and always complete this step right before nanowire use.
- iii. Wash the chip with DI H_2O for 10 seconds to remove the HF and dry the chip with N_2 gas.
! CRITICAL STEP: Failure to wash the HF off can cause cell death when generating nanowire-neuron biointerfaces.
- iv. Release the nanowires from the growth substrate by placing the chip into an Eppendorf tube with 100 μL of modified Tyrode's solution and sonicating for 1 minute.
- v. Apply 20 μL of the nanowire solution into the glass center of the dish where the neurons are without perturbing the neurons and let the nanowires settle onto the neurons for 20 minutes.

64. Pull several 2 M Ω pipettes in preparation for whole cell patch clamping of DRG neurons (see Ref.⁷⁴ for a detailed description).
65. Fill a pipette with internal solution (see Reagent Setup) and mount onto the Ag/AgCl electrode on the electrophysiology setup.
66. Look through the objective of the microscope in the electrophysiology setup to find a neuron soma that is in contact with a single particle or nanowire. In particular, find a Si material that is positioned in such a way that the neuron will be easy to patch clamp while applying an optical pulse to the Si.
- ! CRITICAL STEP:** The particle or nanowire must be touching the neuron, not just floating slightly above it. Also, be sure that the cell is a neuron, not a glial cell.
67. Turn the laser on and attenuate it using an ND filter of 2.5 in order to align the laser spot onto the neuron-Si interface. Align the spot by moving the stage.
68. Use the micromanipulator to lower the pipette into the extracellular solution of the cell culture and use the microscope to focus on the tip of the pipette.
- ! CRITICAL STEP:** Patch clamp requires prior knowledge and practice of electrophysiology. Several excellent resources are cited here that covered substantial amount of details to master this technique^{39,75–78}.
69. Apply a membrane seal test to check that the resistance of the pipette is optimal (~ 2 M Ω).
70. Allow for the pipette to approach the target cell using the micromanipulator by first quickly getting the pipette to a focal plane just above that of the cell while applying positive pressure through a 5 mL glass syringe so that the pipette does not get clogged with debris (but not so much that the Si particles/nanowires sitting atop the target cell is blown away).
71. Using the slower speed regime of the micromanipulator, very carefully allow for the pipette to touch the cell. In the visual field of the microscope, check that the pipette is creating a small dimple in the cell surface.
72. In order to form a >1 G Ω seal between the pipette and the cell membrane, take away the positive pressure by resetting the three-way connector between the syringe and the pipette. In the case of a healthy cell and optimal pipette approach, this should be enough to create the seal.

73. Apply short suction pulses through the glass syringe to break in the membrane.
74. Switch to the current-clamp mode and be sure that the resting membrane voltage is around -60 mV.
75. Once patched, first inject a 1-ms suprathreshold amplitude current to the neuron to assess its excitability. Apply a laser stimulus (minimum energy of ~ 5 μ J) via a TTL pulse onto the neuron-Si interface and measure the membrane voltage of the cell. Use the waveform generator to generate trains of light pulses.

? TROUBLESHOOTING

Extracellular photostimulation with Si diode junctions. Timing: 1–7 days

! CRITICAL When DRGs are cultured on *p-i-n* Si diode junction substrates (Steps 76–82), the cells can be directly photostimulated because of the significant capacitive currents from the diode junction. Using calcium indicators such as Fluo-4 AM, both intracellular and intercellular signal propagations can be readily mapped under fluorescence microscope, in contrast to patch clamp electrophysiology which can only provide recordings from few cells at most simultaneously. Calcium imaging can be used to study the effect of photostimulation.

76. Prepare a DRG neuron culture as described in Steps 51–60.
77. On the day of experiment, prepare a staining medium by diluting 1 mM Fluo-4 AM in DMSO stock solution with the culture medium (DMEM/F12+10% (vol/vol) FBS) to make a final concentration of 2 μ M for Fluo-4 AM (*i.e.*, 2 μ L stock in 1 mL medium). Replace the original medium with the staining medium and keep the cells in the 37 °C incubator for 30 min.
78. Carefully wash the culture for three times with dye-free media by gently removing and adding the liquid to avoid cell detachment. After the final wash, add 1M HEPES to the medium to make a final concentration of 20 mM to buffer the imaging medium.
79. Cover the imaging dish with aluminum foil when transporting the cells to the pre-warmed confocal microscope (37 °C using the air heater) for the calcium imaging.
80. Flip the culture substrate to make the cells facing downwards. Considering both the field of view, depth of view, and fluorescence intensity, a 40 $\times$ oil lens will typically give the highest quality image.

! CRITICAL STEP: In the inverted confocal microscope setup, the opaque Si substrate will block the bright field light transmission. However, the fluorescence signal will not be affected since the excitation light source and the photodetectors are all sitting at the bottom of the dish.

81. Roughly focus the objective using the bright field illumination to identify the surface with cells and use the fluorescence channel (488 nm laser for excitation, 505–530 nm on Leica HyD detector for emission) to finely focus on the cell of interest.
82. Switch to the fluorescence recovery after photobleaching (FRAP) module of the Leica software for the photostimulation. Position the stimulated emission depletion (STED) laser to arbitrary locations under a cell and record the calcium fluorescence images before and after the laser pulse. Typically, at least 1 mW for 1 ms is needed for observable calcium dynamics. Laser intensity and duration can be controlled by the Leica LAS-AF software.

Glia-enabled intracellular photostimulation with Si nanowires Timing: 1–3 days

! CRITICAL: Si nanowires can be internalized by glial cells. Therefore, intracellular stimulation of the glial cell allows the remote modulation of adjacent neurons through naturally occurring junctions (Figure 7d).eliminating unexpected damage to neurons due to either the material or the laser beam. It also allows the studies of glia-neuron interactions. Calcium imaging can be used to study the intracellular and intercellular processes.

83. Prepare a DRG neuron culture as described in Steps 51–60 incubate them with Si nanowires as described in Step 63B. Glia cells can start to uptake Si nanowires in a few hours, forming intracellular junctions. To ensure a complete internalization, wait for 24 hours before stimulation. For calcium imaging, incubate the cells with 2 μ M of Fluo-4 AM for 30 min at 37 °C and wash the culture for three times with dye-free media before imaging.

? TROUBLESHOOTING

84. Image the stained cells using the confocal microscope and stimulate a nanowire/ glial cell intracellular junction of interest in the middle of a calcium imaging time series as described in Steps 78–82.

Immunostaining of Si nanowires with DRG culture. Timing: 1 day

! CRITICAL After coculturing with neuron cultures as described in Step 51–60, Si nanowires (applied in Step 63B) can be selectively internalized by the glial cells and the cellular colocalization can be imaged after cell-type specific immunostaining. In this protocol, immunostaining was done on separated cell cultures to avoid possible interference from calcium indicators. Patch clamp electrophysiology experiments prior to these steps should not affect the staining result.

85. Prepare a DRG neuron culture as described in Steps 51–60 and incubate them with Si nanowires as described in Step 63B. After adding the nanowires to the neuron culture, incubate them for 1 to 3 days. Nanowires will be shown to overlap with glial cells and have an apparent perinucleus clustering pattern, suggesting they are internalized.

86. To study the colocalization of nanowires with a specific type of cell, perform immunofluorescence by first fixing the DRG and nanowire cocultures on glass coverslips with 4% (wt/vol) PFA in PBS for 10 min at room temperature.
87. After rinsing in PBS, permeabilize the cells with 0.1% (xx/vol) Triton X-100 in PBS for another 10 min at room temperature.
88. Block the cells with 1.5% (wt/vol) BSA in PBS for another 1 hour and incubate with primary antibodies of interest at room temperature for 1 hour. The primary antibodies can be:
  - GFAP (GA5) Mouse mAb, 1:300 (vol:vol) in 1.5% (wt/vol) BSA-PBS or S100 Polyclonal Antibody, 1:100 (vol:vol) in 1.5% (wt/vol) BSA-PBS for glia;
  - NeuN (D4G40) XP Rabbit mAb, 1:50 (vol:vol) in 1.5% (wt/vol) BSA-PBS or Neurofilament-H (RMdO 20) Mouse mAb, 1:200 (vol:vol) in 1.5% (wt/vol) BSA-PBS for neurons.
89. Wash the cells three times with PBS for 5 minutes each. Apply the secondary antibodies for another hour at room temperature. The secondary antibodies can be:
  - Goat anti-Mouse IgG (H+L) Superclonal Secondary Antibody, Alexa Fluor 647, 1:150 (vol:vol) in 1.5% (wt/vol) BSA-PBS or Goat anti-Rabbit IgG (H+L) Cross-Adsorbed Secondary Antibody, Alexa Fluor 488, 1:200 (vol:vol) in 1.5% (wt/vol) BSA-PBS for glia;
  - Goat anti-Rabbit IgG (H+L) Secondary Antibody, Alexa Fluor 488, 1:150 (vol:vol) in 1.5% (wt/vol) BSA-PBS or Goat anti-Mouse IgG (H+L) Cross-Adsorbed Secondary Antibody, Alexa Fluor 647, 1:200 (vol:vol) in 1.5% (wt/vol) BSA-PBS for neurons.
90. Wash the cells 3 times with PBS for 5 minutes each. Add one drop of antifade mounting fluid to the culture. Flip the cover slip onto a glass slide and seal with nail polish. Image the labelled cells using a confocal microscope. Use a scattered light channel to image Si nanowires and fluorescence channels to image the antibodies. Overlay the three channels to check the nanowire colocalization with cells.

Photostimulation of brain slice. Timing: 8 hours

! CRITICAL After the proof-of-concept demonstration on cultured cells, one can evaluate the feasibility of the optically-controlled neuromodulation of a small tissue, such as a brain slice using a larger scale Si structure, such as a *p-i-n* diode junction mesh (from Step 33) (Figure 8).

91. **Brain slice preparation (Steps 91–95):** Euthanize the mice (6–9 weeks old) by anesthetic overdose and decapitation.

92. Quickly remove the brains from the sacrificed mice and place them in the 4 °C chilled cutting solution.
93. Use blocking cuts to trim the brains in order to preserve the apical dendrites of cortical pyramidal neurons.
94. Cut the brain slice using a vibratome in the chilled cutting solution to make 250- μ m slices and transfer the slices to ACSF.
95. Incubate the slices for 30 minutes at 34 °C, and then keep them at 22 °C for at least an hour prior to recording.
96. **Electrophysiology (Steps 96–105):** Warm the bath solution consisted of ACSF to 34 °C by an in-line feedback-controlled heater.
97. Place the Si mesh made of a *p-i-n* diode junction (from Step 33) at the bottom inside the recording chamber of an upright microscope.
98. Transfer a brain slice on top of the Si meshes to form contacts.
99. Image the slices by bright-field gradient contrast microscopy with an infrared light source. Use a low-magnification objective lens to visualize and position the slices and use a high-magnification water-immersion lens to identify neurons for whole-cell recordings.
100. Pull the patch pipettes from borosilicate glass to fine tips (resistance of 2–4 M Ω). Fill the interior of the pipette with internal solution containing potassium-based or cesium-based salts for voltage-clamp recordings.
101. Use micro-manipulators to advance pipettes under positive pressure to establish > 1 G Ω seals onto identified neurons.

! CRITICAL STEP: Details for brain slice patch clamping can be found in the cited references^{79,80}.
102. After membrane rupture to establish whole-cell configuration, record the membrane gating currents with the amplifier. Exclude recordings with series resistance > 40 M Ω which means that the pipette tip is blocked.
103. To isolate excitatory (glutamatergic) post synaptic currents (EPSCs), apply a command potential of –70 mV to the cell.
104. Use a blue laser scanning system for focal spatially targeted photostimulation. To test for input to a neuron, deliver laser pulses onto a nearby spot on the Si film.
- ? TROUBLESHOOTING**
105. Use electrophysiology control software such as Ephus to control hardware settings and other parameters for coordinating photostimulation and electrophysiology data acquisition⁸¹.

In vivo photostimulation. Timing: 1 day

! CRITICAL *In vivo* applications can be tested using Si structures with a high flexibility and a large photo-responses, *e.g.*, a PDMS-supported Au-decorated *p-i-n* Si mesh (from Step 43) that produces substantial capacitive and Faradaic currents upon light illumination (Figure 9).

106. *Animal preparation (Steps 106–112):* Deeply anesthetize the mouse (6–9 weeks old) with ketamine-xylazine injected intraperitoneally.

107. Make a small skin incision over the cerebellum to expose the skull.

108. Fix a stainless-steel set screw crimped with a spade terminal with dental cement to the skull but avoid covering the cortex for craniotomy. It will later be screwed into a tapped hole located at the top of a ½" optical post for the head fixation.

! CRITICAL STEP: Wait for at least 30 minutes to make sure the dental cement is solidified. Details regarding the craniotomy surgery procedure can be found in Ref.⁸².

109. Make craniotomies over the motor and somatosensory cortices using a dental drill with large enough openings (~2.5 mm) to allow the attachment of a Si mesh on the cortex and the passage of a linear probe. The stereotaxic coordinate for the exposed skull area (craniotomy window) was between 2.0 mm anterior and 2.0 mm posterior of the bregma, between 0 mm and 2.5 mm from the midline to lateral.

110. Peel off the dura for a full exposure of the cortex, which is important for a good signal transduction at the Si/brain interface.

111. Place the mouse in the recording apparatus with the body temperature monitored with a rectal probe and maintained at ~37.0 °C via a feedback-controlled heating pad.

112. During the subsequent recordings, frequently apply ACSF to the exposed brain area to prevent the damage from dehydration. Continuously monitor the level of anesthesia based on whisker movements and paw-pinching/eye-blinking reflexes. Give additional anesthetics at 50% of the induction dosage when required.

113. *Electrophysiology (Steps 113–119):* Mount a blue-laser source on a three-dimensional linear stage. The laser beam from the light source goes through an acousto-optic modulator (AOM) and an iris before being deflected by a pair of galvanometer scanners and focused to the target (*i.e.*, PDMS-supported Au-decorated Si mesh) by a plano-convex spherical lens.

114. Control the output laser power using the AOM modulated by signal waveforms delivered via a NI USB 6229 board. Use LabVIEW-based software tool to generate and transfer waveforms to the AOM driver. Calibrate the system using a power meter to determine the relationship between the driver input voltage and the laser scanner output power.

- 115.** Fix a multi-channel linear-array Si probe to a motorized four-axis micromanipulator and position it under stereoscopic visualizations over a distributed Si mesh that has been attached to the cortical surface (with the Si layer facing towards the tissue).

? TROUBLESHOOTING

- 116.** Tilt the probe by $\sim 30^\circ$ off the vertical axis for a better collection of the neural signals under the Si mesh.
- 117.** Slowly insert the probe into the cortex at a rate of $2\ \mu\text{m/s}$, until it reached a depth of $1,600\ \mu\text{m}$ from the pia, with the entry point in the cortex adjacent to the edge of the Si mesh. The coordinate of the somatosensory cortex stimulation and electrophysiological recording was $(-1.0, 2.0)\ \text{mm}$.
- 118.** Deliver laser pulses with various powers and durations onto the Si mesh for the photostimulation of the brain.
- 119.** Amplify and stream the signals using a RHD2132 amplifier board and a RHD2000 USB Interface Board. Use a C++/Qt based experimental interface software for the amplifier configuration, online visualization and data logging.
- 120.** *Forelimb movement stimulation (Steps 120–122):* Use a CMOS camera to record the body movements following the laser stimulations. The coordinates of the forelimb motor cortex stimulation were $(1.0, -1.5)\ \text{mm}$ for the cortex on the left side and $(1.0, 1.5)\ \text{mm}$ for the right side. Mount a fixed focal length lens on the camera for the focusing.
- 121.** Trigger and synchronize the video recording by the laser scanning control board. Under a typical 100-Hz frame rate acquisition, collect 50 frames before the start of the stimulation and record a total of 100 frames for a full trial.
- 122.** Track the centroids of the mouse claws in each frame to investigate the forelimb movements following the laser stimulations.

Timing

Steps 1–12 Synthesis of Si materials: mesoporous Si particles: 1 day

Steps 13–18 Synthesis of Si materials: coaxial Si nanowires: 1 day

Steps 19–24 Synthesis of Si materials: *p-i-n* Si diode junctions: 1 day

Steps 25–43 Synthesis of Si materials: PDMS-supported Au-decorated Si meshes: 2 days

Steps 44–50 Measurement of Si photo-responses: 3 hours

Steps 51–90 Photostimulation of cultured neuron

Steps 51–60 Preparing a DRG neuron culture: 3 hours

Steps 61–75 Extracellular photostimulation of neurons with Si particles and nanowires: 1 day

Steps 76–82 Extracellular photostimulation with Si diode junctions: 1–7 days

Steps 83–84 Glia-enabled intracellular photostimulation with Si nanowires: 1–3 days

Steps 85–90 Immunostaining of Si nanowires with DRG culture: 1 day

Steps 91–105 Photostimulation of brain slice

Steps 91–95 Brain slice preparation: 3–4 hours

Steps 96–105 Electrophysiology: 3–4 hours

Steps 106–122 *In vivo* photostimulation

Steps 106–112 Animal preparation: 3 hours

Steps 113–119 Electrophysiology: 5–6 hours

Steps 120–122 Forelimb movement stimulation: 5–6 hours

Troubleshooting

Troubleshooting guidance can be found in Table 1.

Anticipated results

Upon successful synthesis and fabrication of the different Si materials, we anticipate that they can serve as remotely-controlled neuromodulation devices operating in a non-genetic fashion. Specifically, light illumination of the Si structures with the appropriate intensity is expected to induce neural responses such as action potentials or calcium dynamics on the single cell level. This can further provide synaptic inputs to downstream cells on the population and tissue levels and may even evoke enhanced brain activities and motions on the organ and animal levels. Here, we demonstrate results from all possible interface configurations, namely mesoporous Si particles for extracellular stimulation (Steps 61–75), Si nanowires for intra- (Steps 83–90) and extra-cellular stimulation (Steps 61–75), and Si membranes for extracellular stimulation (Steps 76–82 and Steps 91–122). We anticipate that the procedures described herein can also be modified for similar applications using different Si structures or other materials^{18–21,43,61,62,70,83,84}.

For mesoporous Si particles (fabricated in Steps 1–12), the pronounced photothermal effect can induce rapid capacitance change of the interfacing lipid bilayer (Figure 10a). This optocapacitance effect can then be leveraged to elicit neural action potentials from single DRG neurons with a ~5.32 μJ input energy per pulse³⁵. Under repetitive light pulses, a one-pulse-one-spike correlation can be maintained up to 15 Hz of input frequency depending on the cell condition while some DRG neurons are able to fire even up to 40 Hz³⁵. At higher frequencies, action potential generation becomes less efficient due to the intrinsic limit by the cell condition, although a deterministic sub-threshold depolarization still remains evident (Figure 10b)³⁵.

For coaxial *p-i-n* Si nanowires (fabricated in Steps 13–18), at a laser power of 13.5 mW, subthreshold depolarizations can be evoked at increasing pulse durations up to 0.3 ms; a 0.4-ms duration pulse will elicit an action potential³⁶. Keeping the stimulus duration constant at 1 ms, the membrane was progressively depolarized at increasing laser powers until reaching 6.75 mW, at which an AP was generated (Figure 10c)³⁶. Further investigations of the laser power and duration required to elicit an action potential will result in a hyperbolic excitability curve³⁶. Besides extracellular neuromodulations, intrinsic nanocrystalline Si nanowires can also be selectively internalized by glial cells after coculturing and can serve as a remote neuromodulator by inducing intracellular calcium surges of the glial cells that can later propagate to adjacent neurons (Figure 10d)³⁷.

p-i-n Si diode junction membranes (fabricated in Steps 19–22) can directly serve as the cell culture substrates to form extracellular biointerfaces. In combination with laser scanning systems, any cell of interest on the membrane can be photostimulated with a high spatiotemporal resolution. For example, when a 1-ms long focused laser pulse was delivered to a cell, localized and fast calcium elevation near the illumination site can be readily achieved (Figure 10e)³⁷. By moving the laser spot to adjacent cells, sequential calcium dynamics from arbitrary initiation sites (*i.e.*, either cell body or protrusion) can also be realized, that may be further adapted to probing functional communication networks within a cell population³⁷.

With a distributed *p-i-n* Si mesh (fabricated in Steps 25–42), tissue level—or even organ level—neuromodulation then becomes a possibility. When placed underneath an acute brain slice, capacitive artifacts and excitatory postsynaptic currents can both be induced by laser stimulation (Figure 10f)³⁷. When an Au-decorated *p-i-n* Si mesh (fabricated in Steps 25–43) is placed on a mouse brain cortex, its significant capacitive and Faradaic currents can induce enhanced neural activities during the illumination periods, with waveforms typical of natural extracellular electrophysiological recordings (Figure 10g)³⁷. Finally, following laser illumination of a Si mesh placed on the forelimb primary motor cortex (right side in this case), the contralateral left forelimb of the mouse showed an expected flexion-extension movement (Figure 10h)³⁷.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgements

This work is supported by the Air Force Office of Scientific Research (AFOSR FA9550–18–1–0503), US Army Research Office (W911NF-18–1–0042), US Office of Naval Research (N000141612530, N000141612958), the National Science Foundation (NSF MRSEC, DMR 1420709), the Searle Scholars Foundation, the National Institutes of Health (NIH NS101488, NS061963, GM030376, R21-EY023430, R21-EY027101), MSTP Training Grant (T32GM007281), and the Paul and Daisy Soros Foundation. Atom-probe tomography was performed at the Northwestern University Center for Atom-Probe Tomography (NUCAPT), whose APT was purchased and upgraded with funding from NSF-MRI (DMR-0420532) and ONR-DURIP (N00014–0400798, N00014–0610539, N00014–0910781) grants. NUCAPT is a Research Facility at the Materials Research Center of Northwestern University, supported by the National Science Foundation's MRSEC program (grant number DMR-1121262). Instrumentation at NUCAPT was further upgraded by the Initiative for Sustainability and Energy at Northwestern (ISEN). This work made use of the Japan Electron Optics Laboratory (JEOL) JEM-ARM200CF and JEOL JEM-3010 TEM in the Electron Microscopy Service of the Research Resources Center at the University of Illinois

at Chicago (UIC). The acquisition of the UIC JEOL JEM-ARM200CF was supported by an MRI-R2 grant from the National Science Foundation (DMR-0959470).

References

1. Ashkan K, Rogers P, Bergman H & Ughrtdar I Insights into the mechanisms of deep brain stimulation. *Nat. Rev. Neurol* 13, 548–554 (2017). [PubMed: 28752857]
2. Famm K, Litt B, Tracey KJ, Boyden ES & Slaoui M Drug discovery: A jump-start for electroceuticals. *Nature* 496, 159–161 (2013). [PubMed: 23579662]
3. Wichmann T & DeLong MR Deep brain stimulation for neurologic and neuropsychiatric disorders. *Neuron* 52, 197–204 (2006). [PubMed: 17015236]
4. Fisher RS & Velasco AL Electrical brain stimulation for epilepsy. *Nat. Rev. Neurol* 10, 261–270 (2014). [PubMed: 24709892]
5. Jefferys JG Nonsynaptic modulation of neuronal activity in the brain: Electric currents and extracellular ions. *Physiol. Rev* 75, 689–723 (1995). [PubMed: 7480159]
6. Fregni F & Pascual-Leone A Technology insight: Noninvasive brain stimulation in neurology—perspectives on the therapeutic potential of rtms and tdc. *Nat. Clin. Pract. Neurol* 3, 383–393 (2007). [PubMed: 17611487]
7. Perlmutter JS & Mink JW Deep brain stimulation. *Annu. Rev. Neurosci* 29, 229–257 (2006). [PubMed: 16776585]
8. Kringelbach ML, Jenkinson N, Owen SL & Aziz TZ Translational principles of deep brain stimulation. *Nat. Rev. Neurosci* 8, 623–635 (2007). [PubMed: 17637800]
9. Chen R, Canales A & Anikeeva P Neural recording and modulation technologies. *Nat. Rev. Mater* 2, 16093 (2017).
10. Lacour SP, Courtine G & Guck J Materials and technologies for soft implantable neuroprostheses. *Nat. Rev. Mater* 1, 16063 (2016).
11. Salatino JW, Ludwig KA, Kozai TDY & Purcell EK Glial responses to implanted electrodes in the brain. *Nat. Biomed. Eng* 1, 862–877 (2017). [PubMed: 30505625]
12. Jeong JW et al. Soft materials in neuroengineering for hard problems in neuroscience. *Neuron* 86, 175–186 (2015). [PubMed: 25856493]
13. Mineev IR et al. Biomaterials. Electronic dura mater for long-term multimodal neural interfaces. *Science* 347, 159–163 (2015). [PubMed: 25574019]
14. Boyden ES, Zhang F, Bamberg E, Nagel G & Deisseroth K Millisecond-timescale, genetically targeted optical control of neural activity. *Nat. Neurosci* 8, 1263–1268 (2005). [PubMed: 16116447]
15. Zhang F et al. The microbial opsin family of optogenetic tools. *Cell* 147, 1446–1457 (2011). [PubMed: 22196724]
16. Zhang F et al. Multimodal fast optical interrogation of neural circuitry. *Nature* 446, 633–639 (2007). [PubMed: 17410168]
17. Yizhar O, Fenno LE, Davidson TJ, Mogri M & Deisseroth K Optogenetics in neural systems. *Neuron* 71, 9–34 (2011). [PubMed: 21745635]
18. Bareket L et al. Semiconductor nanorod-carbon nanotube biomimetic films for wire-free photostimulation of blind retinas. *Nano Lett* 14, 6685–6692 (2014). [PubMed: 25350365]
19. Carvalho-de-Souza JL et al. Photosensitivity of neurons enabled by cell-targeted gold nanoparticles. *Neuron* 86, 207–217 (2015). [PubMed: 25772189]
20. Ghezzi D et al. A polymer optoelectronic interface restores light sensitivity in blind rat retinas. *Nat. Photonics* 7, 400–406 (2013). [PubMed: 27158258]
21. Maya-Vetencourt JF et al. A fully organic retinal prosthesis restores vision in a rat model of degenerative blindness. *Nat. Mater* 16, 681–689 (2017). [PubMed: 28250420]
22. Kim DH et al. Stretchable and foldable silicon integrated circuits. *Science* 320, 507–511 (2008). [PubMed: 18369106]
23. Patolsky F et al. Detection, stimulation, and inhibition of neuronal signals with high-density nanowire transistor arrays. *Science* 313, 1100–1104 (2006). [PubMed: 16931757]

24. Tian B et al. Three-dimensional, flexible nanoscale field-effect transistors as localized bioprobes. *Science* 329, 830–834 (2010). [PubMed: 20705858]
25. Tian B et al. Macroporous nanowire nanoelectronic scaffolds for synthetic tissues. *Nat. Mater* 11, 986–994 (2012). [PubMed: 22922448]
26. Jiang Y & Tian B Inorganic semiconductor biointerfaces. *Nat. Rev. Mater* 3, 473–490 (2018).
27. Wang W, Wu S, Reinhardt K, Lu Y & Chen S Broadband light absorption enhancement in thin-film silicon solar cells. *Nano Lett* 10, 2012–2018 (2010). [PubMed: 20446722]
28. Wang KX, Yu Z, Liu V, Cui Y & Fan S Absorption enhancement in ultrathin crystalline silicon solar cells with antireflection and light-trapping nanocone gratings. *Nano Lett* 12, 1616–1619 (2012). [PubMed: 22356436]
29. Hong G, Antaris AL & Dai H Near-infrared fluorophores for biomedical imaging. *Nat. Biomed. Eng* 1, 0010 (2017).
30. Yun SH & Kwok SJJ Light in diagnosis, therapy and surgery. *Nat. Biomed. Eng* 1, 0008 (2017). [PubMed: 28649464]
31. Tian B et al. Coaxial silicon nanowires as solar cells and nanoelectronic power sources. *Nature* 449, 885–889 (2007). [PubMed: 17943126]
32. Walter MG et al. Solar water splitting cells. *Chem. Rev* 110, 6446–6473 (2010). [PubMed: 21062097]
33. Hochbaum AI et al. Enhanced thermoelectric performance of rough silicon nanowires. *Nature* 451, 163–167 (2008). [PubMed: 18185582]
34. Roder PB, Smith BE, Davis EJ & Pauzauskie PJ Photothermal heating of nanowires. *J. Phys. Chem. C* 118, 1407–1416 (2014).
35. Jiang Y et al. Heterogeneous silicon mesostructures for lipid-supported bioelectric interfaces. *Nat. Mater* 15, 1023–1030 (2016). [PubMed: 27348576]
36. Parameswaran R et al. Photoelectrochemical modulation of neuronal activity with free-standing coaxial silicon nanowires. *Nat. Nanotechnol* 13, 260–266 (2018). [PubMed: 29459654]
37. Jiang Y et al. Rational design of silicon structures for optically controlled multiscale biointerfaces. *Nat. Biomed. Eng* 2, 508–521 (2018). [PubMed: 30906646]
38. Verkhratsky A, Krishtal OA & Petersen OH From galvanic to patch clamp: The development of electrophysiology. *Pflügers Arch* 453, 233–247 (2006). [PubMed: 17072639]
39. Sakmann B & Neher E Single-channel recording 2nd edn, (Springer US, 1995).
40. Hai A, Shappir J & Spira ME Long-term, multisite, parallel, in-cell recording and stimulation by an array of extracellular microelectrodes. *J. Neurophysiol* 104, 559–568 (2010). [PubMed: 20427620]
41. Spira ME & Hai A Multi-electrode array technologies for neuroscience and cardiology. *Nat. Nanotechnol* 8, 83–94 (2013). [PubMed: 23380931]
42. Robinson JT et al. Vertical nanowire electrode arrays as a scalable platform for intracellular interfacing to neuronal circuits. *Nat. Nanotechnol* 7, 180–184 (2012). [PubMed: 22231664]
43. Ghezzi D et al. A hybrid bioorganic interface for neuronal photoactivation. *Nat. Commun* 2, 166 (2011). [PubMed: 21266966]
44. Chen R, Romero G, Christiansen MG, Mohr A & Anikeeva P Wireless magnetothermal deep brain stimulation. *Science* 347, 1477–1480 (2015). [PubMed: 25765068]
45. Dobson J Remote control of cellular behaviour with magnetic nanoparticles. *Nat. Nanotechnol* 3, 139–143 (2008). [PubMed: 18654485]
46. Huang H, Delikanli S, Zeng H, Ferkey DM & Pralle A Remote control of ion channels and neurons through magnetic-field heating of nanoparticles. *Nat. Nanotechnol* 5, 602–606 (2010). [PubMed: 20581833]
47. Legon W et al. Transcranial focused ultrasound modulates the activity of primary somatosensory cortex in humans. *Nat. Neurosci* 17, 322–329 (2014). [PubMed: 24413698]
48. Marino A et al. Piezoelectric nanoparticle-assisted wireless neuronal stimulation. *ACS Nano* 9, 7678–7689 (2015). [PubMed: 26168074]
49. Tufail Y et al. Transcranial pulsed ultrasound stimulates intact brain circuits. *Neuron* 66, 681–694 (2010). [PubMed: 20547127]

50. Tufail Y, Yoshihiro A, Pati S, Li MM & Tyler WJ Ultrasonic neuromodulation by brain stimulation with transcranial ultrasound. *Nat. Protoc* 6, 1453–1470 (2011). [PubMed: 21886108]
51. Tyler WJ, Lani SW & Hwang GM Ultrasonic modulation of neural circuit activity. *Curr. Opin. Neurobiol* 50, 222–231 (2018). [PubMed: 29674264]
52. Tyler WJ et al. Remote excitation of neuronal circuits using low-intensity, low-frequency ultrasound. *PLoS One* 3, e3511 (2008). [PubMed: 18958151]
53. Montgomery KL, Iyer SM, Christensen AJ, Deisseroth K & Delp SL Beyond the brain: Optogenetic control in the spinal cord and peripheral nervous system. *Sci. Transl. Med* 8, 337rv335 (2016).
54. Maimon BE, Sparks K, Srinivasan S, Zorzos AN & Herr HM Spectrally distinct channelrhodopsins for two-colour optogenetic peripheral nerve stimulation. *Nat. Biomed. Eng* 2, 485–496 (2018). [PubMed: 30948823]
55. Klapoetke NC et al. Independent optical excitation of distinct neural populations. *Nat. Methods* 11, 338–346 (2014). [PubMed: 24509633]
56. Lorach H et al. Photovoltaic restoration of sight with high visual acuity. *Nat. Med* 21, 476–482 (2015). [PubMed: 25915832]
57. Mandel Y et al. Cortical responses elicited by photovoltaic subretinal prostheses exhibit similarities to visually evoked potentials. *Nat. Commun* 4, 1980 (2013). [PubMed: 23778557]
58. Mathieson K et al. Photovoltaic retinal prosthesis with high pixel density. *Nat. Photonics* 6, 391–397 (2012). [PubMed: 23049619]
59. Lugo K, Miao X, Rieke F & Lin LY Remote switching of cellular activity and cell signaling using light in conjunction with quantum dots. *Biomed. Opt. Express* 3, 447–454 (2012). [PubMed: 22435093]
60. Pappas TC et al. Nanoscale engineering of a cellular interface with semiconductor nanoparticle films for photoelectric stimulation of neurons. *Nano Lett* 7, 513–519 (2007). [PubMed: 17298018]
61. Rand D et al. Direct electrical neurostimulation with organic pigment photocapacitors. *Adv. Mater* 30, e1707292 (2018). [PubMed: 29717514]
62. Sytnyk M et al. Cellular interfaces with hydrogen-bonded organic semiconductor hierarchical nanocrystals. *Nat. Commun* 8, 91 (2017). [PubMed: 28733618]
63. Sato T, Shapiro MG & Tsao DY Ultrasonic neuromodulation causes widespread cortical activation via an indirect auditory mechanism. *Neuron* 98, 1031–1041 (2018). [PubMed: 29804920]
64. Guo H et al. Ultrasound produces extensive brain activation via a cochlear pathway. *Neuron* 98, 1020–1030 (2018). [PubMed: 29804919]
65. Yoo S, Hong S, Choi Y, Park JH & Nam Y Photothermal inhibition of neural activity with near-infrared-sensitive nanotransducers. *ACS Nano* 8, 8040–8049 (2014). [PubMed: 25046316]
66. Rogers JA, Lagally MG & Nuzzo RG Synthesis, assembly and applications of semiconductor nanomembranes. *Nature* 477, 45–53 (2011). [PubMed: 21886156]
67. Patolsky F, Zheng G & Lieber CM Fabrication of silicon nanowire devices for ultrasensitive, label-free, real-time detection of biological and chemical species. *Nat. Protoc* 1, 1711–1724 (2006). [PubMed: 17487154]
68. Zhao D et al. Triblock copolymer syntheses of mesoporous silica with periodic 50 to 300 angstrom pores. *Science* 279, 548–552 (1998). [PubMed: 9438845]
69. Kleitz F, Choi SH & Ryoo R Cubic Ia3d large mesoporous silica: Synthesis and replication to platinum nanowires, carbon nanorods and carbon nanotubes. *Chem. Commun*, 2136–2137 (2003).
70. Fang Y et al. Texturing silicon nanowires for highly localized optical modulation of cellular dynamics. *Nano Lett* 18, 4487–4492 (2018). [PubMed: 29894630]
71. Merrill DR, Bikson M & Jefferys JG Electrical stimulation of excitable tissue: Design of efficacious and safe protocols. *J. Neurosci. Methods* 141, 171–198 (2005). [PubMed: 15661300]
72. Luo Z et al. Atomic gold-enabled three-dimensional lithography for silicon mesostructures. *Science* 348, 1451–1455 (2015). [PubMed: 26113718]
73. Melli G & Hoke A Dorsal root ganglia sensory neuronal cultures: A tool for drug discovery for peripheral neuropathies. *Expert Opin. Drug. Discov* 4, 1035–1045 (2009). [PubMed: 20657751]

74. Pipette cookbook 2018: P-97 & P-1000 micropipette pullers, https://www.sutter.com/PDFs/pipette_cookbook.pdf (2018).
75. The Axon™ guide: A guide to electrophysiology and biophysics laboratory techniques, <https://mdc.custhelp.com/euf/assets/content/Axon%20Guide%203rd%20edition.pdf> (2012).
76. Molleman A Patch clamping: An introductory guide to patch clamp electrophysiology (John Wiley & Sons, 2003).
77. Rueda AG Whole cell patch clamp recordings for characterizing neuronal electrical properties of iPSC-derive neurons, <https://docs.axolbio.com/wp-content/uploads/patch-clamp-protocol-final.pdf> (2018).
78. Hamill OP, Marty A, Neher E, Sakmann B & Sigworth FJ Improved patch-clamp techniques for high-resolution current recording from cells and cell-free membrane patches. *Pflügers Arch* 391, 85–100 (1981). [PubMed: 6270629]
79. Edwards FA, Konnerth A, Sakmann B & Takahashi T A thin slice preparation for patch clamp recordings from neurones of the mammalian central nervous system. *Pflügers Arch* 414, 600–612 (1989). [PubMed: 2780225]
80. Stuart GJ, Dodt HU & Sakmann B Patch-clamp recordings from the soma and dendrites of neurons in brain slices using infrared video microscopy. *Pflügers Arch* 423, 511–518 (1993). [PubMed: 8351200]
81. Suter BA et al. Ephus: Multipurpose data acquisition software for neuroscience experiments. *Front. Neural Circuits* 4, 100 (2010). [PubMed: 21960959]
82. Mostany R & Portera-Cailliau C A craniotomy surgery procedure for chronic brain imaging. *J. Vis. Exp.* e680 (2008).
83. Tang J et al. Nanowire arrays restore vision in blind mice. *Nat. Commun* 9, 786 (2018). [PubMed: 29511183]
84. Savchenko A et al. Graphene biointerfaces for optical stimulation of cells. *Sci. Adv* 4, eaat0351 (2018). [PubMed: 29795786]
85. Yao J, Liu B & Qin F Rapid temperature jump by infrared diode laser irradiation for patch-clamp studies. *Biophys J* 96, 3611–3619 (2009). [PubMed: 19413966]

BOX 1**Analysis of the photo-response measurement.**

In a typical measurement, the pipette potential is first held at a fixed level (V_p) and gives rise to a dark state current (I_0). In the middle of the trial, a light pulse with a certain duration is delivered to the Si material to induce the light-generated current ($I_{\text{light}}(t)$). One important note is that, during the light illumination period, both the photovoltaically-induced currents and the photothermal heating due to the Si material can contribute to ($I_{\text{light}}(t)$). The first part is apparent since the counterions in the saline will naturally be attracted due to the photovoltaically-induced surface potential changes. The second part is implicit since the photothermal effect itself does not directly induce ion flows. Rather, the locally elevated saline temperature will increase the ion mobility, and therefore result in a reduced pipette resistance R . Under the fixed V_p , the current flowing through the tip during the light illumination period will be higher than I_0 . Governed by the Ohm's law, the amplitude of the photothermally-induced ionic current ($I_{\text{thermal}}(t)$) will be proportional to the holding potential V_p while the photovoltaically-induced ionic currents ($I_{\text{electric}}(t)$) is only a function of the carrier dynamics on the Si surface and independent of the pipette holding level.

Given the drastically different dependence on the holding potential, the photovoltaic and the photothermal effects of Si may be potentially decoupled by analyzing the recorded currents at different holding potentials. During the light illumination, the recorded current ($I_0 + I_{\text{light}}(t)$) at a given time point excluding the photovoltaically-induced current ($I_{\text{electric}}(t)$), and the pipette tip resistance $R(t)$ will follow the Ohm's law when the holding potential V_p is fixed.

$$V_p = I_0 \times R_0 = (I_0 + \Delta I_{\text{light}}(t) - \Delta I_{\text{electric}}(t)) \times R(t). \quad (1)$$

Eq. 1 can be rearranged to better describe the relationship between the light-induced current $I_{\text{light}}(t)$ and the holding current I_0 that

$$\Delta I_{\text{light}}(t) = \left(\frac{R_0}{R(t)} - 1 \right) \times I_0 + \Delta I_{\text{electric}}(t). \quad (2)$$

As shown in Eq. 2, the photovoltaic effect is clearly shown by the intercept of the curve. Depending on the temporal scale and the amplitude of the currents, two subtypes of the photo-responses, *i.e.*, capacitive and Faradaic, can be further defined. Briefly, the spiky features near the onset and offset points of the light illumination are capacitive currents from the capacitive charging/discharging processes at the Si/saline interface (BOX Figure panel a, top). A long-lasting current with a lower amplitude is the Faradaic current from the surface redox reactions (BOX Figure panel b, top).

The photothermal effect, however, is implicitly embedded in the fitted slope as the pipette resistance is a function of temperature (BOX Figure panel c, top). The amplitude of the

photothermally-induced temperature change from the surrounding medium can be calculated as long as relationship between the pipette resistance and the temperature is calibrated, which typically follows the Arrhenius equation⁸⁵ that

$$\ln R = a \times \frac{1}{T} + c, \quad (3)$$

where a and c are the slope and intercept values, respectively. Combining with the slope $k(t)$ from the $I_{\text{light}}(t) - I_0$ plot that

$$R(t) = \frac{R_0}{k(t) + 1}, \quad (4)$$

the temperature value of the surround medium due to the photothermal heating can be expressed using the slopes of the $I_{\text{light}}(t) - I_0$ and the $\ln R - 1/T$ curves as well as the initial temperature that

$$T(t) = \frac{1}{\frac{1}{T_0} - \frac{1}{a} \ln(k(t) + 1)}. \quad (5)$$

Taken together, plotting the $I_{\text{light}}(t) - I_0$ curve can serve as a general method to assess the photo-responses of various Si materials and, most importantly, it can be applied to virtually all kinds of materials other than just Si. Since the photothermal effect is a function of the illumination duration (*i.e.*, the heat source for Fourier thermal conduction), the slope of the $I_{\text{light}}(t) - I_0$ plot is also time dependent. The maximal temperature is reached at the end point of illumination so one can simply plot the

$I_{\text{light}, t(\text{end})} - I_0$ curve to assess the photothermal responses of the material. The following four categories summarize the possible photo-responses of the $I_{\text{light}}(t) - I_0$ plotted at the end point of the light illumination t_{end} .

1) In one extreme scenario where the material has only the photovoltaic effect without any photothermal effect, *i.e.*, $R_0 = R_{t(\text{end})}$, Eq. 2 can be written as

$$\Delta I_{\text{light}, t(\text{end})} = \Delta I_{\text{electric}, t(\text{end})}. \quad (7)$$

The $\Delta I_{\text{light}, t(\text{end})} - I_0$ plot will be a horizontal line with a non-zero intercept. For example, pure capacitive responses generated from *p-i-n* diode junction membranes under LED illumination (BOX Figure panel a, bottom) or both capacitive and Faradaic responses generated from metal-decorated *p-i-n* diode junction membranes under LED illumination (BOX Figure panel b, bottom).

2) In another extreme case where the material has only the photothermal effect without any photovoltaic effect, *i.e.*, $I_{\text{electric}} = 0$ at all time, Eq. 2 will be reduced to

$$\Delta I_{\text{light}, t(\text{end})} = \left(\frac{R_0}{R_{t(\text{end})}} - 1 \right) \times I_0. \quad (6)$$

The $\Delta I_{\text{light}, t(\text{end})} - I_0$ plot will be a slanted line with a zero intercept. For example, the pure thermal responses generated from intrinsic coaxial nanowires or mesoporous particles under laser illumination (BOX Figure panel c, bottom).

3) If a material does not have any photo-responses, Eq. 2 will be

$$\Delta I_{\text{light}, t(\text{end})} = 0. \quad (8)$$

The $\Delta I_{\text{light}, t(\text{end})} - I_0$ plot will be a horizontal line with a zero intercept.

4) In any intermediate situations where both the photovoltaic and the photothermal effects coexist, the original form of Eq. 2 applies that

$$\Delta I_{\text{light}, t(\text{end})} = \left(\frac{R_0}{R_{t(\text{end})}} - 1 \right) \times I_0 + \Delta I_{\text{electric}, t(\text{end})}. \quad (9)$$

The $\Delta I_{\text{light}, t(\text{end})} - I_0$ plot will be a slanted line with a non-zero intercept.

Fundamental physicochemical processes occurring at the Si surface upon light illumination and general strategies to promote individual photo-responses are summarized in BOX Figure panel d as a selection guide for particular neuromodulation applications³³.

Figure 1. A rational design principle of Si structures for optically-controlled neuromodulation.

a, A schematic diagram illustrating the biology-guided neural interface design. The biological targets place criteria on the material structure (Selection I) and function (Selection II) to establish functional neural with efficient signal transductions across the tight junctions upon light illumination. b, Selected Si structures in this protocol for optically-controlled neuromodulation. They are nanowires (Steps 83–90) for organelle level interfaces, nanowires (Steps 61–75), particles (Steps 61–75), and membranes (Steps 76–82 and Steps 91–105) for cell and tissue level interfaces, and meshes (Steps 106–122) for organ level interfaces. a and b are adapted with permission from Ref.³⁷, Nature Publishing Group.

Figure 2. Schematic overview of the entire protocol.
Four major blocks of procedures are illustrated on the left side, with details of different combinations between Si materials and neural systems connected on the right side.

Figure 3. Experimental setup for the CVD growth of Si materials.

a, A schematic diagram of the home-built CVD system. Three subsystems for gas delivery, reactor, and pumping are highlighted. b, A schematic diagram of the gas flow valve manifolds, including the pneumatic valves, mass flow controllers, and manual valves. c, A photograph of the CVD control modules for the vacuum level, gas flow rates, and valves of the growth chamber. d, A photograph of the growth chamber (*i.e.*, a quartz tube), the tube furnace for temperature control, gas flow valve manifolds, vacuum and pressure transducer, and the vacuum sensor. The orange box marks the region with detailed schematics in b. e, Photographs showing the growth substrates for Si materials. Mesoporous SiO₂ template inside an inner quartz test tube can be used for porous particle growths. A Si wafer placed at the center of the quartz tube can be used for both nanowire or membrane growths. a is adapted with permission from Ref.⁶⁷, Nature Publishing Group.

Figure 4. Structural characterizations of Si material building blocks.

a, Scanning electron microscope (SEM) image (left), transmission electron microscope (TEM) image (middle), and atom probe tomography (APT) reconstruction (right) of mesoporous Si particles produced in Steps 1–12. The particles are consisting of aligned Si nanowire bundles with a hexagonal mesoscale ordering. Scale bars, 100 nm (left); 100 nm (middle); 20 nm (right). b, SEM (left), side-view TEM (middle), cross-sectional TEM (upper right), and selected area electron diffraction (SAED) pattern (lower right) of coaxial Si nanowires produced in Steps 13–18. These nanowires have a single crystalline core and a nanocrystalline shell. Notably, both the dopant type and concentration can be controlled during the CVD growth to yield uniformly doped or diode junction structures. Scale bars, 1 μm (left); 100 nm (middle); 50 nm (upper right). c, TEM, SEM, and SAED of a *p-i-n* Si diode junction produced in Steps 19–22. The nanocrystalline intrinsic and the n-type layers were grown epitaxially from a single crystalline p-type SOI wafer as evidenced by the

SAED patterns taken at different locations of the diode junction. Scale bars, 200 nm (upper left); 200 nm (upper right). a is adapted with permission from Ref.³⁵, Nature Publishing Group. b and c are adapted with permission from Ref.³⁷, Nature Publishing Group.

Author Manuscript

Author Manuscript

Author Manuscript

Author Manuscript

Figure 5. The fabrication process of the PDMS-supported Si mesh (Steps 25–43).

Fabrication of the distributed Si mesh through photolithography (Steps 25–29), RIE (Steps 30–31), and wet etching (Steps 32–33) processes. Fabrication of the holey PDMS membrane using soft lithography (Steps 34–39). Transfer of the Si mesh onto the PDMS membrane (Steps 40–43) and corresponding photos and SEM image of the final device. Photomask designs for the Si mesh and the SU-8 pillar array are included. Black denotes chromium; White denotes the exposed area on the soda lime glass mask. Scale bars in 7/VII, 500 µm (left); 2 mm (upper right); 200 µm (lower right). Adapted with permission from Ref.³⁷, Nature Publishing Group.

Figure 6. Experimental setup of the photo-response measurement (Steps 44–50).

a, Schematic diagrams illustrating the measurement configuration. Light pulses (530 nm LED or 532 nm laser) are delivered through a water-immersion objective to the Si material immersed in a PBS solution. A glass micropipette is placed near the material surface with a $\sim 2 \mu\text{m}$ distance. Light-induced currents are recorded at different pipette command potentials (V_p) under a voltage-clamp mode. R_{feedback} is the resistance of a feedback resistor for the amplifier. b, Front view of an upright microscope showing the light path for the laser stimulation. c, Side view of the microscope showing the light path for the LED stimulation. d, A photograph of a micro-manipulator controller (to move the micropipette), an amplifier (to record ionic currents), and a digitizer (to send TTL signals for light pulse controls and to interface the amplifier and the computer). a is adapted with permission from Ref.³⁷, Nature Publishing Group.

Figure 7. Experimental setups for the *in vitro* photostimulation of cultured neurons (Steps 51–90).

a, Schematic diagrams illustrating the connections between individual pieces of equipment of the patch clamp setup. Si particles and Si nanowires can be applied onto a cultured DRG neuron for the photostimulation with laser pulses. A1 and A3 are high gain amplifiers whereas A2 has gain of one and it just works as a differential amplifier. b, Photographs of the associated amplifier, AD/DA converter, waveform generator, and the AOM controller (left) and the inverted microscope equipped with a laser setup for the photostimulation experiment (right). c, Photographs highlighting important components of the setup, including the 532 nm laser and the AOM (left), the ND filters (middle), and the electrodes (right). d, Photographs of an inverted laser scanning confocal microscope that can monitor calcium dynamics during the photostimulation experiment (top). A 592 nm stimulated emission depletion (STED) laser is used as the stimulation light source, and the laser scanner

allows arbitrary aiming of the laser spot onto the point of interest for the stimulation (bottom). a is adapted with permission from Refs.^{35,36}, Nature Publishing Group.

Author Manuscript

Author Manuscript

Author Manuscript

Author Manuscript

Figure 8. Experimental setup for the photostimulation of acute brain slices (Steps 91–105).
 a, A schematic diagram of the photostimulation setup and optical micrographs showing the Si/slice interface and the patched neuron. Scale bars, 250 μm (upper right); 10 μm (lower right). b, A photograph of an upright microscope equipped with an 850 nm IR LED for imaging. c, A photograph of external devices to control the stimulation light sources (473 nm laser or multi-wavelength LEDs), the Pockels cell for laser modulation, the stage heater, and the micro-manipulator for the photostimulation experiment. d, Side views of the microscope showing the light paths for LED (top) and laser (bottom) stimulation. The laser scanning system allows the photostimulation of multiple sites of the Si mesh for functional circuit mapping. a is adapted with permission from Ref.³⁷, Nature Publishing Group.

Figure 9. Experimental setup for the *in vivo* photostimulation experiment (Steps 106–122).
a, A block diagram of the entire setup combining the laser scanning photostimulation (LSPS) system, the linear array system with five probes for electrophysiology, the video system, the input/output (I/O) interface, and the graphical user interface (GUI). **b**, A schematic diagram highlighting the layout of the photostimulation experiment. The mouse brain covered by the Si mesh is stimulated by the laser from the scanning assembly and a linear array recording electrode is inserted into the nearby cortex. **c**, Photographs of the operating platform overview (left), highlighting the laser scanning assembly (middle), and the electrophysiological recording geometry (right). **d**, Photographs of the I/O interface (left) and the GUI (right) for controls of manipulators, laser scanning, electrophysiology, camera, and data analysis. **b** is adapted with permission from Ref.³⁷, Nature Publishing Group.

Figure 10. Expected results of Si-based optically-controlled neuromodulation.

a, Local solution temperature (top) and bilayer capacitance (bottom) dynamics following laser pulses onto a sheet of mesoporous Si particles supported by a suspended lipid bilayer with different input energies (laser power, 22.4 mW; black, 0.5 ms; red, 1.0 ms; blue, 1.5 ms; olive, 2.0 ms). b, Porous Si particle-enabled modulation of cultured neurons. Representative membrane potential recordings of a DRG neuron with trains of laser pulses (5.32 μJ) delivered to a membrane supported particle at different frequencies, with corresponding FFTs (right). f and f_0 are output and input frequencies, respectively. Green bars indicate when 532 nm laser pulses were delivered. c, *p-i-n* coaxial Si nanowire-enabled modulation of cultured neurons. Patch-clamp electrophysiology current-clamp traces of membrane voltage in DRG neurons illuminated by 532 nm laser pulses at the neuron/nanowire interface with different durations and powers. In general, longer or stronger laser pulses can elicit action potentials while shorter or weaker ones can only depolarize the membrane. d, Glial

cell-internalized intrinsic coaxial Si nanowire-enabled remote modulation of cultured neurons. Calcium imaging time series (green, calcium; blue, Si nanowires) show that the initial calcium surge of the glial cell due to photostimulation of an internalized nanowire can propagate to both adjacent glial cells and neurons. Scale bars, 20 μm . e, *p-i-n* Si diode junctions enable high spatiotemporal-resolution extracellular stimulation of calcium dynamics. Laser illumination (592 nm, ~ 14.4 mW) of cells in a DRG culture (green: calcium) on a *p-i-n* Si diode junction, induced localized and fast calcium elevation near the stimulation site and subsequent calcium wave propagation both intra- and inter-cellularly. Laser stimulation was 1-ms long before the time point of 2.722 s. The white arrow marks the laser stimulation site. Scale bars, 20 μm . f, *p-i-n* Si mesh-enabled modulation of acute brain slices. Data traces from voltage-clamp recordings of the patched neuron with 1-ms-long laser stimulations (left, cyan bar). The grey dashed box marks the time frame for zoomed-in views on the right. EPSCs are marked by stars following the illuminations of the Si mesh (right). The cyan shaded area marks the illumination period in each trial. # denotes the photocapacitive artifact from the Si. g, Au-decorated *p-i-n* Si mesh-enabled modulation of brain activities. Data traces of neural responses from four adjacent channels in one stimulation. The light blue band marks the illumination period (left). A mean neuron-firing waveform (orange) superposed on individual waveforms (grey) of both spontaneous and stimulation-evoked activities (right). The maroon shaded area denotes standard deviations. h, Au-decorated *p-i-n* Si mesh-enabled modulation of animal motions. The left limb (green dot) of the mouse moves up and down following the laser illumination of a Si mesh attached to the right side of the forelimb primary motor cortex. Time-dependent mean limb movements show a preferred motion of the left forelimb after the stimulation. The 0 ms time point represents the start of the light pulse. Shaded areas denote s.e.m. of the data. Scale bars, 1 cm. All rat procedures described here were approved by the Institutional Animal Care and Use Committee at the University of Chicago, and all mouse procedures were approved by the Northwestern University Animal Care and Use Committee. a and b are adapted with permission from Ref.³⁵, Nature Publishing Group. c is adapted with permission from Ref.³⁶, Nature Publishing Group. d-h are adapted with permission from Ref.³⁷, Nature Publishing Group.

Table 1:

Troubleshooting Table

Step	Problem	Possible reason	Solution
6	Poor uniformity of SBA-15 under SEM. Poor hexagonal symmetry from TEM and SAXS	P123 is not completely dissolved in water. The aging process was perturbed.	Stir P123 for at least 30 min to form a uniform solution before adding TEOS. Make sure the aging process is done in a static condition for 24 h.
12	Excessive Si coating on the outer layer of the particle surface under SEM	Si deposition time was too long or SiH ₄ flow rate was too high during the CVD process.	Make sure to use a small quartz tube rather than a quartz boat for the deposition. Perform the synthesis with the exact flow and duration each time.
13	Low uniformity of nanowire diameter and crystallinity.	Gas flow patterns depend highly on the position of the growth wafer. An inconsistent dimension of the growth substrate will introduce large variations from batch to batch; Gold catalysts aggregate together.	Try to cut the growth Si wafers to the same size for each growth and position them at the center of the quartz tube. For a quartz tube of 1-inch inner diameter, a ~ 2-cm wide wafer is typically desired to yield high quality Si growth with good reproducibility; Start the growth right after the temperature reaches the set point in vacuum to avoid over-diffusion and aggregation of the gold nanoparticles.
20	Low photo-response from <i>p-i-n</i> Si diode junctions using LED illumination.	Bad contacts between the substrate and the layers grown by CVD; Undesired doping due to contaminants from used quartz tubes.	Use HF to remove native surface oxide of Si substrates immediately before putting in the CVD chamber to ensure a good contact; Always bake the quartz tube at 950 °C and perform dummy runs prior to any synthesis.
26	The masking SU-8 layer detached from the Si surface after development.	Poor adhesion between SU-8/LOR-3A and the Si wafer.	Use oxygen plasma and MCC primer to modify the Si surface before spin coating.
42	Si mesh cannot be properly transferred onto the holey PDMS membrane.	PDMS is not hydrophilic enough.	Use O ₂ plasma or PVP to treat the PDMS surface prior to the transfer.
46	No photo-response from Si nanowires/nanoparticles using laser illumination.	Laser spot, micropipette, and Si are not aligned well.	Stabilize the headstage and the micromanipulator to minimize drifting; Do not touch the optical table after determining the laser spot position under the microscope.
47	No light pulse is delivered to the Si materials.	Bad contacts at BNC connectors; The light source is not set at the correct trigger mode; The right filter set is not chosen.	Check all the BNC connectors, especially at the T-junctions; Check the laser or LED controllers to make sure they are can be externally triggered by TTL signals; Check the filters at the microscope to make sure they can transmit the wavelength of the light source.
58	Neurons are too sparse or in bad conditions.	Over-digestion due to prolonged trypsinization or mechanical trituration; neuron cell density is too low.	Shorten trypsin incubation time or mechanical trituration time. Distribute cells into fewer plates.
75	Optical pulse of neuron-NW interface does not produce an action potential.	NW is not touching neuron; NW was not HF etched properly; laser pulse is not aligned onto the NW; cell is not a neuron; neuron is not healthy.	Try a different cell and check by moving focus up and down that NW is truly touching the cell. Check that the laser is aligned and that the NW did not move during the experiment. Check morphologically that the cell is indeed a neuron. It is optimal to use the neurons on day 0 or 1 after culture because the culture is not overrun by glial cells or fibroblasts and the neurons are healthiest then. Prepare fresh 10% wt/vol HF solution. Always test that the cell is producing action potentials via injected current before optically stimulating.
83	Cells are dead before the calcium imaging.	The staining concentration is too high or the staining time is too long.	Start with a low concentration of Fluo-4 AM (~ 2 μM) and optimize the staining based on the cell density and condition. Perform the calcium imaging right after the staining is ready (the staining typically takes ~ 30 min).
104	No response of the patched cell from the brain slice after photostimulation.	Poor contact between the Si mesh and the bottom of the brain slice; The patched cell does not necessarily form synaptic junctions with the cell being stimulated.	Use brain slice anchors, such as a harp, to ensure a good contact; Stimulate at different locations of the Si mesh and test the stimulation response.
115	The Si mesh cannot form conformal contacts with the brain cortex.	The PDMS membrane is not hydrophilic enough.	Use a brief O ₂ plasma to activate the PDMS membrane. Prolonged plasma may damage the surface of Si that may lead to negative impacts.