Published in final edited form as:

Chem Commun (Camb). 2019 January 31; 55(11): 1631–1634. doi:10.1039/c8cc09401b.

Modulating ICT emission: a new strategy to manipulate the CPL sign in chiral emitters†

Josué Jiménez^a, Florencio Moreno^a, Beatriz L. Maroto^a, Trevor A. Cabreros^b, Angelenia S. Huy^b, Gilles Muller^b, Jorge Bañuelos^c, Santiago de la Moya^a

^aDepartamento de Química Orgánica, Facultad de Ciencias Químicas, Universidad Complutense de Madrid, Ciudad Universitaria s/n, Madrid, 28040, Spain.

^bDepartment of Chemistry, San José State University, San José, CA 95192-0101, USA

^cDepartamento de Química Física, Facultad de Ciencias y Tecnología, Universidad del País Vasco-EHU, Bilbao, 48080, Spain

Abstract

A new strategy to manipulate the circularly polarized luminescence (CPL) handedness in chiral emitters, based on modulating the population of an emissive ICT state, is proposed. Such a strategy is particularly interesting for conformationally rigid and non-aggregating chiral organic emitters, opening up new perspectives for the development of CPL applications based on organic molecules.

Circularly polarized luminescence (CPL) is the differential emission of right and left circularly polarized light by non-racemic chiral luminescent systems (molecules, polymers, ionic pairs, supra-molecular aggregates, *etc.*) or achiral ones in non-racemic chiral environments (*e.g.*, chiral crystals, solvents, *etc.*).¹ Research on this chiroptical phenomenon has experienced a noticeable growth in the last decade, mainly in that related to the development of efficient CPL emitters based on simple (small-sized, non-polymeric and non-aggregated) organic molecules (SOMs).² The interest of CPL lies in the higher resolution provided by the circular polarization of the light, which is key for the development and improvement of smarter photonic tools, such as 3D displays,³ data storage, enciphering and processing devices (quantum information technology),⁴ chemo-sensors and bioprobes,⁵ or ellipsometry-based tomographers.⁶ On the other hand, resolution and differential interaction with chiral matter makes CPL an unavoidable source of information to study the chirality at excited states (CPL spectroscopy),⁷ but also to discern and quantify chiral enantiomers (CPL chiral sensing).⁸ Moreover, CPL has been successfully used to promote asymmetric reactions,⁹ as well as to control chiral morphologies in nanomaterials.

10

†Electronic supplementary information (ESI) available: Experimental details, and supplementary tables and figures, as well as synthetic procedures and characterization data for new compounds. See DOI: [10.1039/c8cc09401b](https://doi.org/10.1039/c8cc09401b)

santmoya@ucm.es.

Conflicts of interest

There are no conflicts to declare.

The level of CPL is quantified by the luminescence dissymmetry factor, g_{lum} , whose values stand between -2 and $+2$ (full right and left polarized emission, respectively).¹¹ Reversal of the CPL handedness (g_{lum} sign; CPL sign) has been highlighted as a useful phenomenon with huge potential for the development of sophisticated optical materials and devices.¹² However, changing the CPL sign in a chiral emitter, without changing its absolute configuration, is rare and it has been generally achieved only by two general strategies: (1) modifying the 3D geometry in flexible chromophoric systems;^{12a,13} (2) promoting excimer emission,^{12b,14} since key CPL differences (sign and level) are possible when such species are at play (note that emission from excimers should involve states with very different geometries, as they only exist at the excited state). Therefore, research directed to expand the strategies to manipulate the CPL sign, especially in conformationally-rigid emitters or without the capability to interact, intra or intermolecularly, promoting excimer emission, is needed to advance in the development of smarter photonic applications based on CPL.

Boron dipyrromethenes (BODIPY dyes) have emerged as interesting CPL-enabling SOMs.^{12c,15,16} This is due to the possibility of combining CPL with the outstanding physical and chemical properties of the BODIPY dyes, such as good solubility in many different solvents, low aggregation capability, high chemical robustness and photostability, large both light-absorption coefficients and fluorescence quantum yields, and workable chemistry allowing ample structural diversity.¹⁷ Moreover, CPL BODIPYs exhibit a good linear correlation between their absolute g_{lum} and g_{abs} values, the latter being the absorbance dissymmetry ratio,¹⁸ availing the potential of the BODIPY dyes as useful SOMs to develop CPL applications. However, although BODIPY chemistry allows finely modulating different photonic properties,¹⁹ it has been marginally explored with the aim of manipulating the CPL sign.^{16b}

Herein, we have investigated a new strategy to change the CPL sign. We have used a family of CPL-enabling *O*-BODIPY dyes for this purpose. The strategy introduced here could be expanded to other chiral emitters and is particularly interesting for manipulating the CPL sign in conformationally-rigid and non-aggregating emitting systems.

Our research is based on the following hypothesis: promoting the population of an intramolecular charge-transfer (ICT) state enabling CPL with opposite sign to that obtained from the locally-excited (LE) state should serve to manipulate the CPL sign, since such an emission should provide a larger $|g_{\text{lum}}|$ value than that from the LE state (note the weaker character of the ICT transition; see Fig. 1).^{1,2a} It should be also noted that the subtle structural change caused by the ICT could be enough to induce a change in the potential energy surface and the vibrational frequency and spacing,^{2b} as significant as to reverse the ICT-CPL handedness when compared to the LE-CPL one in some cases.

As a hypothesis-confirming bias, we realized from previous data reported by us that related, conformationally-rigid, non-aggregating and chiral *O*-BODIPY dyes (*R*)-**1a** and (*R*)-**1b** (see Fig. 2) exhibit CPL with opposite signs upon visible (vis) irradiation (*i.e.*, BODIPY-chromophore excitation) in chloroform solution under identical experimental conditions (maximum $g_{\text{lum}}(568 \text{ nm}) = +0.7 \times 10^{-3}$ for (*R*)-**1a** and $g_{\text{lum}}(589 \text{ nm}) = -0.6 \times 10^{-3}$ for (*R*)-**1b**; see Fig. 3).^{16a,c} This fact seems striking, since both dyes involve very similar

BODIPY chromophores. In fact, (*R*)-**1a** and (*R*)-**1b** show similar vis electronic circular dichroism (ECD) spectra, with the same negative sign, under identical conditions (maximum g_{abs} (ca. 525 nm) = -0.9×10^{-3} for both dyes in chloroform solution; see Fig. 3 and Table S1 in ESI†).^{16a,c} However, both dyes are also known to show very different capability to populate emissive ICT states: higher for BINOL-based **1a**; undetectable for 3,3'-dibromoBINOL-based **1b**.¹⁹ Thus, the luminescent ICT state of **1a**, originated by charge transfer from the electron-rich BINOL moiety to the electron-poor BODIPY core,¹⁹ must be responsible for the observed change in the CPL sign.

To confirm this hypothesis, we decided to chiroptically study (*R*)-**1c** and (*R*)-**1d** in comparison to related (*R*)-**1a** and (*R*)-**1b** (Fig. 2). Thus, the known high capability of the VAPOL (2,2'-diphenyl-3,3'-biphenanthr-4-ol) moiety of (*R*)-**1d** to promote ICT in such a dye upon its vis excitation¹⁹ could induce a change in the sign of the observed vis CPL when compared to that of the corresponding vis ECD (*i.e.*, opposite signs for the corresponding g_{lum} and g_{abs} values), as it occurs in ICT-enabling BINOL-based (*R*)-**1a**. Oppositely, the demonstrated incapability of the 3,3'-bis[(3,5-trifluoromethyl)phenyl]BINOL moiety of (*R*)-**1c** to promote ICT in this dye¹⁹ should keep the CPL sign in agreement with that of the ECD spectrum, as it happens in 3,3'-dibromoBINOL-based (*R*)-**1b**.

(*R*)-**1c** and (*R*)-**1d** were straightforwardly prepared from commercial (*R*)-3,3'-bis[(3,5-trifluoromethyl)phenyl]BINOL and (*R*)-VAPOL, respectively, following the same procedure described by us for the corresponding racemates.¹⁹ Similarly to that occurring in C_2 -symmetric (*R*)-**1a** and (*R*)-**1b**, (*R*)-**1c** and (*R*)-**1d** enable huge specific optical rotations ($[\alpha]_{\text{D}}^{20}$) in solution (see Table S1 in ESI†), as well as similar negative vis ECD signals upon vis irradiation under the same experimental conditions (see Fig. 3 and Table S1 in ESI†). However, whereas (*R*)-**1c** exhibits a CPL spectrum with a vis negative band in chloroform solution, (*R*)-**1d** does it with a positive vis band (see Fig. 3 and Table S1 in ESI†). This result shows that it is possible to control the CPL handedness by modulating the ICT emission, which can be done chemically by modifying the electron richness of the bipolyarene moiety.

It should be noted that the selected *O*-BODIPYs dyes have some important characteristics availing their properness for supporting our hypothesis on changing the CPL sign by modulating CPL from ICT: (1) their capability to populate luminescent ICT states; (2) the conformational rigidity of the acting BODIPY chromophore, discarding changes in the CPL sign due to differences in the 3D geometry of the chromophore when comparing related dyes; (3) their peculiar spiranic structure, avoiding aggregation and excimer formation and, therefore, discarding changes in the CPL sign due to differential excimer emission by differential behaviour in related dyes. Besides, it must also be noted that spectral shifting in CPL spectra, when compared to each other and to ECD spectra, is associated to the specific conditions used for recording the CPL spectra (*i.e.*, excitation energy and dye concentration; see in General methods, instrumentation and techniques in ESI†), as well as to differential

†Electronic supplementary information (ESI) available: Experimental details, and supplementary tables and figures, as well as synthetic procedures and characterization data for new compounds. See DOI: [10.1039/c8cc09401b](https://doi.org/10.1039/c8cc09401b)

participation of the ICT state in such spectra. On the other hand, the method used for plotting the CPL spectra of (*R*)-**1a** and (*R*)-**1d** was different from that used for the other dyes (Fig. 3). This is because two different methods were used to record the spectra. Thus, due to the observed high sensitivity of (*R*)-**1a** and (*R*)-**1d** to the excitation source (see in General methods, instrumentation and techniques in ESI[†]), it was not possible to record CPL spectra by using a single sample-solution badge, but a set of solution badges was used instead to record single g_{lum} values for each given wavelength. The said sample sensitivity also explains the significant noise of the CPL spectra of (*R*)-**1a** and (*R*)-**1d** (Fig. 3).

As a proof of concept, we have studied two additional spiranic *O*-BODIPY dyes: the couple formed by (*R*)-**2a** and (*R*)-**2b**, which are based on BINOL and 3,3'-dibromobINOL, respectively (see Fig. 2). Despite (*R*)-**2a** being based on BINOL, this dye is expected to have no capability for ongoing from-BINOL-to-BODIPY ICT, due to the electron-rich character of the involved BODIPY chromophore (note the electron-donating methoxyl groups attached to the π -extended BODIPY chromophore; see Fig. 2).¹⁹ Therefore, this new couple of related dyes should exhibit the same ECD sign and, additionally, the same CPL sign.

(*R*)-**2a** and (*R*)-**2b** were straightforwardly prepared by the same methodology used for obtaining the previous dyes (see Fig. S1 and synthetic details in ESI[†]). As expected, the new C_2 -symmetric *O*-BODIPY dyes enable huge specific optical rotations in solution, as well as notable fluorescence and CPL efficiencies in solution, too (see Table S1 and Fig. S2 in ESI[†]). Noticeably, ICT is not detected in 3,3'-dibromobINOL-based (*R*)-**2b**, nor in BINOL-based (*R*)-**2a**, as shown by the lack of significant dependency of the fluorescence efficiency on the solvent polarity (see Table S2 and Fig. S3 in ESI[†]). To our satisfaction, (*R*)-**2a** and (*R*)-**2b** exhibit not only vis ECD with the same sign (negative), but also vis CPL with the same negative sign (see Fig. 3 and Table S1 in ESI[†]), supporting our hypothesis.

It must be noted here that the CPL spectrum of (*R*)-**2a** could not be recorded in chloroform solution due to rapid and full photodegradation of the dye. This differential behaviour is attributed to the higher instability of the boron chelate involved in **2a**, due to both steric and electronic factors, combined with the significant acidity of chloroform. Thus, acetone was used as an alternative polar enough solvent (see Fig. 3). Nonetheless, to discard differential effects affecting the CPL sign, additional polar solvents were also tested (*e.g.*, dichloromethane) giving place to CPL spectra with negative maxima in all cases.

In summary, we report the first examples of the control of the CPL handedness (sign of observed circularly emission) by chemically modulating ICT emission competing with that from the LE state. Although chiral BODIPYs were selected to exemplify this control, it could be easily applied to other chiral emitters, too. To apply such a control, it is not necessary that the emission from the ICT state surpasses the one from the LE one, since the ICT emission is expected to involve larger circular polarization. However, both circularly polarized emissions do need to show opposite handedness. This is an unprecedented strategy to manipulate the CPL sign in chiral emitters without changing the absolute configurations, being specifically useful for rigid emitters and emitters without the capability to promote excimer emission. This makes the new strategy especially valuable for manipulating CPL sign in simple organic molecules (SOMs), since SOMs fulfilling those characteristics,

conformational rigidity and inability to aggregate, are expected to exhibit high fluorescence in solution, being interesting for the development of specific photonic applications.^{2a} However, general alternative ways to change the CPL sign in SOMs were not available beyond changing the absolute configurations. Moreover, this new strategy paves the way to expand the use of such SOMs to applications based on switching the CPL sign, since the key sign-controlling ICT should be dynamically modulated by external stimuli, such a temperature or solvent polarity. Moreover, since only the CPL sign, but not the ECD one, is changed, the strategy could be also interesting for the development of sophisticated applications based on differential ECD vs. CPL behaviour (*e.g.*, cryptochirality).²⁰ Further studies are in progress to exploit this possibility by developing advanced ICT-switching dyes based on rigid and non-aggregating CPL-enabling SOMs, as well as to predict computationally the reversal of the CPL from ICT when compared to the CPL from LE (necessary condition to apply the reported CPL-sign control).

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

Financial support from Ministerio de Ciencia, Innovación y Universidades de España (MAT2017-83856-C3-2-P and MAT2017-83856-C3-3-P) and Gobierno Vasco (IT912-16) is gratefully acknowledged. G. M. thanks the NIH, Minority Biomedical Research Support (1 SC3 GM089589-08) and the Henry Dreyfus Teacher-Scholar Award for financial support. J. J. thanks Comunidad de Madrid – UCM for a research contract. G. M. also thanks Victoria Y. Chang and Jamie L. Lunkley for their technical help in the CPL measurements.

Notes and references

1. (a)Riehl JP and Richardson FS, *Chem. Rev.* 1986, 86, 1–16;(b)Brittain HG, *Chirality*, 1996, 8, 357–373;(c)Comprehensive Chiroptical Spectroscopy. Instrumentation, Methodologies, and Theoretical Simulations, ed. Berova N, Polavarapu PL, Nakanishi K and Woody RW, John Wiley and Sons, Hoboken, 2012, vol. 1;(d)Luminescence of Lanthanide ions in Coordination Compounds and Nanomaterials, ed. de Bettencourt-Dias A, John Wiley and Sons, Chichester, 2014;(e)Longhi G, Castiglioni E, Koshoubu J, Mazzeo G and Abbate S, *Chirality*, 2016, 28, 696–707. [PubMed: 27670249]
2. (a)Sánchez-Carnerero EM, Agarrabeitia AR, Moreno F, Maroto BL, Muller G, Ortiz MJ and de la Moya S, *Chem. - Eur. J.*, 2015, 21, 13488–13500; [PubMed: 26136234] (b)Tanaka H, Hiroki I, Inoue Y and Mori T, *ChemPhotoChem*, 2018, 2, 386–402;(c)Kumar J, Nakashima T and Kawai T, *J. Phys. Chem. Lett.*, 2015, 6, 3445–3452. [PubMed: 26269090]
3. For example, see:Khorasaninejad M, Ambrosio A, Kanhaiya P and Capasso F, *Sci. Adv.*, 2016, 2, e1501258, DOI: 10.1126/sciadv.1501258. [PubMed: 27386518]
4. (a)Farshchi R, Ramsteiner M, Herfort J, Tahraoui A and Grahn HT, *Appl. Phys. Lett.*, 2011, 98, 162508;(b)Amako T, Nakabayashi K, Suzuki N, Guo S, Abdul Rahim NA, Harada T, Fujiki M and Imai Y, *Chem. Commun.*, 2015, 51, 8237–8240;(c)Choi M and Choi J, *Opt. Express*, 2017, 25, 22253–22267; [PubMed: 29041539] (d)Plechinger G, Korn T and Lupton JM, *J. Phys. Chem. C*, 2017, 121, 6409–6413.
5. (a)Haketa Y, Bando Y, Takaishi K, Uchiyama M, Muranaka A, Naito M, Shibaguchi H, Kawai T and Maeda H, *Angew. Chem., Int. Ed.*, 2012, 51, 7967–7971;(b)Isla H, Srebro-Hooper M, Jean M, Vanthuyne N, Roisnel T, Lunkley JL, Muller G, Williams JAG, Autschbach J and Crassous J, *Chem. Commun.*, 2016, 52, 5932–5935;(c)Shuvaev S, Pal R and Parker D, *Chem. Commun.*, 2017, 53, 6724–6727;(d)Resa S, Miguel D, Guisán-Ceinos S, Mazzeo G, Choquesillo-Lazarte D, Abbate S, Crovetto L, Cárdenas DJ, Carreño MC, Ribagorda M, Longhi G, Mota AJ, de Cienfuegos LA and

- Cuerva JM, Chem. - Eur. J, 2018, 24, 2653–2662; [PubMed: 29240981] (e)Imai Y, Nakano Y, Kawai T and Yuasa J, Angew. Chem., Int. Ed, 2018, 57, 8973–8978.
6. For example, see:(a)Jan CM, Opt. Express, 2011, 19, 5431–5441; [PubMed: 21445182] (b)Kulkarni C, Di Nuzzo D, Meijer EW and Meskers SCJ, J. Phys. Chem. B, 2017, 121, 11520–11527. [PubMed: 29200297]
7. For example, see:(a)Dekkers HPJM, in Circularly Polarized Luminescence: A Probe for Chirality in the Excited State Circular Dichroism: Principles and Applications, ed. Berova N, Nakanishi K and Woody RW, Wiley-VCH, New York, 2nd edn, 2000, pp. 185–215;(b)Okayasu Y and Yuasa J, Mol. Syst. Des. Eng, 2018, 3, 66–72.
8. (a)Munetaka I, Yoshihiro K, Risa M and Koichi N, Inorg. Chem, 2012, 51, 4094–4098; [PubMed: 22414194] (b)Song F, Wei G, Jiang X, Li F, Zhu C and Cheng Y, Chem. Commun, 2013, 49, 5772–5774;(c)Zou W, Yan Y, Fang J, Yang Y, Liang J, Deng K, Yao J and Wei A, J. Am. Chem. Soc, 2014, 136, 578; [PubMed: 24370236] (d)Carmo Dos Santos NA, Badetti E, Licini G, Abbate S, Longhi G and Zonta C, Chirality, 2018, 30, 65–73. [PubMed: 29105860]
9. For example, see:(a)Meinert C, Hoffmann SV, Cassam-Chenai P, Evans AC, Giri C, Nahon L and Meierhenrich UJ, Angew. Chem., Int. Ed, 2014, 53, 210–214;(b)Bisoyi HK and Li Q, Angew. Chem., Int. Ed, 2016, 55, 2994–3010.
10. For example, see:(a)Saito K and Tatsuma T, Nano Lett, 2018, 18, 3209–3212; [PubMed: 29664299] (b)Yeom J, Yeom B, Chan H, Smith KW, Dominguez-Medina S, Bahng JH, Zhao G, Chang W-S, Chang S-J, Chuvilin A, Melnikau D, Rogach AL, Zhang P, Link S, Král P and Kotov NA, Nat. Mater, 2015, 14, 66–72. [PubMed: 25401922]
11. The degree of CPL is given by the luminescence dissymmetry ratio, $glum(\lambda) = 2 \frac{I_L - I_R}{I_L + I_R}$, where I_L and I_R refer, respectively, to the intensity of left and right circularly polarized emissions.
12. For example, see:(a)Gopal A, Hifsudheen M, Furumi S, Takeuchi M and Ajayaghosh A, Angew. Chem., Int. Ed, 2012, 51, 10505–10509;(b)Ito S, Ikeda K, Nakanishi S, Imai Y and Asami M, Chem. Commun, 2017, 53, 6323–6326;(c)Han J, Guo S, Lu H, Liu S, Zhao Q and Huang W, Adv. Opt. Mater, 2018, 1800538.
13. (a)Yan F, Copeland RA and Brittain HG, Inorg. Chem, 1982, 21, 1180–1185;(b)Satrijo A, Meskers SCJ and Swager TM, J. Am. Chem. Soc, 2006, 128, 9030–9031; [PubMed: 16834365] (c)Maeda H, Bando Y, Shimomura K, Yamada I, Naito M, Nobusawa K, Tsumatori H and Kawai T, J. Am. Chem. Soc, 2011, 133, 9266–9269; [PubMed: 21599014] (d)Yuasa J, Ohno T, Miyata K, Tsumatori H, Hasegawa Y and Kawai T, J. Am. Chem. Soc, 2011, 133, 9892–9902; [PubMed: 21598978] (e)Harada T, Tsumatori H, Nishiyama K, Yuasa J, Hasegawa Y and Kawai T, Inorg. Chem, 2012, 51, 6476–6485; [PubMed: 22667353] (f)Yuasa J, Ueno H and Kawai T, Chem. - Eur. J, 2014, 20, 8621–8627; [PubMed: 24958164] (g)Nagata Y, Nishikawa T and Sugimoto M, Chem. Commun, 2014, 50, 9951–9953;(h)Okazaki M, Mizusawa T, Nakabayashi K, Yamashita M, Tajima N, Harada T, Fujiki M and Imai Y, J. Photochem. Photobiol., A, 2016, 331, 115–119.
14. (a)Haketa Y, Bando Y, Takaishi K, Uchiyama M, Muranaka A, Naito M, Shibaguchi H, Kawai T and Maeda H, Angew. Chem., Int. Ed, 2012, 51, 7967–7971;(b)Sheng Y, Ma J, Liu S, Wang Y, Zhu C and Cheng Y, Chem. - Eur. J, 2016, 22, 9519–9522; [PubMed: 27140195] (c)Mimura Y, Kitamura S, Shizuma M, Kitamatsu M, Fujiki M and Imai Y, ChemistrySelect, 2017, 2, 7759–7764.
15. (a)Clarke R, Ho KL, Alsimaree AA, Woodford OJ, Waddell P-G, Bogaerts J, Herrebout W, Knight JG, Pal R, Penfold TJ and Hall MJ, ChemPhotoChem, 2017, 1, 513–517;(b)Toyoda M, Imai Y and Mori T, J. Phys. Chem. Lett, 2017, 8, 42–48; [PubMed: 27936744] (c)Zinna F, Bruhn T, Guido CA, Ahrens J, Bröring M, Di Bari L and Pescitelli G, Chem. - Eur. J, 2016, 22, 16089–16098; [PubMed: 27658919] (d)Wang Y, Li Y, Liu S, Li F, Zhu C, Li S and Cheng Y, Macromolecules, 2016, 49, 5444–5451;(e)Saikawa M, Nakamura T, Uchida J, Yamamura M and Nabeshima T, Chem. Commun, 2016, 52, 10727–10730;(f)Gobo Y, Yamamura M, Nakamura T and Nabeshima T, Org. Lett, 2016, 18, 2719–2721; [PubMed: 27214262] (g)Alnoman RB, Rihn S, O'Connor DC, Black FA, Costello B, Waddell PG, Clegg W, Peacock RD, Herrebout W, Knight JG and Hall MJ, Chem. - Eur. J, 2016, 22, 93–96. [PubMed: 26555772]
16. (a)Sanchez-Carnerero EM, Moreno F, Maroto BL, Agarrabeitia AR, Ortiz MJ, Vo BG, Muller G and de la Moya S, J. Am. Chem. Soc, 2014, 136, 3346–3349; [PubMed: 24524257] (b)Ray C,

- Sanchez-Carnerero EM, Moreno F, Maroto BL, Agarrabeitia AR, Ortiz MJ, Lopez-Arbeloa I, Bañuelos J, Cohovi KD, Lunkley JL, Muller G and de la Moya S, *Chem. -Eur.J.*, 2016,22, 8805–8808; [PubMed: 27123965] (c)Jiménez J, Cerdán L, Moreno F, Maroto BL, García-Moreno I, Lunkey JL, Muller G and de la Moya S, *J. Phys. Chem. C*, 2017, 121, 5287–5292.
17. For example, see:(a)Bañuelos J, *Chem. Rec*, 2016, 16, 335–348; [PubMed: 26751982] (b)Lakshmi V, Sharma R and Ravikanth M, *Curr. Org. Chem*, 2016, 6, 1–24;(c)Boens N, Verbelen B and Dehaen W, *Eur.J. Org. Chem*, 2015, 6577–6595;(d)Lakshmi V, Rao MR and Ravikanth M, *Org. Biomol. Chem*, 2015, 13, 2501–2517; [PubMed: 25594728] (e)Lu H, Mack J, Yang Y and Shen Z, *Chem. Soc. Rev*, 2014, 43, 4778–4823. [PubMed: 24733589]
18. Similar to the luminescence dissymmetry ratio (see ref. 11), the degree of circular dichroism is given by the absorbance dissymmetry ratio (Kuhn's dissymmetry ratio), $g_{abs}(\lambda) = 2(\epsilon_L - \epsilon_R) / (\epsilon_L + \epsilon_R)$, where ϵ_L and ϵ_R refer, respectively, to the molar absorptivity of left and right circularly polarized absorptions.
19. Gartzia-Rivero L, Sánchez-Carnerero EM, Jiménez J, Bañuelos J, Moreno F, Maroto BL, López-Arbeloa I and de la Moya S, *Dalton Trans*, 2017, 46, 11830–11839. [PubMed: 28848944]
20. (a)Amako T, Nakabayashi K, Suzuki N, Guo S, Abdul Rahim NA, Harada T, Fujiki M and Imai Y, *Chem. Commun*, 2015, 51, 8237–8240;(b)Bruhn T, Pescitelli G, Witterauf F, Ahrens J, Funk M, Wolfram B, Schneider H, Radius U and Broering M, *J. Org. Chem*, 2016, 24, 4236–4243; (c)Nakanishi S, Nakabayashi K, Mizusawa T, Suzuki N, Guo S, Fujiki M and Imai Y, *RSC Adv.*, 2016, 6, 99172–99176.

Fig. 1. Jablonsky diagram explaining the change of the CPL handedness by promoting the population of an ICT state enabling CPL with the opposite sign to that from the LE state.

Fig. 2. Studied CPL-enabling dyes and strategy to manipulate chemically the CPL sign. The acting BODIPY chromophore is highlighted in red, whereas the ICT-modulating bipolyarene moiety (based on BINOL for **1a** and **2a**, 3,3'-dibromoBINOL for **1b** and **2b**, 3,3'-(BTFMP)BINOL for **1c**, and VAPOL for **1d**) is highlighted in blue. BTFMP: bis(3,5-trifluoromethyl)phenyl.

Fig. 3. ECD (top, left) and UV-vis absorption (bottom, left), CPL (top, right) and total luminescence (bottom, right) spectra for (*R*)-**1a–d** and (*R*)-**2a–b** in solution (concentration ca. 3.5×10^{-6} M for UV-vis absorption and ECD and ca. 2.0×10^{-3} M for CPL and total luminescence). The chloroform solution was used in all cases, with the exception of the CPL and total luminescence spectra of (*R*)-**2a** (recorded in acetone; see text). Regarding the spectral-shifting, plotting and noise issues, see text. For additional details, see ESI.†