Published in final edited form as:

Osteoarthritis Cartilage. 2021 September ; 29(9): 1351–1361. doi:10.1016/j.joca.2021.05.059.

Spatially-resolved Nanometer-scale Measurement of Cartilage Matrix Extracellular Matrix Mobility

Brittany D. Partain¹, Qingteng Zhang², Mythreyi Unni³, Jessica Aldrich¹, Carlos Rinaldi^{1,3}, Suresh Narayanan², Kyle D. Allen^{1,4}

¹J. Crayton Pruitt Family Department of Biomedical Engineering, University of Florida, Gainesville, FL, USA

²X-ray Science Division, Argonne National Laboratory, Lemont, IL, USA

³Department of Chemical Engineering, University of Florida, Gainesville, FL, USA

⁴Department of Orthopaedics and Rehabilitation, University of Florida, Gainesville, FL, USA

Abstract

Objective: Tissues have complex structures, comprised of solid and fluid phases. Improved understanding of interactions between joint fluid and extracellular matrix (ECM) is required in models of cartilage mechanics. X-ray photon correlation spectroscopy (XPCS) directly measures nanometer-scale dynamics, and thus can provide insight into biofluid-biosolid interactions in cartilage. This study applies XPCS to evaluate dynamic interactions between intact cartilage and biofluids.

Design: Cartilage biopsies were collected from bovine femoral condyles. During XPCS measurements, cartilage samples were exposed to different fluids: deionized water, PBS, synovial fluid, or sonicated synovial fluid. ECM-biofluid interactions were also assessed at different length scales and different depths from the cartilage surface.

Results: Using SA-XPCS, cartilage ECM mobility was detected at length scales from 50 to 207 nm. As length scale decreased, time scale for autocorrelation decay decreased, suggesting smaller ECM components are more mobile. ECM dynamics were slowed by dehydrating the sample, demonstrating XPCS assesses matrix mobility in hydrated environments. At all length scales, the matrix was more mobile in deionized water and slowest in synovial fluid. Using the 207 nm length scale assessment, ECM dynamics in synovial fluid were fastest at the cartilage surface and progressively slowed as depth into the sample increased, demonstrating XPCS can assess spatial distribution of ECM dynamics. Finally, ECM mobility increased for sonicated synovial fluid.

Corresponding Author: Kyle D. Allen, Ph.D., Associate Professor, J. Crayton Pruitt Family Department of Biomedical Engineering, University of Florida, 1275 Center Drive, Biomedical Sciences Building, Gainesville, Florida 32611, (352) 273-9337, kyle.allen@bme.ufl.edu.

Author Contributions

Brittany Partain (BDP), Mythreyi Unni (MU), Carlos Rinaldi (CR), and Kyle Allen (KDA) contributed to study design. BDP isolated and prepared cartilage and fluid samples. BDP and Jessica Aldrich (JA) performed XPCS measurements. BDP analyzed data with assistance from Suresh Narayanan (SN) and Qingteng Zhang (QZ). BDP, KDA, SN, and QZ interpreted data. The manuscript was prepared by BDP, with critical feedback from KDA, CR, MU, QZ and xxxx.

Competing Interests

There are no competing interests

Conclusions: This study demonstrates the potential of XPCS to provide unique insights into nanometer-scale cartilage ECM mobility in a spatially resolved manner and illustrates the importance of biosolid-biofluid interactions in dictating dynamics of ECM components.

Keywords

Extracellular Matrix Mobility; X-ray Photon Correlation Spectroscopy (XPCS); Synovial Fluid; Extracellular Matrix Dynamics; Cartilage

Introduction

Biological tissues have complex structures with spatially differing material properties. For example, most tissues contain solid and fluid phases with the solid extracellular matrix (ECM) having intricate hierarchical structures that vary across length scales [1]. Due to these hierarchical structures, the interaction of ECM with the fluid phase of a tissue is also likely to have spatial variation. Moreover, tissue microarchitecture dynamically changes in response to loading. Here, weak bonds within the ECM and between the ECM and fluid can break and dissipate energy. These microstructures can also remodel in response to loading, dynamically changing interactions between the ECM and the biofluids that surround them [2].

Measuring the dynamics of biosolid-biofluid interactions at length scales associated with the tissue microstructure is challenging. Spatial variation in microscopic level mechanics of the ECM and cells within the ECM have been evaluated using atomic force microscopy, traction force microscopy, multiphoton fluorescence microscopy, and second harmonic generation imaging [3–5]. However, making direct measurements of biosolid-biofluid interactions remain a challenge for these techniques. Mechanical models assume certain biosolid-biofluid interactions, aiming to predict mechanical responses of a hydrated tissue to mechanical loading [1]. For example, biphasic theory predicts the behavior of a soft, porous and permeable, elastic solid filled with a fluid [6], and poroviscoelastic theory evaluates biological tissues as an elastic biosolid phase with biofluid filling the tissue's pores [1,7]. While these models are useful, much of the mechanical behaviors of biological tissues revolve around assumptions of how the viscous fluid phase within a tissue interacts with the solid phase of ECM. Thus, understanding dynamics of biosolid-biofluid interactions is pivotal to filling gaps in our mechanical understanding of biological tissue function.

Small-angle X-ray photon correlation spectroscopy (SA-XPCS) allows for direct measurement of nanometer-scale dynamics [8], but to date, biological applications of XPCS have only been in complex fluids and protein solutions [9–11]. Briefly, in XPCS, a coherent X-ray synchrotron beam is passed through a sample. The sample's microstructure scatters the beam, generating a speckle pattern on the X-ray detector. Microstructural motion within the sample creates corresponding time-dependent changes in the speckle pattern. Thus, intensity fluctuations of speckles can provide information on the sample's nanometer-scale dynamics [12]. This has been demonstrated in complex fluids to measure dynamics of colloidal particles in a shear flow, phase separation dynamics of colloid-polymer mixtures, dynamics of metallic glasses, and recently, dynamics of concentrated lysozyme solutions

[9,13,14]. However, in principle XPCS can be expanded to measure motion of the ECM in complex hydrated tissues, as well as biosolid-biofluid interactions with spatial dependence. Using cartilage and synovial fluid as a model system, this paper describes the first application of XPCS to directly evaluate interactions between functionally intact complex ECM and complex a biofluid.

Methods

Cylindrical cartilage biopsies (4 mm) were collected from femoral condyles of three juvenile bovines (Research 87 Inc., Boylston, MA, USA); specimen collections occurred at the University of Florida, Gainesville, FL. For storage, samples were wrapped in 1x protease inhibitor-soaked gauze (ThermoFisher Scientific Inc., Waltham, MA, USA) and placed in conical tubes. Samples were frozen, shipped to Argonne National Laboratory (Lemont, IL, USA) on dry ice, and stored at -20°C until sample preparation. Prior to XPCS measurements at Argonne National Laboratory, wrapped biopsies were thawed in phosphate buffered saline (PBS) at 4°C for 1 hr. Then, 4 mm biopsies were cut orthogonally with a 3 mm biopsy punch, creating a half-moon-shaped sample. These samples were inserted into a 3 mm sample holder with the articular surface on top (Supplemental Fig. 1); while in the sample holder, samples were exposed to different conditions for the specific experiments discussed below.

Mobility of the cartilage ECM was assessed in multiple experiments. However, a proof-of-concept experiment is presented first, where we evaluate whether hydration is required for XPCS measurements of ECM mobility in cartilage. Here, cartilage was dried in an oven at 37°C for 2 hrs. Dried cartilage was placed on the beamline without any fluid. XPCS measurements were collected at 10 equally spaced vertical increments throughout the cartilage.

In the second experiment, ECM mobility was assessed as a function of depth from the cartilage surface. Here, all cartilage samples were exposed to $20\text{ }\mu\text{L}$ of non-degraded bovine synovial fluid (Animal Technologies, Tyler, TX, USA), with XPCS measurements collected vertically at equally spaced increments throughout the cartilage. Note, synovial fluid was first centrifuged at 3000 rpm to remove cellular debris, tissues, and fats.

In the third experiment, the effects of collagen crosslinking on XPCS measurements were evaluated. Here, samples were first soaked in 2 mM, 5 mM, or 10 mM genipin for 30 min (collagen crosslinker) and then stored in PBS at 4°C for 22–24 hrs. XPCS measurements were then collected near the cartilage surface in $20\text{ }\mu\text{L}$ of PBS.

In the fourth experiment, the effects of different fluids on ECM mobility were explored. Here, cartilage was exposed to $20\text{ }\mu\text{L}$ of deionized water, PBS, or non-degraded bovine synovial fluid. In these samples, XPCS measurements were collected near the cartilage surface.

In the final experiment presented, the effects of synovial fluid degradation on ECM mobility were evaluated. Here, bovine synovial fluid (13 mL) was centrifuged at 3000 rpm to remove cellular debris, tissues, and fats. A 3 mL synovial fluid aliquot was removed (non-degraded

synovial fluid); then, the remaining 10 mL of synovial fluid were mechanically degraded via ultrasonication (Qsonica Q500, 38% amplitude) in 10 sec increments. At 40 sec and 120 sec, additional 3 mL aliquots were removed. Synovial fluid aliquots were stored at -20°C until thawed for XPCS measurements, which were collected near the cartilage surface.

All XPCS data were collected at the 8-ID-I beamline of the Advanced Photon Source. Details of XPCS measurements are provided in the next section. Immediately following XPCS measurements, cartilage samples were removed from sample holders and placed in 10% neutral buffered formalin (Fisher Scientific, Pittsburgh, PA, USA) for one week at room temperature. Then, cartilage samples were dehydrated through an ethanol ladder, infiltrated, and embedded in paraffin wax. Sections (10 μm) were acquired, with at least one section taken at every 100 μm . Three to four sections per sample were stained with Safranin O Fast Green.

SA-XPCS Measurements

A single SA-XPCS measurement is a temporal sequence of coherent X-ray scattering intensities ('speckles'), collected at transmission scattering geometry and fixed sample location. The use of a coherent beam enables the dynamics of heterogeneous spatial structures to be reflected in temporal decorrelation of scattering intensities, which can be evaluated by calculating the intensity autocorrelation function g_2 [15]. The time-average of all SA-XPCS detector frames provides the equivalent of a small-angle X-ray scattering (SAXS) measurement with the same total exposure time.

The coherent X-ray beam was produced by a set of two 33 mm-period, 2.4 m long undulators (68 m upstream from sample). The X-ray beam was first deflected by a plane silicon mirror (43 m upstream from sample) at an angle of 5 mrad to filter out higher order harmonics, and passed through a Germanium (111) monochromator (4 m upstream from sample) to select a 10.91 keV X-ray beam with an energy bandpass of 0.03%. The monochromatic X-ray beam was then cropped to 15 μm in the horizontal direction using highly polished tungsten carbide slit blades (2 m upstream from sample) to select a partially coherent beam. In the vertical direction, a 150 μm beam was selected and focused to a 10 μm spot size on the sample by 15 beryllium compound refractive lenses (2.4 m upstream from sample). The final partially coherent X-ray beam had a beam size of 15 μm (horizontal) $\times$ 10 μm (vertical) on the sample and a total flux of 1.9×10^{10} photons per sec.

Before collecting real measurements, a set of controlled structure and dynamics measurements were carried out to determine the optimal radiation dose the sample could withstand without producing radiation-induced artifacts. Based on these measurements, photon flux was reduced to 1×10^9 photons per second. Additionally, total radiation dose on the sample was kept below the determined radiation damage threshold, by performing XPCS measurements in a mode where time series of frames were collected with a duty cycle of 20%. Duty cycle was controlled by using a fast X-ray shutter with an opening and closing time of 0.002 sec.

Structure and organization of components in biosolids have been assessed using SAXS [16]. Fig. 1A illustrates the SAXS pattern collected using a Lambda-750k detector [17]. The x

and y coordinates of the detector pixels are converted to the wavelength transfer, Q , in reciprocal space using the equation $Q = 2k \sin(2\theta/2)$, where $k = 2\pi/\lambda$ is the wavevector, λ is the X-ray wavelength (1.12 Å for a photon energy of 11 keV), and $2\theta = D/L$ is the scattering angle of the pixel location calculated by dividing the distance from the pixel to the direct transmitted beam (D) over the distance from the sample to the detector ($L = 4$ m).

To simplify analysis, the heterogeneous 2D SAXS pattern was corrected by creating a horizontal mask (white dashed lines in Fig. 1A). Only data between the two white dashed lines were analyzed for all experiments (Fig. 1B). Data shown in the results are indicative of normalized g_2 from horizontally masked 2D SAXS patterns, which is calculated by subtracting the baseline from g_2 and then normalizing by the highest value of g_2 at the lowest decay time [18].

Statistics

Data were evaluated using a linear mixed effects regression model that treated fluid type or degradation time (for synovial fluid) as a factor and treated the animal as a random factor. If significant, a comparison of least squared means was conducted using a Tukey's HSD correction for multiple comparisons.

Results

The Cartilage ECM is Heterogeneous and Does Not Change During XPCS Measurements

In this study, the 2D SAXS pattern illustrated in Fig. 1A is elliptical rather than circular, indicating the cartilage structure is heterogeneous, which aligns with previous literature [19]. While the cartilage structure is heterogeneous, dynamic trends in both the horizontal and vertical masked data were the same; therefore, horizontally masked data were analyzed in data below (Fig 1B).

After creating a mask, several parameters (described above) were adjusted to reduce radiation damage to the sample, while still providing enough scatter to collect reliable data. Radiation damage was determined by overlaying the static structure generated from the 1D SAXS pattern (Fig. 1C). In Fig. 1C, the 1D SAXS pattern was generated from taking the azimuthal intensity average from the 2D SAXS pattern and plotting it as a function of Q . Then, the 1D SAXS pattern was averaged in 100 frame increments and overlaid. The overlaid static structures remained the same, demonstrating that the structural integrity of cartilage ECM did not change during XPCS measurements.

Cartilage ECM Mobility Can Be Detected at Different Length Scales

The dynamics at multiple length scales, Q s, and how the dynamic behavior of cartilage changed across length scale were assessed. To improve statistics, g_2 from regions of pixels with approximately the same Q s were averaged using the method described in Khan et al. [20]. The length scales assessed here ranged from 50 – 207 nm as calculated by $2\pi/Q$ (Fig. 2). For reference, aggrecan is roughly 257 ± 87 nm in end to end length; glycosaminoglycan side chains on aggrecan are roughly $32 \text{ nm} \pm 8$ in end to end length [21]. Thus, the dynamics of aggrecan glycosaminoglycans are likely being measured by XPCS (Fig. 2). As length

scale decreased, time scale for the autocorrelation function to decay decreased, suggesting smaller components are more mobile. In addition, at all length scales, the matrix was more mobile in deionized water and was slowest in non-degraded synovial fluid.

While the XPCS signal can be discerned at length scales associated with glycosaminoglycan side chains, data became noisier at smaller length scales. Therefore, we chose to assess data shown hereafter at the largest length scale (207 nm, size range for aggrecan molecules).

Cartilage ECM Mobility Changes as a Function of Depth

Cartilage behaves as a biphasic material, where the material mechanics derive from a fluid phase, solid phase, and interaction between the two [22,23]. Collectively, these solid and fluid phases affect cartilage mobility. If dehydrated, the cartilage ECM was immobile throughout at all depths (Fig. 3A), where a dehydrated cartilage sample shows no mobility in the timescale of 1000 seconds for XPCS measurement.

When hydrated, cartilage matrix dynamics change as a function of depth into the sample. Cartilage matrix dynamics were fastest at the cartilage surface and progressively slowed down as the depth into the sample increased (Fig. 3B). Importantly, this trend was consistent in cartilage samples from three different animals. Furthermore, as visualized in the normalized autocorrelation decay, the time for normalized autocorrelations to decay increased as a function of depth in the sample (Fig. 3C). Specifically, the time for normalized autocorrelations to decay 25% increased by 0.2 s per μm of depth ($p < 0.0001$) and to decay 50% increased by 0.24 s per μm of depth ($p < 0.0001$) in hydrated samples. Furthermore, the cartilage matrix remained intact after XPCS measurements, and histological cross-sections of cartilage are shown in Fig. 3D.

Cartilage ECM Mobility Decreases as ECM Crosslinking Increases

Next, the biosolid was modified and the effects on mobility were assessed. Healthy cartilage has a hierarchical structure that is often described as three different zones: surface zone, middle zone, and deep zone. Each zone has a different structural composition that affects the matrix mobility. As shown in Fig. 3, cartilage ECM was most mobile at the surface. Different concentrations of genipin (a collagen crosslinker) were used to evaluate how matrix crosslinking affected ECM mobility. Here, ECM mobility decreased as genipin concentrations increased for all three cartilage samples (Fig. 4A–4C). At high genipin concentrations, autocorrelations functions did not decay by 25% or 50% (Fig. 4D). However, the matrix never became completely immobile, suggesting smaller matrix components located in the surface zone contribute to matrix dynamics in this biosolid-biofluid system.

Cartilage ECM Mobility is Slowest in Synovial Fluid and Fastest in Deionized Water

Next, the biofluid was modified and the effects on ECM mobility were assessed. Again, cartilage is hydrated, and the surface is in constant contact with synovial fluid. However, many studies that model cartilage behavior and transport within cartilage use Newtonian fluids like deionized water and PBS [24]. Thus, in this study, biosolid-biofluid interactions at the surface were evaluated by hydrating cartilage in deionized water, PBS, or non-degraded synovial fluid. As shown in Fig. 5, the cartilage matrix was most mobile in deionized water,

then PBS, and least mobile in non-degraded synovial fluid for all three cartilage samples (Fig 5A–5C). The 50% decay time was different for the cartilage ECM in deionized water, PBS, and synovial fluid (Fig. 5D, $p = 0.008$). Specifically, the cartilage ECM autocorrelation function decayed slower and thus was less mobile in synovial fluid compared to deionized water ($p = 0.004$) and PBS ($p = 0.02$) and less mobile in PBS compared to deionized water ($p = 0.04$).

Cartilage ECM Mobility Increases as Synovial Fluid Degeneration Increases

In this specific biosolid-biofluid system, the most biologically relevant fluid is synovial fluid. In joint diseases including osteoarthritis (OA), the length of hyaluronic acid chains decreases in synovial fluid, resulting in reduced synovial fluid viscosity [25]. Here, synovial fluid was degraded to decrease viscosity and ultimately mimic disease conditions. Cartilage matrix mobility increased as synovial fluid degradation time increased for all bovine cartilage samples (Fig. 6A–6C). For degraded synovial fluid, 25% and 50% decay times were decreased as degree of degradation increased (Fig. 6D, $p = 0.02$, $p = 0.01$, respectively). Specifically, compared to non-degraded synovial fluid, the 25% decay time was faster for 40 sec and 120 sec of sonication ($p = 0.04$, $p = 0.005$, respectively). Moreover, compared to non-degraded synovial fluid, the 50% decay time was faster for 40 sec and 120 sec of sonication ($p = 0.04$, $p = 0.004$), and compared to 40 sec of sonication, the 50% decay time was fast for 120 sec of sonication ($p = 0.041$). The autocorrelations decay times and location in the sample of XPCS measurement for all experiments can be found in Supplemental Tables 1 and 2.

Discussion

Biological tissues have complex structures that provide complex physical functions. These functions derive from interactions occurring across length scales. However, many questions remain in how tissue interactions serve to provide mechanical function. Models have been generated to predict mechanics and interactions between the biosolid and biofluid components of tissues based on assumptions. Making direct measurements of these interactions could further validate these models. Biological tissues are dynamic, and small shifts in the nanoscale structure can change the measured macroscale mechanics. Here, X-ray photon correlation spectroscopy (XPCS) was used to determine nanometer-scale structural dynamic trends in a complex biological tissue in different hydrated environments. Although this discussion primarily revolves around our results with cartilage, XPCS is a powerful tool that can be applied to many biological tissues.

The first goal of this study was to determine the length scale of tissue components contributing to matrix dynamics at specific locations. The use of a large area detector and an angstrom-wavelength X-ray beam covers a large range of Q s, allowing XPCS to simultaneously assess the mobility of ECM components of various sizes, with minimal disruption of the native ECM structure. As in other biological matrices, cartilage is composed of multiple ECM components that vary in size. First, much of cartilage ECM is formed from large collagen type II fibrils. Attached to these fibrils are long hyaluronic acid chains, and attached to these hyaluronic acid chains is aggrecan, an aggregating

proteoglycan with multiple glycosaminoglycan side chains. XPCS has the capability of measuring the mobility of ECM components at length scales associated with each cartilage ECM component - collagen fibril, hyaluronic acid chain, large aggregating proteoglycan, and glycosaminoglycan side chains.

Additionally, individual components in biological tissues have varying lengths, making their behavior dependent on location within the tissue. XPCS allows the ability to collect measurements at specific anatomical locations within the sample and can selectively probe spatial fluctuations from the submicron level to a few nanometers. Thus, XPCS can directly measure dynamics of components at different length scales at specific locations, with minimal disruption of the native ECM structure. Data collected in this study ranged from length scales of 207 nm to 10.5 nm (not shown). The scattering intensity decreases at smaller length scales; therefore, data shown here are representative of the largest length scale due to the reliability of the measurement from higher scatter intensities. However, other biological tissues have different structures, composed of different sized constituents. Thus, directly measuring dynamics of a wide size range of structural constituents is possible in other biosolid systems.

Several studies have directly measured dynamics of different cartilage constituents (collagen, chondroitin sulfate, and aggrecan) in solution [26,27]. While determining the mobility of each cartilage constituent in solution is important, it is not biologically translatable to the dense cartilage ECM. Another group characterized mobility of collagen in bulk cartilage samples using HR NMR and solid-state ^{13}C NMR spectroscopy [27,28]. However, the study was performed after air-drying cartilage to remove excess water. Our results demonstrate the ability to analyze the dynamics of cartilage in its native ECM structure and within a hydrated environment.

Assessing dynamic interactions between the biosolid-biofluid at different sample depths was also a goal of this work. While depth related changes in cartilage permeability and molecular transport are known, this study is the first to show biosolid-biofluid dynamic changes as a function of depth. Previous literature has shown the effective diffusivity of low molecular weight solutes was fivefold less in the deep zone compared to other zones [29], and that decreased permeability in the deep zone is attributed to a slight increase in the fixed charge density of the matrix in this direction [30]. Our results align with these findings, demonstrating that depth also has important effects on cartilage matrix dynamics.

The final goal of this study was to alter the biosolid and biofluid separately and observe changes in biosolid-biofluid dynamics. Collagen is the biggest cartilage ECM component and is aligned parallel to the cartilage surface in the surface zone [31,32]. Although collagen was too large to independently measure its dynamics, crosslinking collagen with genipin did reduce the dynamics of other ECM components. From a mechanical perspective, increases in genipin concentration result in increases in cartilage stiffness [33]. Upon increasing genipin concentration in this work, matrix mobility decreased but did not become completely immobile. These data further verify that smaller matrix components, including the proteoglycan aggrecan and glycosaminoglycans are contributing to the measured dynamics. Although collagen was specifically targeted here, other constituents of the

biosolid could have been crosslinked or degraded. Thus, teasing out dynamic contributions from other structure components could be refined in future investigations.

The biofluid comprising the fluid phase of a biological tissue is an important consideration for modeling tissue behaviors and molecular transport within the tissues. For cartilage, Newtonian fluids, including water and PBS, are commonly used in these models [24]. Although these fluids simplify models, using Newtonian fluids creates assumptions regarding biosolid-biofluid interactions, resulting in model limitations for predicting tissue behaviors. In this study, cartilage matrix dynamics were measured in deionized water, PBS, and non-degraded synovial fluid to compare how fluid properties affect dynamics. The cartilage matrix dynamics were fastest in deionized water followed by PBS. Proteoglycans within cartilage have a large number of negative charges, which contribute to cartilage's hydrophilic nature and osmotic swelling pressure [34]. Therefore, cartilage ECM may have faster dynamics in deionized water due to osmotic swelling, causing matrix components to be farther apart and allowing faster dynamics. Furthermore, matrix dynamics were slowest in non-degraded synovial fluid. Synovial fluid is known to form a lubricating layer [35], stabilizing collagen fibrils near the articular surface, and therefore could account for the decrease in cartilage matrix mobility. Importantly, these results demonstrate consistent differences in dynamics between fluids typically used in models and fluids most relevant to the biological system. Similarly, XPCS can be used in other systems with a non-Newtonian fluid phase, including blood vessels and blood, to directly measure biosolid-biofluid interactions.

One limitation of this study is the non-homogenous nature of articular cartilage. Due to the complex, hierarchal structure of cartilage ECM, the speckle pattern must be masked, reducing the scatter intensity, thus not providing enough scatter to analyze dynamics at lengths below 50 nm. Additionally, the cartilage matrix is a network with an intricate composition; therefore, a deeper look at the temporal and spatial heterogeneity measured by XPCS could shine light on biophysical properties of cartilage ECM. Cartilage is also a load bearing tissue; however, this study did not explore biosolid-biofluid interactions during load or after load. Future studies could examine matrix dynamics in loaded and unloaded samples. Lastly, cartilage samples were taken from three different juvenile bovine knees. Exact sizes and ages of the animals were not reported and could have accounted for the variability between animals. While this sample size may appear small, XPCS measurements require upwards of an hour per scan and can only be performed at select beamlines at large governmental labs. Hence, the reproducibility of the findings across samples is encouraging but variabilities in these measures across animals, between species, and across biological factors (age, sex) remain to be investigated in a larger scale study. Nonetheless, this study produced consistent trends across animals and demonstrated the applicability of XPCS in probing dynamics in biofluid/biosolid systems.

Conclusions

This study demonstrates the potential of XPCS to provide unique insights into nanometer-scale cartilage ECM mobility in a spatially resolved manner and illustrates the importance of biosolid-biofluid interactions in dictating dynamics of ECM components. These findings

demonstrate the ability of XPCS to measure matrix dynamics in native ECM within a hydrated environment, specifically within their relevant biological fluid. Furthermore, we directly measure depth dependent changes in cartilage matrix dynamics at the 200 nm length scale. These results could ultimately provide fundamental knowledge for understanding biosolid-biofluid interactions and cartilage tissue mechanics.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

The authors would like to thank Dr. Eric Dufresne, Dr. Alec Sandy, and Dr. Raymond Ziegler at Advanced Photon Source for their assistance during XPCS measurements.

Role of the Funding Source

This work was supported by the National Institutes of Health/National Institute of Arthritis and Musculoskeletal and Skin Diseases [R01AR068424]. Funding sources had no role in study design, data collection and analysis, manuscript preparation, or decision to publish. This work also used resources from the Advanced Photon Source, a U.S. Department of Energy (DOE) Office of Science User Facility operated for the DOE Office of Science by Argonne National Laboratory under Contract No. DE-AC02-06CH11357.

References

- [1]. Stokes IA, Chegini S, Ferguson SJ, Gardner-Morse MG, Iatridis JC, Laible JP, Limitation of finite element analysis of poroelastic behavior of biological tissues undergoing rapid loading, *Ann. Biomed. Eng* 38 (2010) 1780–1788. doi:10.1007/s10439-010-9938-0. [PubMed: 20306136]
- [2]. Dumont S, Prakash M, Emergent mechanics of biological structures, *Mol. Biol. Cell* 25 (2014) 3461–3465. doi:10.1091/mbc.E14-03-0784. [PubMed: 25368421]
- [3]. Mitsui K, Nakajima K, Arakawa H, Hara M, Ikai A, Dynamic measurement of single protein's mechanical properties, *Biochem. Biophys. Res. Commun* 272 (2000) 55–63. doi:10.1006/bbrc.2000.2742. [PubMed: 10872803]
- [4]. Polacheck WJ, Chen CS, Measuring cell-generated forces: A guide to the available tools, *Nat. Methods* 13 (2016) 415–423. doi:10.1038/nmeth.3834. [PubMed: 27123817]
- [5]. Miron-Mendoza M, Koppaka V, Zhou C, Petroll WM, Techniques for assessing 3-D cell-matrix mechanical interactions in vitro and in vivo, *Exp. Cell Res* 319 (2013) 2470–2480. doi:10.1016/j.yexcr.2013.06.018. [PubMed: 23819988]
- [6]. Mow VC, Holmes MH, Michael Lai W, Fluid transport and mechanical properties of articular cartilage: A review, *J. Biomech* 17 (1984) 377–394. doi:10.1016/0021-9290(84)90031-9. [PubMed: 6376512]
- [7]. Huang CY, Soltz MA, Kopacz M, Mow VC, Ateshian GA, Experimental verification of the roles of intrinsic matrix viscoelasticity and tension-compression nonlinearity in the biphasic response of cartilage, *J. Biomech. Eng* 125 (2003) 84–93. doi:10.1115/1.1531656. [PubMed: 12661200]
- [8]. Leheny RL, XPCS: Nanoscale motion and rheology, *Curr. Opin. Colloid Interface Sci* 17 (2012) 3–12. doi:10.1016/j.cocis.2011.11.002.
- [9]. Möller J, Sprung M, Madsen A, Gutt C, X-ray photon correlation spectroscopy of protein dynamics at nearly diffraction-limited storage rings, *IUCrJ*. 6 (2019) 794–803. doi:10.1107/S2052252519008273.
- [10]. Vodnala P, Karunaratne N, Lurio L, Thurston GM, Vega M, Gaillard E, Narayanan S, Sandy A, Zhang Q, Dufresne EM, Foffi G, Grybos P, Kmon P, Maj P, Szczygiel R, Hard-sphere-like dynamics in highly concentrated alpha-crystallin suspensions, *Phys. Rev. E* 97 (2018) 020601. doi:10.1103/PhysRevE.97.020601.

- [11]. Chung PJ, Zhang Q, Hwang HL, Leong A, Maj P, Szczygiel R, Dufresne EM, Narayanan S, Adams EJ, Lee KYC, α -Synuclein Sterically Stabilizes Spherical Nanoparticle-Supported Lipid Bilayers, *ACS Appl. Bio Mater* 2 (2019) 1413–1419. doi:10.1021/acsabm.8b00774.
- [12]. Möller J, Chushkin Y, Prevost S, Narayanan T, Multi-speckle X-ray photon correlation spectroscopy in the ultra-small-angle X-ray scattering range, *J. Synchrotron Radiat* 23 (2016) 929–936. doi:10.1107/S1600577516008092. [PubMed: 27359141]
- [13]. Fluerasu A, Moussaïd A, Falus P, Gleyzolle H, Madsen A, X-ray photon correlation spectroscopy under flow, *J. Synchrotron Radiat* 15 (2008) 378–384. doi:10.1107/S0909049508006420. [PubMed: 18552431]
- [14]. Madsen A, Fluerasu A, Ruta B, Structural dynamics of materials probed by X-ray photon correlation spectroscopy, in: *Synchrotron Light Sources Free. Lasers Accel. Physics, Instrum. Sci. Appl.*, Springer International Publishing, 2016: pp. 1617–1641. doi:10.1007/978-3-319-14394-1_29.
- [15]. Zhang Q, Dufresne EM, Narayanan S, Maj P, Kozioł A, Szczygiel R, Grybos P, Sutton M, Sandy AR, Sub-microsecond-resolved multi-speckle X-ray photon correlation spectroscopy with a pixel array detector, *J. Synchrotron Radiat* 25 (2018) 1408–1416. doi:10.1107/S1600577518009074. [PubMed: 30179180]
- [16]. Moger CJ, Barrett R, Bleuët P, Bradley DA, Ellis RE, Green EM, Knapp KM, Muthuvelu P, Winlove CP, Regional variations of collagen orientation in normal and diseased articular cartilage and subchondral bone determined using small angle X-ray scattering (SAXS), *Osteoarthr. Cartil* 15 (2007) 682–687. doi:10.1016/J.JOCA.2006.12.006.
- [17]. Pennicard D, Lange S, Smoljanin S, Hirsemann H, Graafsma H, LAMBDA - Large area medipix3-based detector array, in: *J. Instrum.*, IOP Publishing, 2012: p. C11009. doi:10.1088/1748-0221/7/11/C11009.
- [18]. Zhang Q, Bahadur D, Dufresne EM, Grybos P, Kmon P, Leheny RL, Maj P, Narayanan S, Szczygiel R, Ramakrishnan S, Sandy A, Dynamic Scaling of Colloidal Gel Formation at Intermediate Concentrations, *Phys. Rev. Lett* 119 (2017) 178006. doi:10.1103/PhysRevLett.119.178006.
- [19]. Othman SF, Williams JM, Sumner DR, Magin RL, MRI heterogeneity of articular cartilage in strong magnetic fields: Dependence on proteoglycan content, *Concepts Magn. Reson* 23B (2004) 33–43. doi:10.1002/cmr.b.20017.
- [20]. Khan F, Narayanan S, Sersted R, Schwarz N, Sandy A, Distributed X-ray photon correlation spectroscopy data reduction using Hadoop MapReduce, *J. Synchrotron Radiat* 25 (2018) 1135–1143. doi:10.1107/S160057751800601X. [PubMed: 29979175]
- [21]. Ng L, Grodzinsky AJ, Patwari P, Sandy J, Plaas A, Ortiz C, Individual cartilage aggrecan macromolecules and their constituent glycosaminoglycans visualized via atomic force microscopy, *J. Struct. Biol* 143 (2003) 242–257. doi:10.1016/j.jsb.2003.08.006. [PubMed: 14572479]
- [22]. Cohen NP, Foster RJ, Mow VC, Composition and dynamics of articular cartilage: structure, function, and maintaining healthy state., *J. Orthop. Sports Phys. Ther* 28 (1998) 203–15. doi:10.2519/jospt.1998.28.4.203. [PubMed: 9785256]
- [23]. Zernia G, Huster D, Collagen dynamics in articular cartilage under osmotic pressure, *NMR Biomed.* 19 (2006) 1010–1019. doi:10.1002/nbm.1061. [PubMed: 16823903]
- [24]. DiDomenico CD, Bonassar LJ, How can 50 years of solute transport data in articular cartilage inform the design of arthritis therapeutics?, *Osteoarthr. Cartil* 26 (2018) 1438–1446. doi:10.1016/J.JOCA.2018.07.006.
- [25]. Kusayama Y, Akamatsu Y, Kumagai K, Kobayashi H, Aratake M, Saito T, Changes in synovial fluid biomarkers and clinical efficacy of intra-articular injections of hyaluronic acid for patients with knee osteoarthritis, *J. Exp. Orthop* 1 (2014) 1–9. doi:10.1186/s40634-014-0016-7. [PubMed: 26914746]
- [26]. Papagiannopoulos A, Waigh TA, Hardingham T, Heinrich M, Solution Structure and Dynamics of Cartilage Aggrecan, (2006). doi:10.1021/bm060287d.
- [27]. Huster L'z D, Naji L, Schiller J, Arnold K, Dynamics of the Biopolymers in Articular Cartilage Studied by Magic Angle Spinning NMR, 2004.

- [28]. Huster D, Schiller J, Arnold K, Comparison of collagen dynamics in articular cartilage and isolated fibrils by solid-state NMR spectroscopy, *Magn. Reson. Med* 48 (2002) 624–632. doi:10.1002/mrm.10272. [PubMed: 12353279]
- [29]. Arkill KP, Winlove CP, Solute transport in the deep and calcified zones of articular cartilage, *Osteoarthr. Cartil* 16 (2008) 708–714. doi:10.1016/j.joca.2007.10.001.
- [30]. Mow VC, Mansour JM, The nonlinear interaction between cartilage deformation and interstitial fluid flow, *J. Biomech* 10 (1977) 31–39. doi:10.1016/0021-9290(77)90027-6. [PubMed: 845175]
- [31]. Holmes DF, Lu Y, Starborg T, Kadler KE, Collagen Fibril Assembly and Function, in: *Curr. Top. Dev. Biol.*, Academic Press Inc., 2018: pp. 107–142. doi:10.1016/bs.ctdb.2018.02.004.
- [32]. Sophia Fox AJ, Bedi A, Rodeo SA, The basic science of articular cartilage: structure, composition, and function., *Sports Health*. 1 (2009) 461–8. doi:10.1177/1941738109350438. [PubMed: 23015907]
- [33]. McGann ME, Bonitsky CM, Jackson ML, Ovaert TC, Trippel SB, Wagner DR, Genipin crosslinking of cartilage enhances resistance to biochemical degradation and mechanical wear., *J. Orthop. Res* 33 (2015) 1571–1579. doi:10.1002/jor.22939. [PubMed: 25939430]
- [34]. Ko LS, Quinn TM, Matrix fixed charge density modulates exudate concentration during cartilage compression, *Biophys. J* 104 (2013) 943–950. doi:10.1016/j.bpj.2012.12.036. [PubMed: 23442973]
- [35]. Schmidt TA, Gastelum NS, Nguyen QT, Schumacher BL, Sah RL, Boundary lubrication of articular cartilage: Role of synovial fluid constituents, *Arthritis Rheum*. 56 (2007) 882–891. doi:10.1002/art.22446. [PubMed: 17328061]

Fig. 1:

A time-averaged 2D SAXS pattern was determined for a representative cartilage sample (A). The cartilage structure is anisotropic; therefore, beam scattering is also anisotropic. A horizontal mask was created to simplify data analysis and can be visualized with the white dashed lines (B). Only data between the two white dashed lines were analyzed. XPCS acquisition parameters were adjusted to reduce radiation damage to the cartilage (C). The 1D SAXS was averaged in 100 frame increments and then the 100 frame increments were overlaid. The overlaid static structures remained the same, demonstrating the structural integrity of the cartilage ECM did not change during XPCS measurement collection.

Fig. 2:

Normalized autocorrelation decays were determined at different length scales. Cartilage matrix components that are 207 nm (A), 102 nm (B), and 50 nm (C) follow the same trend, where their mobility is fastest in deionized water and slowest in non-degraded synovial fluid. Furthermore, as the length scale becomes smaller, the time scale for decay is faster.

Fig. 3:

Normalized autocorrelation decays were determined for ten different depths in a dried/dehydrated cartilage sample (A), and ten different depths in three different cartilage samples hydrated with non-degraded synovial fluid (B). The time for normalized autocorrelations to decay 25% (open shapes) increased by 0.2 s per μm of depth ($p < 0.0001$) and to decay 50% (closed shapes) increased by 0.24 s per μm of depth ($p < 0.0001$) in hydrated samples (C). Histological cross-sections of cartilage samples were stained with Safranin O Fast Green. Images were acquired at 4x and scale bars represent 1 mm (D).

Fig. 4:

Normalized autocorrelation decays were determined at the cartilage surface hydrated with PBS and cross-linked in three different concentrations of genipin. The dynamics of the ECM were slowed by increased matrix crosslinking and trends were repeatable across all three animals (A-C). Histological cross-sections of cartilage samples were stained with Safranin O Fast Green. Images were acquired at 10x and scale bars represent 200 μm . Black arrows indicate the location of data collection. The time for normalized autocorrelations to decay 25% and 50% increased as genipin concentration increased (D).

Fig. 5:

Normalized autocorrelation decays were determined at the cartilage surface of samples exposed to non-degraded synovial fluid, deionized water, and PBS. For all three animals, the matrix was more mobile in deionized water and slowest in synovial fluid (A-C). Histological cross-sections of cartilage samples were stained with Safranin O Fast Green. Images were acquired at 10x and scale bars represent 200 μ m. Black arrows indicate the location of data collection. The 50% decay time was different for the cartilage ECM in deionized water, PBS, and synovial fluid (D, $p = 0.008$). Specifically, the cartilage ECM autocorrelation

function decayed slower and thus was less mobile in synovial fluid compared to deionized water ($p = 0.004$) and PBS ($p = 0.02$) and less mobile in PBS compared to deionized water ($p = 0.04$).

Author Manuscript

Author Manuscript

Author Manuscript

Author Manuscript

Fig. 6:

Normalized autocorrelation decays were determined at the cartilage surface of samples exposed to different degrees of degraded synovial fluid. Cartilage ECM mobility increased as synovial fluid degradation increased, and dynamic trends were repeatable across all three animals (A-C). Histological cross-sections of cartilage samples were stained with Safranin O Fast Green. Images were acquired at 10x and scale bars represent 200 μ m. Black arrows indicate the location of data collection. The 25% and 50% decay times were decreased as degree of synovial fluid degradation increased (D, $p = 0.02$, $p = 0.01$, respectively).

Specifically, compared to non-degraded synovial fluid, the 25% decay time was faster for 40 sec and 120 sec of sonication ($p = 0.04$, $p = 0.005$, respectively). Moreover, compared to non-degraded synovial fluid, the 50% decay time was faster for 40 sec and 120 sec of sonication ($p = 0.04$, $p = 0.004$), and compared to 40 sec of sonication, the 50% decay time was fast for 120 sec of sonication ($p = 0.041$).