EPA Public Access

Author manuscript

Environ Res. Author manuscript; available in PMC 2021 November 08.

About author manuscripts

Submit a manuscript

Published in final edited form as:

Environ Res. 2020 August ; 187: 109700. doi:10.1016/j.envres.2020.109700.

Role of water chemistry on stability, aggregation, and dissolution of uncoated and carbon-coated copper nanoparticles

Ayenachew Tegenaw^a, George A. Sorial^{a,*}, Endalkachew Sahle-Demessie^b, Changseok Han^c

^a Environmental Engineering Program, Department of Chemical and Environmental Engineering, College of Engineering and Applied Science, University of Cincinnati, 701 Engineering Research Center, 2901 Woodside Drive P.O. Box 210012, Cincinnati, OH, 45221-0012, United States

^b U.S. Environmental Protection Agency, Office of Research and Development, Center for Environmental Solution and Emergency Response, 26 W. Martin Luther Drive, Cincinnati, OH, 45268, United States

^c Department of Environmental Engineering, College of Engineering, INHA University, 100 Inharo, Nam-gu Incheon, 22212, South Korea

Abstract

Intentional or accidental release of copper nanoparticles (Cu-NPs) from consumer products during manufacturing, use, and end-of-life management could pose health and ecological risks. This paper presents a detailed study on the role of water chemistry on the fate of uncoated and carbon-coated Cu-NPs dispersed in aqueous cetyltrimethylammonium bromide (CTAB) surfactant in the presence and absence of humic acids (HAs). A range of water chemistry and HAs had minimum impact on hydrodynamic diameter and zeta-potential values of uncoated and carbon-coated Cu-

* Corresponding author. george.sorial@uc.edu (G.A. Sorial).

Credit author contribution statement

Ayenachew Tegenaw: Conceptualization, Methodology, Formal analysis, Investigation, Data curation, Writing – original draft, Writing - review, and Visualization, George A. Sorial: Conceptualization, Methodology, Validation, editing, and Supervision, Endalkachew Sahle-Demessie: Validation, Conceptualization, Supervision, Methodology and editing, Changseok Han: Methodology, Formal Analysis, and Data curation.

Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Appendix A. Supplementary data

Supplementary data to this article can be found online at <https://doi.org/10.1016/j.envres.2020.109700>.

Supplementary data

Detailed discussion of TGA analysis of SRHA/SAHA and FTIR analysis of SRHA/SAHA with and without uncoated and carbon-coated Cu-NPs is presented in Sections S1 and S2. Analytical tables of XRD, D_h , ζ -potential, aggregation, and dissolution data of uncoated and carbon-coated Cu-NPs are provided in the supplementary data (Tables S1–S11). Analytical figures of more TEM images (Fig. S1), D_h of uncoated and carbon-coated Cu-NPs in PVP dispersant (Fig. S2), thermogravimetric analysis of SRHA/SAHA samples (Fig. S3), FTIR spectroscopy analysis of SRHA/SAHA with and without uncoated and carbon-coated Cu-NPs samples (Fig. S4) and mass balance of dissolved Cu (Fig. S5) are also located in the supplementary data.

Disclaimer

This paper has been subjected to the U.S. EPA review and has been approved for publication. Note that approval does not signify that the contents necessarily reflect the views of the Agency. Any mention of trade names, manufacturers, or products does not imply an endorsement by the U.S. Government or the U.S. EPA. The U.S. EPA and its employees do not endorse any commercial products, services, or enterprises.

NPs. The water pH significantly ($p < 0.001$) affected the aggregation of uncoated Cu-NPs unlike that of carbon-coated Cu-NPs; however, the presence of HAs increased the stability of uncoated Cu-NPs. Although CTAB is considered as an efficient dispersant to stabilize Cu-NPs, the effect descended with time for uncoated Cu-NPs. The dissolution of Cu over time decreased with increasing pH for both uncoated (0.5–50% weight) and carbon-coated (0.5–40% weight) Cu-NPs. However, carbon-coated Cu-NPs exhibited significant dissolution ($p < 0.001$) at neutral pH than uncoated Cu-NPs may be due to the additional carbon it acquired during coating. Increasing HAs concentration from 0 to 15 mg L⁻¹ at pH 5.5 inhibited aggregations but enhanced dissolution of the uncoated and carbon-coated Cu-NPs. These findings inform risk analysis of Cu-NPs including how Cu-NPs fate, mobility and bioavailability are modulated by particles coating and dispersant, HAs presence, water chemistry and exposure time in dispersion media.

Keywords

Aggregation; Cu-NPs fate; Ecological risks; Risk analysis; Water chemistry

1. Introduction

Copper nanoparticles (Cu-NPs) have attracted a growing interest for catalysis, optical, electronic, conductive coatings/inks/pastes/slurry, nanofluids, and antimicrobial applications (Ingle et al., 2014; Jang et al., 2010; Umer et al., 2012). Nearly 200,000 kg of Cu and Cu_xO NPs were produced in 2010, and about 75%, 18%, 5.5%, and 1.5% of this account were ended up in landfill, soil, water, and air, respectively (Keller et al., 2013). The release of Cu-NPs into the ecosystems during manufacturing, use, and end-of-life management via different exposure pathways is an emerging ecological concern (Taylor and Walker, 2016). Cu is required by all organisms to carry out fundamental biological functions for normal growth and development (Yruela, 2009). However, excessive Cu oxidizes important biomolecules such as lipids, proteins, deoxy (ribonucleic) acids, and modifies molecular oxygen to produce reactive oxygen radicals that damage cells, enzymes, and protein structures (Chen et al., 2000; Sarkar et al., 2011).

Past research has found that excess Cu can have detrimental environmental effects. Studies have shown that exposure to Cu-NPs could cause health effects including hepatotoxicity, nephrotoxicity, cytotoxicity, phytotoxicity, and genotoxicity (Hejazy et al., 2018; Ingle et al., 2014; Lei et al., 2008; Mosa et al., 2018; Prasad et al., 2016). Cu-NPs have been reported to impact the performance of key wastewater treatment processes such as nitrification, denitrification, anaerobic digestion and enhanced biological phosphorus removal (Mu et al., 2014; Yang et al., 2013). Cu-NPs could also inhibit the microbial degradation of several pesticides (Gaw et al., 2006; Gunasekara et al., 2005; Jindal et al., 2000; Kim et al., 2011; Liu et al., 2007). The U.S. Environmental Protection Agency (U.S. EPA) listed Cu and its compounds as toxic and priority pollutants under the Clean Water Act (CWA) and Comprehensive Environmental Response, Compensation, and Liability Act (CERCLA) at the Code of Federal Regulations (CFR) 40 CFR 401.15 and 40 CFR 302, respectively.

Although detailed review of Cu-NPs toxicity exist (Hejazy et al., 2018; Ingle et al., 2014); however, in the complex and dynamic environmental matrices the toxicity depends on the stability of the NPs in the encountered media and their transformations (Conway et al., 2015; Keller et al., 2017; Song et al., 2014). The stability of Cu-NPs is subject to pH, ionic strength, and electrolyte valence of the environmental media and the presence of natural organic matter (NOM) (Aiken et al., 2011; Arenas-Lago et al., 2019; Cornelis et al., 2014). Solution pH could impact the aggregation, dissolution, bioavailability, and toxicity of Cu-NPs by affecting the surface potential of the NPs (Adeleye et al., 2014; Peng et al., 2017; Xiao et al., 2018b). Dissolved organic matter (DOM) adsorbed to Cu-NPs surfaces could alter NPs surfaces physicochemical properties and enhance/suppress NPs aggregation/dissolution via electrostatic repulsion and/or steric interactions (Kloster et al., 2013; Wang et al., 2015; Xiao et al., 2018b). However, the complexation of polyvalent cations with the carboxylic groups of DOM could form intermolecular bridging effect that compresses the electrical double layer (EDL) of the NPs (Kloster et al., 2013; Zhang et al., 2009). The EDL compression caused by the intermolecular bridging effect could diminish ζ -potential values of NPs which in turn lead to NPs aggregation (Chen and Elimelech, 2007; Kloster et al., 2013; Zhang et al., 2009). The origin, composition, and properties of DOM also influence the fate and mobility of the NPs (Baken et al., 2011; Li et al., 2017).

Information on the role of water chemistry on Cu-NP is far less available than Ag, TiO₂, and ZnO NPs (Adeleye et al., 2014; Arenas-Lago et al., 2019; Conway et al., 2015; Jones and Su, 2012; Keller et al., 2017; Xiao et al., 2018a, 2018b). Moreover, there is a need of information regarding the role of water chemistry on Cu-NPs stability in consideration of capping (dispersants and coatings) agents (Li et al., 2007; Saterlie et al., 2012). Capping agents such as polymers and surfactants (cationic, anionic, and non-ionic) prevent NPs aggregation via electrostatic, steric or electro steric stabilization mechanisms (El Badawy et al., 2010). Capping agents change the surface properties of NPs and could exhibit surface charge-dependent toxicity of NPs (El Badawy et al., 2011; Saterlie et al., 2012). Cu-NPs were also coated with carbon at laboratory and mass production scales to enhance oxidation stability (Athanasios et al., 2006; Eiroma et al., 2012; Li and Liu, 2009; Li et al., 2010). However, no research work has been done on uncoated versus carbon-coated Cu-NPs colloidal stability at a range of water chemistry in the presence and absence of DOM. Therefore, the goal of the current research was to investigate how water chemistry of the exposure media modulates the stability (aggregation and dissolution) of uncoated and carbon-coated Cu-NPs in view of potential ecological implications.

2. Material and methods

2.1. Cu-NPs

Two types of Cu-NPs (uncoated and carbon-coated Cu-NPs) were selected for this study. The uncoated and carbon-coated Cu-NPs in powder forms were obtained from US Research Nanomaterials, Inc. (Houston, Texas). As per the manufacturer, the uncoated and carbon-coated Cu-NPs were made by laser synthesis method and have the following common properties: 25 nm average particle size, 99.8% purity, 30–50 m² g⁻¹ specific surface area,

0.15–0.35 g cm⁻³ bulk density, 8.94 g cm⁻³ true density, and spherical shape. The uncoated Cu-NP has a dark-brown color, whereas the carbon-coated Cu-NP is black.

2.2. The crystalline phases of Cu-NPs

The crystalline phases of uncoated and carbon-coated Cu-NPs were analyzed using X-ray diffractometer (XRD: PANalytical Xpert Pro 2 θ) with Cu-K α radiation source ($\lambda = 1.5415$ Å) operating at 40 kV and 40 mA. Phase identification and peak analysis were carried out by means of X'Pert accompanying software program PANalytical High Score Plus in conjunction with the Joint Committee on Powder Diffraction Standards (JCPDS) Database (Kobayashi et al., 2012; Yu et al., 2010). The elemental spectra of the uncoated and carbon-coated Cu-NPs were also analyzed using energy dispersive X-ray analysis (EDXA) installed in a scanning electron microscope (SEM: JSM-6490LV, JEOL) to verify the uncoated and carbon-coated Cu-NPs as Cu-NPs and imply the occurrence of oxidation due to oxygen presence.

2.3. Cu-NPs hydrodynamic diameter (D_h), zeta potential (ζ -potential), and morphology

A 100 mg of each Cu-NPs was dispersed separately in 1 L of 0.09 mM aqueous cetyl trimethylammonium bromide (CTAB) cationic surfactant solution using probe sonicator at 30 W for 10 min. Milli-Q water (deionized ultra-pure water, Millipore Corporation, “Type 1”, as defined by ISO 3696 with resistivity (> 18 M Ω -cm) and conductivity (< 0.056 μ S cm⁻¹) at 25 °C) was used in the preparation of 0.09 mM (i.e., the critical micelle concentration (CMC) value) CTAB solution. The uncoated and carbon-coated Cu-NPs were also prepared in the presence of 5 and 15 mg L⁻¹ of HAs from Suwannee River (SRHA) and Sigma Aldrich (SAHA) to make a total of ten dispersions samples (five for uncoated Cu-NPs (HA-0, SRHA-5, SRHA-15, SAHA-5, and SAHA-15) and five for carbon-coated Cu-NPs (HA-0, SRHA-5, SRHA-15, SAHA-5, and SAHA-15). Particle sizer and ζ -potential analyzer (NanoBrook Omni, Brookhaven Instruments Corporation) was used to measure D_h and ζ -potential values of triplicate samples of all dispersions using dynamic light scattering (DLS) and phase analysis light scattering (PALS) techniques, respectively. Dispersions of the uncoated and carbon-coated Cu-NPs in polyvinylpyrrolidone (PVP) polymeric dispersant were also prepared and analyzed for D_h and ζ -potential measurements to see the effect of a different dispersing agent. PVP was selected for this study since it is an effective reducing agent, surface stabilizer and dispersant that modifies NPs surfaces (Koczur et al., 2015). PVP is also a common and widely used dispersant for Cu-NPs (Umer et al., 2012).

The thermal stability and chemical analysis (functional groups) of SRHA and SAHA were analyzed using a thermogravimetric analyzer (TGA: Q500, TA Instruments) and a Fourier-transform infrared spectroscopy (FTIR: PerkinElmer 200), respectively. The FTIR spectra of uncoated Cu-NPs (alone and with SRHA/SAHA) and carbon-coated Cu-NPs (alone and with SRHA/SAHA) were also analyzed to see a change in the FTIR spectrum peak. The results and discussions of the TGA and FTIR analyses are presented in the Supplementary Data (S) in Figs. S3 and S4 and Section S1, S2.

The morphology of the uncoated and carbon-coated Cu-NPs was determined using transmission electron microscope (TEM: JEM-2100, JEOL) operating at 200 kV after the dispersions in CTAB solution were placed and dried separately on 200 mesh TEM Au grids (Ted Pella, Inc.).

2.4. Role of water chemistry on Cu-NPs D_h and ζ -potential

We investigated the role of water chemistry on the stability of Cu-NPs after sonication in triplicates for a total of ten dispersions (Section 2.4). The dispersions were adjusted to three ionic strengths (1, 10, and 20 mM) of Na^+ (using NaCl) and Ca^{2+} (using CaCl_2), respectively. All samples were prepared in three pH values (5.5, 7.0, and 8.5) using 0.1 M HCl/NaOH solution and stirred for 15 min. The selection of HAs (5 and 15 mg L^{-1}), ionic strengths of both Na^+ and Ca^{2+} (1, 10, and 20 mM), and pH (5.5, 7.0, and 8.5) values was based on environmental considerations of most agricultural soils and aquatic (surface and ground waters) ecosystems, and water/wastewater treatment processes in which Cu-NPs may be released and/or transported (Fondriest Environmental Inc, 2013; French et al., 2009; Gao et al., 2017; Kobayashi et al., 2012; McCauley et al., 2009; Rodrigues et al., 2009; Sobek et al., 2007; Yu et al., 2010; Zazouli et al., 2007). A total of 540 subsamples (37.5 mL each in a 50 mL tube) were analyzed for D_h and ζ -potential measurements using DLS and PALS techniques, respectively. The account of the 540 subsamples was as follows: two Cu-NPs (uncoated and carbon-coated), five dispersions for each Cu-NPs (HA-0, SRHA-5, SRHA-15, SAHA-5, and SAHA-15), six ionic strengths (1, 10, 20 mM Na^+ and 1, 10, 20 mM Ca^{2+}), three pH (5.5, 7.0, and 8.5), and three replicates, i.e., $2 \times 5 \times 6 \times 3 \times 3 = 540$ subsamples.

Statistically significant differences between D_h and ζ -potential values were evaluated by t -tests using Microsoft Excel 2016 software. The specific analysis of the applied t -test was “ t -test: two-sample assuming unequal variances” with a more stringent alpha value of 0.001 (Johnson, 2013). The statistically significant differences were determined based on the obtained probability value (p-value) of one-tailed distribution t -test.

2.5. Role of water chemistry on Cu-NPs aggregation and dissolution

The role of water chemistry on aggregation and dissolution of Cu-NPs in HA-0, SAHA-5, and SAHA-15 solutions after sonication (Section 2.4) was investigated for a total of six dispersions (three for uncoated Cu-NPs and three for carbon-coated Cu-NPs) as a function of time (0.01, 0.5, 1, 2, 3, 6, 9, 12, 15, 30, and 60 d). The criteria of choosing SAHA over that of SRHA for this experiment was due to insignificant differences in D_h and ζ -potential values between SRHA and SAHA solutions in both uncoated and carbon-coated Cu-NPs (see Section 3.2) and SRHA is (acted as) a standard or reference HA. The six dispersions in triplicate were adjusted to the ionic strength of 10 mM Ca^{2+} . The Ca^{2+} was selected due to the influence of polyvalent cations to undergo complexation with HAs to produce intermolecular bridging effect that cause reduction of surface ζ -potential and aggregation of the NPs and 10 mM was chosen in consideration of most likely environmental compartments in which the NPs may undergo (Kloster et al., 2013; Wang et al., 2015; Xiao et al., 2018b). The pH was also adjusted to 5.5, 7.0, and 8.5 using 0.1 M HCl/NaOH solution. A total of 594 sealed vials (50 mL) with 37.5 mL solution were then placed in a mechanical tumbler at 12 ± 1 revolution per min (rpm). Three sealed vials were used at each pH level to measure

D_h and dissolved Cu for dispersions matrix. The pH of each sample was also measured during the course of the experiment to observe pH variation.

The dissolved Cu ion concentration of each sample was then analyzed using atomic absorption spectroscopy (AAS: PerkinElmer AAnalyst 300) following centrifugal ultrafiltration process (10 kDa pore size Amicon centrifugal ultrafiltration tubes at 6000 rpm for 30 min at 20 °C) and acidification of 5 mL of the sample with 5 mL of concentrated HCl solution (Zhang et al., 2011). The 10 kDa pore size Amicon centrifugal ultrafiltration tubes have two compartments (the upper and the lower). The lower compartment is for the collection of dissolved ionic Cu after passing through the 10 kDa ultrafiltration membrane, whereas the undissolved NPs remain in the upper compartment. The dissolved Cu ions cannot pass through the 10 kDa ultrafiltration membrane without the use of centrifuge. The maximum pore size of the 10 kDa ultrafiltration membrane is ~3 nm (Conway et al., 2015; Erickson, 2009; Sweeney et al., 2006). A mass balance of uncoated and carbon-coated Cu-NPs was also conducted at all pH and HA values using 15 min samples to evaluate the lost Cu during processing.

3. Results and discussion

3.1. The crystalline phases and morphology of Cu-NPs

The XRD spectra of the uncoated and carbon-coated Cu-NPs recorded in the 2 θ range of 20°–80° are shown in Fig. 1a–b. The diffraction peaks observed in the uncoated and carbon-coated Cu-NPs at 43.3°, 50.4°, and 74.2° correspond to (111), (200), and (220) planes of Cu crystal, respectively (Fig. 1a–b; Table S1). The diffraction peaks observed in the uncoated and carbon-coated Cu-NPs at 29.5°, 36.4°, 42.3°, and 61.4° correspond to (110), (111), (200), and (220) planes of Cu₂O crystals, respectively (Fig. 1a–b; Table S1). The diffraction peaks observed in uncoated Cu-NPs at 35.4° and 38.6° correspond to (111) and (111) planes of CuO crystal, respectively (Fig. 1a; Table S1). The results are in good agreement with the reported values of JCPDS no. 04–0836 for Cu crystals (Kobayashi et al., 2012; Yu et al., 2010), JCPDS no. 05–0667 for Cu₂O crystals (Giannousi et al., 2014; Khan et al., 2016), and JCPDS no. 80–1268 for CuO crystals (Lanje et al., 2010; Zhu et al., 2004). The presence of Cu₂O and CuO could be due to oxidation of Cu at ambient atmosphere (Bojko et al., 2000; Iijima et al., 2006; Platzman et al., 2008; Suzuki et al., 1997). The oxidation of uncoated Cu-NPs produced both Cu₂O and CuO, whereas the oxidation of carbon-coated Cu-NPs yielded only Cu₂O. The result furnishes the information that although the coating of Cu-NPs with carbon slows oxidation compared to uncoated one; however, Cu-NPs are prone to oxidation. The average crystalline sizes of the uncoated and carbon-coated Cu-NPs based on Scherrer's formula, were estimated to be about 20 nm (Purushothaman and Muralidharan, 2009).

The elemental spectra conducted on the uncoated and carbon-coated Cu-NPs using EDXA in conjunction with SEM verified the NPs as Cu by showing strong peaks of Cu at 1, 8, and 9 keV (Fig. 1c–d, f–g). The presence of elemental oxygen on the EDXA spectra in the uncoated and carbon-coated Cu-NPs (Fig. 1d, g) also reinforced the oxidation of the uncoated and carbon-coated Cu-NPs by XRD analysis (Fig. 1a–b). The morphology of the uncoated and carbon-coated Cu-NPs in CTAB dispersant after TEM analysis is shown in

Fig. 1e, h. The TEM images showed polydisperse spherical NPs in the size range of 5–50 nm with mean value of 25 nm for the uncoated and carbon-coated Cu-NPs (Fig. 1e, h). Up to 100 nm or higher clusters of Cu-NPs were also observed in the additional TEM images provided in Fig. S1.

3.2. Cu-NPs D_h and ζ -potential

The D_h and ζ -potential values of uncoated Cu-NPs in all dispersions (HA-0, SRHA-5, SRHA-15, SAHA-5, and SAHA-15) after DLS and PALS measurements analyses were in the range of 245–315 nm and +41-(+49) mV, respectively (Fig. 1i–j). Correspondingly, the D_h and ζ -potential values of carbon-coated Cu-NPs in all dispersions were in the range of 120–140 nm and +35-(+47) mV, respectively (Fig. 1i–j). The D_h value of NPs is the combined diameter of the particle and the surrounding fluid layer/media adsorbed on the NPs surfaces (Bhattacharjee, 2016). From the point of coating carbon-coated Cu-NPs could have larger D_h value than the uncoated Cu-NPs. However, the carbon-coated Cu-NPs were coated with carbon during synthesis that may control their sizes. In addition, the thickness of the fluid layer adsorbed on uncoated and carbon-coated Cu-NPs may vary and significantly affects the D_h value. Thus, microscopic images are needed to verify the actual size of the NPs. The analysis of the results showed that there were significant D_h differences ($p = 0.001$) and insignificant ζ -potential difference ($p = 0.122$) between uncoated and the corresponding carbon-coated Cu-NPs of each tested dispersion. Moreover, there were insignificant differences in D_h values ($p = 0.172$) and ζ -potential values ($p = 0.280$) among all tested dispersions of uncoated and carbon-coated Cu-NPs. On the other hand, uncoated Cu-NPs were stable in PVP dispersant having average D_h of 290 ± 10 nm and ζ -potential of $+9 \pm 2$ mV (Fig. S2a); however, carbon-coated Cu-NPs were aggregated in PVP dispersant having average D_h of 2200 ± 200 nm and ζ -potential of -7 ± 3 mV (Fig. S2b). The stability of Cu-NPs by CTAB cationic surfactant is through electrostatic stabilization mechanism, whereas in the case of PVP polymer the stability is through steric stabilization due to the adsorption of PVP on Cu-NPs surfaces. However, adsorption of PVP polymer on the surfaces of the carbon-coated Cu-NPs (already coated with carbon) resulted in larger D_h value (the D_h value of NPs is the combined diameter of the particle and the surrounding fluid layer adsorbed on the NPs surfaces). The PVP is an uncharged polymer that does not protonate/deprotonate; thus it has lower ζ -potential value and its stabilization effect is through steric repulsion (Csempeš and Csáki, 2000; El Badawy et al., 2010). The lower limit of 30 mV ζ -potential absolute value is a general term and may not apply to sterically stabilized NPs with PVP or other uncharged polymers (Csempeš and Csáki, 2000; El Badawy et al., 2010). The result showed that CTAB is a good dispersant for uncoated and carbon-coated Cu-NPs than PVP. This scenario implies that the type of dispersant plays a key role in the stability of NPs during synthesis and nanopowder dispersion and in aqueous ecosystems in which such NPs could be released (Bakshi, 2009; Chen et al., 2003; Mulvaney, 1996).

3.3. Role of water chemistry on D_h and ζ -potential values of Cu-NPs

The role of solution pH, ionic strength, electrolytes valence, and SRHA/SAHA on D_h and ζ -potential values of uncoated and carbon-coated Cu-NPs dispersed in aqueous CTAB solution after DLS and PALS measurements are shown in Fig. 2 and Fig. 3 and Tables S2–

S5, respectively. The D_h and ζ -potential values of uncoated Cu-NPs in all tested dispersions across all ionic strength of Na^+ (1–20 mM) at pH 5.5, 7.0, and 8.5 were in the range of 255–365 nm and +43-(+53) mV, 248–345 nm and +39-(+54) mV, and 250–335 nm and +40-(+51) mV, respectively (Fig. 2a–c; Fig. 3a–c; Tables S2 and S4). The D_h and ζ -potential values of uncoated Cu-NPs in all tested dispersions for ionic strength of Ca^{2+} (1–20 mM) at pH 5.5, 7.0, and 8.5 were also in the range of 280–375 nm and +38-(+52) mV, 285–360 nm and +33-(+54) mV, and 280–365 nm and +32-(+53) mV, respectively (Fig. 2d–f; Fig. 3d–f; Tables S2 and S4). Correspondingly, the D_h and ζ -potential values of carbon-coated Cu-NPs in all tested dispersions across all ionic strength of Na^+ at pH 5.5, 7.0, and 8.5 were in the range of 117–133 nm and +34-(+46) mV, 119–138 nm and +34-(+45) mV, and 120–143 nm and +32-(+43) mV, respectively (Fig. 2g–i; Fig. 3g–i; Tables S3 and S5). The D_h and ζ -potential values of carbon-coated Cu-NPs in all tested dispersions across all ionic strength of Ca^{2+} at pH 5.5, 7.0, and 8.5 were also in the range of 123–135 nm and +34-(+45) mV, 123–139 nm and +32-(+46) mV, and 124–141 nm and +32-(+43) mV, respectively (Fig. 2j–l; Fig. 3j–l; Tables S3 and S5).

The results showed significant differences in D_h values ($p = 0.0004$) between uncoated and the corresponding carbon-coated Cu-NPs at a range of water chemistry while the effects on ζ -potential values differences were less significant ($p = 0.091$). The effect of the other factors including ionic strengths of Na^+ and Ca^{2+} (1–20 mM), pH values (5.5–8.5) and presence of SRHA/SAHA solutions (0–15 mg L^{-1}) was not significant on the D_h ($p = 0.070$ for uncoated and $p = 0.196$ for carbon-coated) and ζ -potential ($p = 0.247$ for uncoated and $p = 0.228$ for carbon-coated) values among the uncoated and carbon-coated Cu-NPs. The differences in the thermal degradation steps and the main functional groups present in the analyzed SRHA/SAHA samples accounts for the variations in the D_h and ζ -potential values (Figs. S3 and S4; Section S1, S2). Although the ζ -potential values of carbon-coated Cu-NPs decreased by < 20% compared to uncoated Cu-NPs; however, the ζ -potential values of uncoated and carbon-coated Cu-NPs in any dispersion was above +30 mV. This shows that the uncoated and carbon-coated Cu-NPs may be stable at a range of water chemistry. The stability of uncoated and carbon-coated Cu-NPs in aqueous CTAB surfactant was due to electrostatic stabilization by CTAB (El Badawy et al., 2012; Li et al., 2007; Mandel et al., 2011). Thus, uncoated and carbon-coated Cu-NPs dispersed in CTAB or related surfactants may be stable in aqueous ecosystems of similar media characteristics as the tested water chemistry parameters. This in turn may favor the mobility of these NPs in aqueous ecosystems. However, long-term stability could not be achieved as in the case of uncoated Cu-NPs and may be for carbon-coated Cu-NPs as well (Fig. 4; Tables S6 and S7).

3.4. Role of water chemistry on aggregation of Cu-NPs

The impact of pH and SAHA on aggregation of uncoated and carbon-coated Cu-NPs in aqueous CTAB solution at 10 mM Ca^{2+} as a function of time (15 min–60 d) after D_h measurement using DLS technique is shown in Fig. 4 and Tables S6 and S7. The D_h values of uncoated Cu-NPs in SAHA-0, SAHA-5, and SAHA-15 solutions at pH 5.5 for the entire time interval were in the range of 170–2480 nm, 150–2080 nm, and 160–1230 nm, respectively (Fig. 4a–c; Table S6). The D_h values of uncoated Cu-NPs in SAHA-0, SAHA-5, and SAHA-15 solutions at pH 7.0 were in the range of 300–2060 nm, 300–1120

nm, and 300–1160 nm, respectively (Fig. 4a–c; Table S6). The D_h values of uncoated Cu-NPs in SAHA-0, SAHA-5, and SAHA-15 solutions at pH 8.5 were also in the range of 300–3780 nm, 320–1170 nm, and 300–1210 nm, respectively (Fig. 4a–c; Table S6). The D_h of uncoated Cu-NPs in the absence of SAHA was significantly impacted by solution pH ($p = 0.007$ for pH 5.5 versus pH 7.0; $p = 0.0002$ for pH 5.5 versus pH 8.5, and $p = 0.012$ for pH 7.0 versus pH 8.5) (Fig. 4a; Table S6). This may be due to the replacement of Br^- by OH^- that transform CTAB to cetyltrimethylammonium hydroxide (CTAOH) at basic pH values (Balakrishnan et al., 2004). This implies that the NPs may lose the support of the electrostatic stabilization of CTAB that could lead to aggregation and precipitation of the uncoated Cu-NPs as time increased (Al-thabaiti et al., 2015). However, this significant effect of pH on the D_h of uncoated Cu-NPs in the absence of SAHA was significantly attenuated by the presence of SAHA-5 ($p = 0.324$) and SAHA-15 ($p = 0.164$) solutions (Fig. 4b–c; Table S6). This could be due to the steric and/or electrosteric stabilization of uncoated Cu-NPs by HAs (Adeleye and Keller, 2014; Yang et al., 2009). Furthermore, time had a significant impact ($p = 0.0001$) on the D_h of uncoated Cu-NPs at day 60 (compared to D_h at 15 min) at all tested pH values and SAHA concentrations. This may be attributed to the inadequacy of CTAB to keep the NPs stability in a longer period of time (Sui et al., 2006). Time also significantly impacted the D_h of uncoated Cu-NPs in the absence of SAHA at pH 7.0 on day 3 (130% increase) and at pH 8.5 on day 0.5 (1000% increase) (Table S6). The percent change (increase/decrease) in the D_h values at each time interval for all tested samples in all pH values is also shown in Table S6. Thus, uncoated Cu-NPs dispersed in CTAB surfactant are prone to aggregation at solution pH 7.0 in the absence of SAHA and in a longer time at all tested pH values in the presence and absence of SAHA solution.

On the other hand, the D_h values of carbon-coated Cu-NPs in SAHA-0, SAHA-5, and SAHA-15 solutions for the entire time interval were in the range of (130–165, 120–195, and 125–165 nm) at pH 5.5, (130–250, 120–180, and 130–180 nm) at pH 7.0, and (130–260, 125–215, and 125–160 nm) at pH 8.5, respectively (Fig. 4d–f; Table S7). Generally, the D_h of carbon-coated Cu-NPs at any tested pH, SAHA, and time values was in the range of 120–260 nm. Thus, solution pH, SAHA concentration, and exposure time had minimum impact ($p > 0.001$) on aggregation of carbon-coated Cu-NPs compared to uncoated Cu-NPs (Fig. 4d–f; Table S7). This may be due to the steric repulsion effect of carbon on carbon-coated Cu-NPs which prevents the particles from aggregation, whereas uncoated Cu-NPs lacks the steric repulsion effect due to the absence of carbon-coating (Kloster et al., 2013; Wang et al., 2015; Xiao et al., 2018b). Table S7 shows the details of percent change in the D_h values of carbon-coated Cu-NPs at any given time at a range of water chemistry in the presence and absence of HAs. This implies that carbon-coated Cu-NPs may stay stable in aqueous ecosystems under similar water chemistry ranges as the tested values. Thus, water chemistry and time had minimum impact on aggregation of carbon-coated Cu-NPs, whereas they had significant impact ($p < 0.001$) on aggregation of uncoated Cu-NPs.

The morphology of the uncoated and carbon-coated Cu-NPs in SAHA-0 solutions after 15 min and 3 d are shown in Fig. 5a–d. The uncoated Cu-NPs showed aggregation after 3 d by forming clusters of particles (Fig. 5b). However, the carbon-coated Cu-NPs did not form clusters after 3 d (Fig. 5d). The results of the SEM microscopic images clearly support the results and discussions of section 3.4.

3.5. Role of water chemistry on dissolution of Cu-NPs

The impact of pH and SAHA on dissolution of uncoated and carbon-coated Cu-NPs in aqueous CTAB solution at 10 mM Ca^{2+} as a function of time (15 min–60 d) after AAS analysis is shown in Fig. 6 and Tables S8 and S9. The result showed that the dissolution of Cu at a range of water chemistry and time was from 5 to 500 g kg^{-1} (0.5–50% weight) for uncoated Cu-NPs and from 5 to 400 g kg^{-1} (0.5–40% weight) for carbon-coated Cu-NPs (Fig. 6a–f; Tables S8 and S9). The highest Cu dissolution was at pH 5.5 and the lowest at pH 8.5 for all scenarios (Fig. 6a–f; Tables S8 and S9). The dissolved Cu in SAHA-0, SAHA-5, and SAHA-15 solutions as a function of time at pH 5.5 was in the range of 290–500 g kg^{-1} , 155–400 g kg^{-1} , and 370–480 g kg^{-1} for uncoated and in the range of 170–400 g kg^{-1} , 150–330 g kg^{-1} , and 300–385 g kg^{-1} for carbon-coated Cu-NPs, respectively (Fig. 6a–f; Tables S8 and S9). The dissolved Cu in SAHA-0, SAHA-5, and SAHA-15 solutions as a function of time at pH 7.0 was in the range of 13–85 g kg^{-1} , 16–110 g kg^{-1} , and 16–170 g kg^{-1} for uncoated and 75–160 g kg^{-1} , 160–230 g kg^{-1} , and 185–250 g kg^{-1} for carbon-coated Cu-NPs, respectively (Fig. 6a–f; Tables S8 and S9). The dissolved Cu in SAHA-0, SAHA-5, and SAHA-15 solutions as a function of time at pH 8.5 was in the range of 5–25 g kg^{-1} , 5–30 g kg^{-1} , and 8–30 g kg^{-1} for uncoated and 5–27 g kg^{-1} , 5–30 g kg^{-1} , and 7–40 g kg^{-1} for carbon-coated Cu-NPs, respectively (Fig. 6a–f; Tables S8 and S9). Generally, the dissolution of Cu in SAHA-0, SAHA-5, and SAHA-15 solutions of uncoated and carbon-coated Cu-NPs increased with decreasing pH.

The dissolution of Cu in SAHA-0, SAHA-5, and SAHA-15 solutions as a function of time from 15 min to 60 d decreased at pH 5.5 and 7.0 but increased at pH 8.5 (Fig. 6a–f; Tables S8 and S9). The overall decrease of Cu dissolution in SAHA-0, SAHA-5, and SAHA-15 solutions as a function of time at pH 5.5 from 15 min to 60 d time interval was 35%, 53%, and 15% weight for uncoated Cu-NPs and 48%, 44%, and 11% weight for carbon-coated Cu-NP, respectively (Fig. 6a–f; Tables S8 and S9). The overall decrease of Cu dissolution in SAHA-0, SAHA-5, and SAHA-15 solutions as a function of time at pH 7.0 was also 80%, 82%, and 88% weight for uncoated Cu-NPs and 45%, 21%, and 14% weight for carbon-coated Cu-NP, respectively (Fig. 6a–f; Tables S8 and S9). However, the overall increase of Cu dissolution in SAHA-0, SAHA-5, and SAHA-15 solutions as a function of time from 15 min to 60 d at pH 8.5 was 270%, 323%, and 182% for uncoated Cu-NPs and 342%, 373%, and 295% for carbon-coated Cu-NPs, respectively (Fig. 6a–f; Tables S8 and S9). The decreased Cu dissolution at pH 5.5 and 7.0 as a function of time may be due to the formation of insoluble complexes of Cu (Conway et al., 2015), whereas the increased Cu dissolution at pH 8.5 as a function of time was attributed to the formation of soluble complexes of Cu at alkaline pH (Doelsch et al., 2010; Temminghoff et al., 1997).

The dissolved Cu in all solutions as a function of time at pH 7.0 and 8.5 was lower than the dissolved Cu at pH 5.5 by 65–95% and 85–99% for uncoated Cu-NPs and by 4–65% and 84–99% for carbon-coated Cu-NPs, respectively (Fig. 6a–f; Tables S8 and S9). Furthermore, the dissolved Cu at pH 8.5 was lower than the dissolved Cu at pH 7.0 by 2–94% and 70–97% for uncoated and carbon-coated Cu-NPs, respectively (Fig. 6a–f; Tables S8 and S9). However, the dissolved Cu at pH 8.5 was slightly greater than the dissolved Cu at pH 7.0 for uncoated Cu-NPs after day 15 (Tables S8 and S9). Thus,

the dissolved Cu at pH 5.5 was significant ($p = 0.0003$) for uncoated and carbon-coated Cu-NPs. However, carbon-coated Cu-NPs exhibited significant dissolution ($p = 0.0001$) of Cu at pH 7.0 compared to uncoated Cu-NPs in all dispersions (Fig. 6a–f; Tables S8 and S9). This may be due to the interaction of the additional carbon (the carbon-coated Cu-NPs acquired during coating) at pH 7.0 with the Cu-NPs to produce more Cu^{+2} ions in the presence of aqueous CTAB solution assisted by pH drop (-0.35), whereas uncoated Cu-NPs lacks such interaction due to the absence of carbon. The pH drop may be due to the inadequacy of 0.01 M HCl/NaOH solution to maintain pH stability over time. However, the complexation of both uncoated and carbon-coated Cu-NPs at pH 8.5 produce only very low magnitude (concentration) of soluble complexes of Cu such as $\text{Cu}_2(\text{OH})_2^{+2}$, $\text{Cu}(\text{OH})_3^-$, $\text{Cu}(\text{OH})_4^{-2}$, CuOH^+ , $\text{Cu}(\text{OH})_2(\text{aq})$, CuCl_3^- , $\text{CuCl}_2(\text{aq})$, CuCl_4^{-2} , and CuCl^+ . Thus, there was insignificant dissolution differences between uncoated and carbon-coated Cu-NPs in all tested dispersions at pH 8.5 (Tables S8 and S9). The highest level of Cu dissolution at pH 5.5 for the uncoated and carbon-coated Cu-NPs and at pH 7.0 for carbon-coated Cu-NPs may increase the bioavailability and mobility of Cu in aqueous ecosystems. Thus, the application and release of Cu-NPs at pH 7 may increase the dissolution of Cu-NPs and the subsequent environmental bioavailability and mobility. The change of pH during the extended period of the experiment was up to $+0.25$, -0.35 , and -0.70 at pH 5.5, 7.0, and 8.5, respectively. This pH variation may be due to the inadequacy of 0.01 M HCl/NaOH solution to maintain pH stability over time. The lost Cu due to processing was found to be 0.1% weight of Cu-NPs used in each dispersions of uncoated and carbon-coated Cu-NPs at all pH and HA values (Fig. S5). This amount is considered negligible as compared to the dissolved Cu amounts presented in Fig. 6a–f; Tables S8 and S9. It is also observed that the concentration of ionic copper was decreasing as the pH increased, whereas the concentration of particulate Cu was increasing as the pH increased (Fig. S5).

The use of SAHA-5 at pH 5.5 reduced the dissolved Cu of uncoated and carbon-coated Cu-NPs of SAHA-0 by 20–50% and 3–20%, respectively as a function of time (Fig. 6a–b, d–e; Tables S10 and S11). However, SAHA-15 at pH 5.5 enhanced the dissolution of uncoated and carbon-coated Cu-NPs of SAHA-0 by 10–40% and 10–70%, respectively as a function of time (Fig. 6b–c, e–f; Tables S10 and S11). This finding demonstrates the dual function of HAs (reduction and enhancement) towards NPs dissolution (Slowey, 2010; Waples et al., 2005). On the other hand, SAHA-5 and SAHA-15 at pH 7.0 increased the dissolved Cu of uncoated Cu-NPs of SAHA-0 by 10–275% and 10–250% and carbon-coated Cu-NPs of SAHA-0 by 50–110% and 60–150%, respectively as a function of time (Fig. 6b–c, e–f; Tables S10 and S11). Furthermore, SAHA-5 and SAHA-15 at pH 8.5 increased the dissolved Cu of uncoated Cu-NPs of SAHA-0 by 0–15% and 0–75% and carbon-coated Cu-NPs of SAHA-0 by 0–40% and 0–75%, respectively as a function of time (Fig. 6b–c, e–f; Tables S10 and S11). The impact of increasing SAHA concentration on Cu dissolution may be due to the adsorption of more Cu by active binding sites of SAHA (Boudesocque et al., 2007). The analysis of this result implies that depending on its concentration HA can inhibit or enhance the dissolution of both uncoated and carbon-coated Cu-NPs at $\text{pH} < 7.0$. Thus, the application and release of uncoated and carbon-coated Cu-NPs at pH 7 in the presence of HAs may increase the dissolution of Cu-NPs and the subsequent environmental bioavailability and mobility.

4. Conclusion

The environmental stability of both uncoated and carbon-coated Cu-NPs is dependent on the type of dispersant, water chemistry, exposure time, and the presence of humic acids. Water chemistry and the presence of humic acids had minimum impact on hydrodynamic diameter and ζ -potential of both uncoated and carbon-coated Cu-NPs. Solution pH, humic acids, and time had minimum impact on aggregation of carbon-coated Cu-NPs; however, the significant effect of pH and time on aggregation of uncoated Cu-NPs was significantly attenuated by the presence of humic acids. Although cetyltrimethylammonium bromide (CTAB) is considered as an efficient dispersant to stabilize Cu-NPs, the effect descended with time for uncoated Cu-NPs. Carbon-coated Cu-NPs exhibited significant dissolution at pH 7.0 compared to uncoated Cu-NPs in all dispersions may be due to the additional carbon it acquired during coating. Humic acid concentration of 5 mg L⁻¹ inhibited Cu dissolution while a humic acid concentration of 15 mg L⁻¹ enhanced Cu dissolution at pH 5.5, respectively for the uncoated and carbon-coated Cu-NPs. Thus, the application and release of uncoated and carbon-coated Cu-NPs at pH 7 could increase the dissolved Cu amount and the subsequent environmental bioavailability and mobility to adversely affect the biotic and abiotic components of the ecosystems. The findings in this study provide information into the potential mobility and bioavailability of uncoated and carbon-coated Cu-NPs at a range of water chemistry.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

Funding

This research did not receive any specific grant from funding agencies in the public, commercial, or not-for-profit sectors.

References

- Adeleye AS, Conway JR, Perez T, Rutten P, Keller AA, 2014. Influence of extracellular polymeric substances on the long-term fate, dissolution, and speciation of copper-based nanoparticles. *Environ. Sci. Technol* 48, 12561–12568. [PubMed: 25295836]
- Adeleye AS, Keller AA, 2014. Long-term colloidal stability and metal leaching of single wall carbon nanotubes: effect of temperature and extracellular polymeric substances. *Water Res.* 49, 236–250. [PubMed: 24342047]
- Aiken GR, Hsu-Kim H, Ryan JN, 2011. Influence of dissolved organic matter on the environmental fate of metals, nanoparticles, and colloids. *Environ. Sci. Technol* 45, 3196–3201. [PubMed: 21405118]
- Al-thabaiti SA, Obaid AY, Khan Z, Bashir O, Hussain S, 2015. Cu nanoparticles: synthesis, crystallographic characterization, and stability. *Colloid Polym. Sci* 293, 2543–2554.
- Arenas-Lago D, Monikh FA, Vijver MG, Peijnenburg WJ, 2019. Dissolution and aggregation kinetics of zero valent copper nanoparticles in (simulated) natural surface waters: simultaneous effects of pH, NOM and ionic strength. *Chemosphere* 226, 841–850. [PubMed: 30974377]
- Athanassiou EK, Grass RN, Stark WJ, 2006. Large-scale production of carbon-coated copper nanoparticles for sensor applications. *Nanotechnology* 17, 1668. [PubMed: 26558576]

- Baken S, Degryse F, Verheyen L, Merckx R, Smolders E, 2011. Metal complexation properties of freshwater dissolved organic matter are explained by its aromaticity and by anthropogenic ligands. *Environ. Sci. Technol* 45, 2584–2590. [PubMed: 21405071]
- Bakshi MS, 2009. A simple method of superlattice formation: step-by-step evaluation of crystal growth of gold nanoparticles through seed–growth method. *Langmuir* 25, 12697–12705. [PubMed: 19618928]
- Balakrishnan VK, Han X, VanLoon GW, Dust JM, Toullec J, Buncel E, 2004. Acceleration of nucleophilic attack on an organophosphorothioate neurotoxin, fenitrothion, by reactive counterion cationic micelles. Regioselectivity as a probe of substrate orientation within the micelle. *Langmuir* 20, 6586–6593. [PubMed: 15274559]
- Bhattacharjee S, 2016. DLS and zeta potential—what they are and what they are not? *J. Contr. Release* 235, 337–351.
- Bojko I, Hilleret N, Scheuerlein C, 2000. Influence of air exposures and thermal treatments on the secondary electron yield of copper. *J. Vac. Sci. Technol. A* 18, 972–979.
- Boudesocque S, Guillon E, Aplincourt M, Marceau E, Stievano L, 2007. Sorption of Cu (II) onto vineyard soils: macroscopic and spectroscopic investigations. *J. Colloid Interface Sci* 307, 40–49. [PubMed: 17140594]
- Chen KL, Elimelech M, 2007. Influence of humic acid on the aggregation kinetics of fullerene (C 60) nanoparticles in monovalent and divalent electrolyte solutions. *J. Colloid Interface Sci* 309, 126–134. [PubMed: 17331529]
- Chen L, Lin CC, Kao CH, 2000. Copper toxicity in rice seedlings: changes in anti-oxidative enzyme activities, H₂O₂ level, and cell wall peroxidase activity in roots. *Bot. Bull. Acad. Sin. (Taipei)* 41, 99–103.
- Chen S, Wang ZL, Ballato J, Foulger SH, Carroll DL, 2003. Monopod, bipod, tripod, and tetrapod gold nanocrystals. *J. Am. Chem. Soc* 125, 16186–16187. [PubMed: 14692749]
- Conway JR, Adeleye AS, Gardea-Torresdey J, Keller AA, 2015. Aggregation, dissolution, and transformation of copper nanoparticles in natural waters. *Environ. Sci. Technol* 49, 2749–2756. [PubMed: 25664878]
- Cornelis G, Hund-Rinke K, Kuhlbusch T, Van den Brink N, Nickel C, 2014. Fate and bioavailability of engineered nanoparticles in soils: a review. *Crit. Rev. Environ. Sci. Technol* 44, 2720–2764.
- Csempeš F, Csáki KF, 2000. Mixed adsorption layers of uncharged polymers at particle/solution interfaces. *Langmuir* 16, 5917–5920.
- Doelsch E, Masion A, Moussard G, Chevassus-Rosset C, Wojciechowicz O, 2010. Impact of pig slurry and green waste compost application on heavy metal exchangeable fractions in tropical soils. *Geoderma* 155, 390–400.
- Eiroma K, Forsman J, Hult E-L, Auvinen A, Sipiläinen-Malm T, Alastalo A, Tapper U, Leppäniemi J, Mattila P, Lyyrinen J, 2012. Water-based carbon-coated copper nanoparticle fluid—formation of conductive layers at low temperature by spin coating and inkjet deposition. *J. Imag. Sci. Technol* 56 40501–40501-40501–40510.
- El Badawy AM, Luxton TP, Silva RG, Scheckel KG, Suidan MT, Tolaymat TM, 2010. Impact of environmental conditions (pH, ionic strength, and electrolyte type) on the surface charge and aggregation of silver nanoparticles suspensions. *Environ. Sci. Technol* 44, 1260–1266. [PubMed: 20099802]
- El Badawy AM, Scheckel KG, Suidan M, Tolaymat T, 2012. The impact of stabilization mechanism on the aggregation kinetics of silver nanoparticles. *Sci. Total Environ* 429, 325–331. [PubMed: 22578844]
- El Badawy AM, Silva RG, Morris B, Scheckel KG, Suidan MT, Tolaymat TM, 2011. Surface charge-dependent toxicity of silver nanoparticles. *Environ. Sci. Technol* 45, 283–287. [PubMed: 21133412]
- Erickson HP, 2009. Size and shape of protein molecules at the nanometer level determined by sedimentation, gel filtration, and electron microscopy. *Biol. Proced Online* 11, 32–51.
- Fondriest Environmental Inc, 2013. Fundamentals of Environmental Measurements: pH of Water. Accessed on 06/01/2019. <https://www.fondriest.com/environmental-measurements/parameters/water-quality/ph/>.

- French RA, Jacobson AR, Kim B, Isley SL, Penn RL, Baveye PC, 2009. Influence of ionic strength, pH, and cation valence on aggregation kinetics of titanium dioxide nanoparticles. *Environ. Sci. Technol* 43, 1354–1359. [PubMed: 19350903]
- Gao J, Liang C, Shen G, Lv J, Wu H, 2017. Spectral characteristics of dissolved organic matter in various agricultural soils throughout China. *Chemosphere* 176, 108–116. [PubMed: 28259078]
- Gaw S, Wilkins A, Kim N, Palmer G, Robinson P, 2006. Trace element and EDDT concentrations in horticultural soils from the Tasman, Waikato and Auckland regions of New Zealand. *Sci. Total Environ* 355, 31–47. [PubMed: 15882892]
- Giannousi K, Sarafidis G, Mourdikoudis S, Pantazaki A, Dendrinou-Samara C, 2014. Selective synthesis of Cu₂O and Cu/Cu₂O nanoparticles: antifungal activity to yeast *Saccharomyces cerevisiae* and DNA interaction *Inorg. Inside Chem.* 53, 9657–9666.
- Gunasekara AS, TenBrook PL, Palumbo AJ, Johnson CS, Tjeerdema RS, 2005. Influence of phosphate and copper on reductive dechlorination of thiobencarb in California rice field soils. *J. Agric. Food Chem* 53, 10113–10119. [PubMed: 16366703]
- Hejazy M, Koohi MK, Bassiri Mohamad Pour A, Najafi D, 2018. Toxicity of manufactured copper nanoparticles - a review. *Nanomed. Res. J* 3, 1–9.
- Iijima J, Lim J-W, Hong S-H, Suzuki S, Mimura K, Isshiki M, 2006. Native oxidation of ultra high purity Cu bulk and thin films. *Appl. Surf. Sci* 253, 2825–2829.
- Ingle AP, Duran N, Rai M, 2014. Bioactivity, mechanism of action, and cytotoxicity of copper-based nanoparticles: a review. *Appl. Microbiol. Biotechnol* 98, 1001–1009. [PubMed: 24305741]
- Jang S, Seo Y, Choi J, Kim T, Cho J, Kim S, Kim D, 2010. Sintering of inkjet printed copper nanoparticles for flexible electronics. *Scripta Mater.* 62, 258–261.
- Jindal T, Singh DK, Agarwal H, 2000. Persistence, degradation and leaching of coumaphos in soil. *J. Environ. Sci. Health B* 35, 309–320. [PubMed: 10808995]
- Johnson VE, 2013. Revised standards for statistical evidence. *Proc. Natl. Acad. Sci. U.S.A* 110, 19313–19317. [PubMed: 24218581]
- Jones EH, Su C, 2012. Fate and transport of elemental copper (Cu₀) nanoparticles through saturated porous media in the presence of organic materials. *Water Res.* 46, 2445–2456. [PubMed: 22386886]
- Keller AA, Adeleye AS, Conway JR, Garner KL, Zhao L, Cherr GN, Hong J, Gardea-Torresdey JL, Godwin HA, Hanna S, 2017. Comparative environmental fate and toxicity of copper nanomaterials. *NanoImpact* 7, 28–40.
- Keller AA, McFerran S, Lazareva A, Suh S, 2013. Global life cycle releases of engineered nanomaterials. *J. Nanoparticle Res* 15, 1692.
- Khan A, Rashid A, Younas R, Chong R, 2016. A chemical reduction approach to the synthesis of copper nanoparticles. *Int. Nano Lett.* 6, 21–26.
- Kim B, Kim YS, Kim BM, Hay AG, McBride MB, 2011. Effect of soil metal contamination on glyphosate mineralization: role of zinc in the mineralization rates of two copper-spiked mineral soils. *Environ. Toxicol. Chem* 30, 596–601. [PubMed: 21298705]
- Kloster N, Brigante M, Zanini G, Avena M, 2013. Aggregation kinetics of humic acids in the presence of calcium ions. *Colloid. Surface. Physicochem. Eng. Aspect* 427, 76–82.
- Kobayashi Y, Shirochi T, Yasuda Y, Morita T, 2012. Metal–metal bonding process using metallic copper nanoparticles prepared in aqueous solution. *Int. J. Adhesion Adhes* 33, 50–55.
- Koczkur KM, Mourdikoudis S, Polavarapu L, Skrabalak SE, 2015. Polyvinylpyrrolidone (PVP) in nanoparticle synthesis. *Dalton Trans.* 44, 17883–17905. [PubMed: 26434727]
- Lanje AS, Sharma SJ, Pote RB, Ningthoujam RS, 2010. Synthesis and optical characterization of copper oxide nanoparticles. *Adv. Appl. Sci. Res* 1, 36–40.
- Lei R, Wu C, Yang B, Ma H, Shi C, Wang Q, Wang Q, Yuan Y, Liao M, 2008. Integrated metabolomic analysis of the nano-sized copper particle-induced hepatotoxicity and nephrotoxicity in rats: a rapid in vivo screening method for nanotoxicity. *Toxicol. Appl. Pharmacol* 232, 292–301. [PubMed: 18706438]
- Li J, Liu C. y., 2009. Carbon-coated copper nanoparticles: synthesis, characterization and optical properties. *New J. Chem* 33, 1474–1477.

- Li L, Zhang H, Pang J, Lin J, 2010. Fabrication and performance of carbon coated copper nanoparticles. *Mater. Sci-Poland* 28, 181–187.
- Li X, Zhu D, Wang X, 2007. Evaluation on dispersion behavior of the aqueous copper nano-suspensions. *J. Colloid Interface Sci* 310, 456–463. [PubMed: 17395195]
- Li Z, Sahle-Demessie E, Hassan AA, Pressman JG, Sorial GA, Han C, 2017. Effects of source and seasonal variations of natural organic matters on the fate and transport of CeO₂ nanoparticles in the environment. *Sci. Total Environ* 609, 1616–1626. [PubMed: 28810513]
- Liu T-F, Cheng S, Na T, Jun H, Yang S. g., Chen C. x., 2007. Effect of copper on the degradation of pesticides cypermethrin and cyhalothrin. *J. Environ. Sci* 19, 1235–1238.
- Mandel K, Hutter F, Gellermann C, SEXTL G, 2011. Synthesis and stabilisation of superparamagnetic iron oxide nanoparticle dispersions. *Colloids Surf., A* 390, 173–178.
- McCauley A, Jones C, Jacobsen J, 2009. Soil pH and organic matter. *Nutrient management module* 8, 1–12.
- Mosa KA, El-Naggar M, Ramamoorthy K, Alawadhi H, Elnaggar A, Wartanian S, Ibrahim E, Hani H, 2018. Copper nanoparticles induced genotoxicity, oxidative stress, and changes in superoxide dismutase (SOD) gene expression in Cucumber (*Cucumis sativus*) plants. *Front. Plant Sci* 9.
- Mu Q, Jiang G, Chen L, hou H, Fourches D, Tropsha A, Yan B, 2014. Chemical basis of interactions between engineered nanoparticles and biological systems. *Chem. Rev* 114, 7740–7781. [PubMed: 24927254]
- Mulvaney P, 1996. Surface plasmon spectroscopy of nanosized metal particles. *Langmuir* 12, 788–800.
- Peng C, Shen C, Zheng S, Yang W, Hu H, Liu J, Shi J, 2017. Transformation of CuO nanoparticles in the aquatic environment: influence of pH, electrolytes and natural organic matter. *Nanomaterials* 7, 326.
- Platzman I, Brener R, Haick H, Tannenbaum R, 2008. Oxidation of polycrystalline copper thin films at ambient conditions. *J. Phys. Chem. C* 112, 1101–1108.
- Prasad PR, Kanchi S, Naidoo E, 2016. In-vitro evaluation of copper nanoparticles cytotoxicity on prostate cancer cell lines and their antioxidant, sensing and catalytic activity: one-pot green approach. *J. Photochem. Photobiol., B* 161, 375–382. [PubMed: 27318296]
- Purushothaman K, Muralidharan G, 2009. The effect of annealing temperature on the electrochromic properties of nanostructured NiO films. *Sol. Energy Mater. Sol. Cells* 93, 1195–1201.
- Rodrigues A, Brito A, Janknecht P, Proença MF, Nogueira R, 2009. Quantification of humic acids in surface water: effects of divalent cations, pH, and filtration. *J. Environ. Monit* 11, 377–382. [PubMed: 19212596]
- Sarkar A, Das J, Manna P, Sil PC, 2011. Nano-copper induces oxidative stress and apoptosis in kidney via both extrinsic and intrinsic pathways. *Toxicology* 290, 208–217. [PubMed: 22000994]
- Saterlie MS, Sahin H, Kavlicoglu B, Liu Y, Graeve OA, 2012. Surfactant effects on dispersion characteristics of copper-based nanofluids: a dynamic light scattering study. *Chem. Mater* 24, 3299–3306.
- Slowey AJ, 2010. Rate of formation and dissolution of mercury sulfide nanoparticles: the dual role of natural organic matter. *Geochem. Cosmochim. Acta* 74, 4693–4708.
- Sobek S, Tranvik LJ, Prairie YT, Kortelainen P, Cole JJ, 2007. Patterns and regulation of dissolved organic carbon: an analysis of 7,500 widely distributed lakes. *Limnol. Oceanogr* 52, 1208–1219.
- Song L, Connolly M, Fernández-Cruz ML, Vijver MG, Fernández M, Conde E, de Snoo GR, Peijnenburg WJ, Navas JM, 2014. Species-specific toxicity of copper nanoparticles among mammalian and piscine cell lines. *Nanotoxicology* 8, 383–393. [PubMed: 23600739]
- Sui Z, Chen X, Wang L, Xu L, Zhuang W, Chai Y, Yang C, 2006. Capping effect of CTAB on positively charged Ag nanoparticles. *Phys. E Low-dimens. Syst. Nanostruct* 33, 308–314.
- Suzuki S, Ishikawa Y, Isshiki M, Waseda Y, 1997. Native oxide layers formed on the surface of ultra high-purity iron and copper investigated by angle resolved XPS. *Mater. Trans., JIM* 38, 1004–1009.
- Sweeney SF, Woehrle GH, Hutchison JE, 2006. Rapid purification and size separation of gold nanoparticles via diafiltration. *J. Am. Chem. Soc* 128, 3190–3197. [PubMed: 16522099]

- Taylor AA, Walker SL, 2016. Effects of copper particles on a model septic system's function and microbial community. *Water Res.* 91, 350–360. [PubMed: 26815140]
- Temminghoff EJM, van der Zee SEATM, de Haan FAM, 1997. Copper mobility in a copper-contaminated sandy soil as affected by pH and solid and dissolved organic matter. *Environ. Sci. Technol* 31, 1109–1115.
- Umer A, Naveed S, Ramzan N, Rafique MS, 2012. Selection of a suitable method for the synthesis of copper nanoparticles. *Nano* 7 1230005-(1230001–1230018).
- Wang L-F, Habibul N, He D-Q, Li W-W, Zhang X, Jiang H, Yu H-Q, 2015. Copper release from copper nanoparticles in the presence of natural organic matter. *Water Res.* 68, 12–23. [PubMed: 25462713]
- Waples JS, Nagy KL, Aiken GR, Ryan JN, 2005. Dissolution of cinnabar (HgS) in the presence of natural organic matter. *Geochem. Cosmochim. Acta* 69, 1575–1588.
- Xiao Y, Peijnenburg WJ, Chen G, Vijver MG, 2018a. Impact of water chemistry on the particle-specific toxicity of copper nanoparticles to *Daphnia magna*. *Sci. Total Environ* 610, 1329–1335. [PubMed: 28851153]
- Xiao Y, Vijver MG, Peijnenburg WJGM, 2018b. Impact of water chemistry on the behavior and fate of copper nanoparticles. *Environ. Pollut* 234, 684–691. [PubMed: 29227954]
- Yang K, Lin D, Xing B, 2009. Interactions of humic acid with nanosized inorganic oxides. *Langmuir* 25, 3571–3576. [PubMed: 19708146]
- Yang Y, Zhang C, Hu Z, 2013. Impact of metallic and metal oxide nanoparticles on wastewater treatment and anaerobic digestion. *Environ. Sci. Process. Impact* 15, 39–48.
- Yruela I, 2009. Copper in plants: acquisition, transport and interactions. *Funct. Plant Biol* 36, 409–430. [PubMed: 32688656]
- Yu W, Xie H, Chen L, Li Y, 2010. Investigation on the thermal transport properties of ethylene glycol-based nanofluids containing copper nanoparticles. *Powder Technol.* 197, 218–221.
- Zazouli M, Nasser S, Mahvi A, Mesdaghinia A, Gholami M, 2007. Study of natural organic matter fractions in water sources of Tehran. *Pakistan J. Biol. Sci* 10, 1718–1722.
- Zhang W, Yao Y, Sullivan N, Chen Y, 2011. Modeling the primary size effects of citrate-coated silver nanoparticles on their ion release kinetics. *Environ. Sci. Technol* 45, 4422–4428. [PubMed: 21513312]
- Zhang Y, Chen Y, Westerhoff P, Crittenden J, 2009. Impact of natural organic matter and divalent cations on the stability of aqueous nanoparticles. *Water Res.* 43, 4249–4257. [PubMed: 19577783]
- Zhu J, Li D, Chen H, Yang X, Lu L, Wang X, 2004. Highly dispersed CuO nanoparticles prepared by a novel quick-precipitation method. *Mater. Lett* 58, 3324–3327.

Fig. 1.

XRD spectra of: (a) uncoated Cu-NPs and (b) carbon-coated Cu-NPs; uncoated Cu-NPs: (c) SEM image, (d) EDXA spectra, and (e) TEM image; carbon-coated Cu-NPs: (f) SEM image, (g) EDXA spectra, and (h) TEM image; uncoated and carbon-coated Cu-NPs: (i) D_h and (j) ζ -potential.

Fig. 2.

Hydrodynamic diameter of: uncoated Cu-NPs in aqueous solutions of Na⁺ (a, b, c) and Ca²⁺ (d, e, f); carbon-coated Cu-NPs in Na⁺ (g, h, i) and Ca²⁺ (j, k, l) at selected pH in the absence and presence of SRHA and SAHA. * Triplicate measurements with triplicate run (30 s per run) were taken and obtained after ~15 min of ionic strength and pH adjustments.

Fig. 3. ζ -Potential of: uncoated Cu-NPs in aqueous solutions of Na⁺ (a, b, c) and Ca²⁺ (d, e, f); carbon-coated Cu-NPs in Na⁺ (g, h, i) and Ca²⁺ (j, k, l) at selected pH in the absence and presence of SRHA and SAHA. * Triplicate measurements with triplicate run (30 s per run) were taken and obtained after ~15 min of ionic strength and pH adjustments.

Fig. 4. Hydrodynamic diameter of uncoated Cu-NPs (a, b, c) and carbon-coated Cu-NPs (d, e, f) at selected pH as a function of time in the absence and presence of SAHA.

Fig. 5. SEM images of uncoated Cu-NPs (a, b) and carbon-coated Cu-NPs (c, d) in SAHA-0 solution at pH 7 after 15 min and 3 d.

Fig. 6. Dissolved Cu ions of uncoated Cu-NPs (a, b, c) and carbon-coated Cu-NPs (d, e, f) at selected pH as a function of time in the absence and presence of SAHA.